

# AERONAUTICAL MATERIAL SPECIFICATIONS

## AMS 5759A

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 2-1-56  
Revised 1-15-60

ALLOY, CORROSION AND HEAT RESISTANT  
Cobalt Base - 20Cr - 10Ni - 15W

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Bars, forgings, flash welded rings, and stock for forgings or flash welded rings.
3. APPLICATION: Primarily for parts and assemblies requiring high strength up to approximately 1500 F and oxidation resistance up to 2000 F.
4. COMPOSITION:

		Check Analysis	
		Under Min	or Over Max
Carbon	0.05 - 0.15	0.01	0.01
Manganese	1.00 - 2.00	0.04	0.04
Silicon	1.00 max	--	0.05
Phosphorus	0.040 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	19.00 - 21.00	0.25	0.25
Nickel	9.00 - 11.00	0.15	0.15
Tungsten	14.00 - 16.00	0.10	0.10
Iron	3.00 max	--	0.10
Cobalt	remainder		

5. CONDITION:
  - 5.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated, unless otherwise specified.
    - 5.1.1 Bars shall be hot rolled.
    - 5.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with the latest issue of AMS 7490, unless otherwise specified.
  - 5.2 Stock for Forgings or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.
6. TECHNICAL REQUIREMENTS:
  - 6.1 Bars, Forgings, and Flash Welded Rings:
    - 6.1.1 Heat Treatment: The product shall be solution heat treated by heating to 2250 F  $\pm$  25, holding at heat for not less than 1 hr per inch of cross section, and either quenching in water or rapid air cooling.

Section 7C of the SAE Technical Board rules provides that: "All technical reports prepared for the use of anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

6.1.2 Hardness:

6.1.2.1 Bars: Shall have hardness not higher than Brinell 225 or equivalent when taken approximately midway between surface and center.

6.1.2.2 Forgings and Flash Welded Rings: Shall have hardness not higher than Brinell 225 or equivalent.

6.1.3 Tensile Properties: Specimens taken from bars and forgings, and from parent metal of flash welded rings shall conform to the following requirements:

Tensile Strength, psi	125,000 min
Yield Strength at 0.2% Offset	45,000 min
Elongation, % in 4D	30 min

6.1.4 Stress-Rupture Test at 1500 F: Specimens taken from bars and forgings, and from parent metal of flash welded rings, shall be capable of meeting the following requirements:

6.1.4.1 The tensile specimen maintained at 1500 F + 5 while an axial stress of 24,000 psi is applied continuously, shall not rupture in less than 24 hours. The test shall be continued, after the 24 hr, until the specimen ruptures, either maintaining the same stress or increasing the stress to not over 30,000 psi as necessary to produce rupture. In either case the elongation after rupture, measured at room temperature, shall be not less than 10% in 4D.

6.2 Stock for Forging and Flash Welding: When a sample of stock is forged to a test coupon and heat treated as in 6.1.1, specimens taken from the heat treated coupon shall conform to the requirements of 6.1.2, 6.1.3, and 6.1.4. If specimens taken from the stock after heat treatment as in 6.1.1 conform to the requirements of 6.1.2, 6.1.3, and 6.1.4, the tests shall be accepted as equivalent to tests of the forged coupon.

7. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

8. TOLERANCES: Unless otherwise specified, tolerances for bars shall conform to the latest issue of AMS 2241 as applicable to hot finished.

9. REPORTS:

9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each size from each heat to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat. If forgings are supplied, the part number and size of stock used to make the forgings shall also be included.