

**ADOPTION NOTICE**

SAE-AMS5768, "ALLOY, CORROSION AND HEAT RESISTANT, BARS, FORGINGS, AND RINGS 21CR - 20NI - 20CO - 3.0MO - 2.5W - 1.0CB - 0.15N - 31FE SOLUTION AND PRECIPITATION HEAT TREATED", was adopted on 17-MAR-89 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Supply Center Philadelphia, ATTN: DSCP-ILEA, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Copies of this document may be purchased from the Society of Automotive Engineers 400 Commonwealth Drive Warrendale, Pennsylvania, United States, 15096-0001. <http://www.sae.org/>

**Custodians:**

Army - MR  
Navy - AS  
Air Force - 11  
DLA - IS

**Adopting Activity:**

DLA - IS

SAENORM.COM : Click to view the full PDF of ams5768j

**FSC 9510**

**DISTRIBUTION STATEMENT A:** Approved for public release; distribution is unlimited.

# AEROSPACE MATERIAL SPECIFICATION



AMS 5768J

Issued MAY 1948  
Revised JAN 1994  
Reaffirmed SEP 2000

Superseding AMS 5768H

Alloy, Corrosion and Heat Resistant, Bars, Forgings, and Rings  
21Cr - 20Ni - 20Co - 3.0Mo - 2.5W - 1.0Cb - 0.15N - 31Fe  
Solution and Precipitation Heat Treated

UNS R30155

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion and heat resistant iron-chromium-nickel-cobalt alloy in the form of bars, wire, forgings, flash welded rings, and stock for forging, flash welded rings, or heading.

### 1.2 Application:

These products have been used typically for parts, such as turbine rotors, shafts, blades, and bolts, requiring high strength up to 1350 °F (732 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys.
AMS 2261	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars Rods and Wire
MAM 2261	Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Bars Rods and Wire
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
AMS 2750	Pyrometry

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

Distributed under license from the IHS Archive

## 2.1 (Continued):

- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- AMS 7490 Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys or Precipitation Hardenable Alloys

## 2.2 ASTM Publications:

- ASTM E 10 Brinell Hardness of Metallic Materials
- ASTM E 139 Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.08	0.16
Manganese	1.00	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.00	22.50
Nickel	19.00	21.00
Cobalt	18.50	21.00
Molybdenum	2.50	3.50
Tungsten	2.00	3.00
Columbium	0.75	1.25
Tantalum (see 3.1.2)	--	0.050
Nitrogen	0.10	0.20
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.1.2 Determination not required for routine acceptance.

3.2 Condition::

The product shall be supplied in the following condition:

3.2.1 Bars, Wire, Forgings, and Flash Welded Rings: Solution and precipitation heat treated and descaled.

3.2.1.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging, Flash Welded Rings, or Heading: As ordered by the forging, flash welded ring, or heading manufacturer.

3.3 Heat Treatment:

Bars, wire, forgings, and flash welded rings shall be solution heat treated by heating to 2150 °F ± 25 (1177 °C ± 14), holding at heat for not less than 60 minutes, and quenching in water and precipitation heat treated by heating to 1500 °F ± 25 (816 °C ± 14), holding at heat for not less than 4 hours and cooling in air. Pyrometry shall be in accordance with AMS 2750.

### 3.4 Properties:

The product shall conform to the following requirements:

#### 3.4.1 Bars, Wire, Forgings, and Flash Welded Rings:

3.4.1.1 Hardness: Shall be 192 to 241 HB, or equivalent, determined in accordance with ASTM E 10 (see 8.2).

3.4.1.2 Stress-Rupture Properties at 1350 °F (732 °C): A tensile specimen, maintained at 1350 °F  $\pm$  3 (732 °C  $\pm$  2) while a load sufficient to produce an initial axial stress of 32.0 ksi (221 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 4D. Tests shall be conducted in accordance with ASTM E 139.

3.4.1.2.1 The test of 3.4.1.2 may be conducted using a load higher than required to produce an initial axial stress of 32.0 ksi (221 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.1.2.

3.4.1.2.2 The test of 3.4.1.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 32.0 ksi (221 MPa) shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 to 16 hours, preferably 8 to 10 hours thereafter, the stress shall be increased in increments of 2000 psi (14 MPa). Elongation requirements shall be as specified in 3.4.1.2.

3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1 and 3.4.1.2. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1 and 3.4.1.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4.3 Stock for Flash Welded Rings or Heading: Specimens taken from the stock after heat treatment as in 3.3 shall conform to the requirements of 3.4.1.1 and 3.4.1.2.

### 3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

### 3.6 Tolerances:

Bars, and wire, shall conform to all applicable requirements of AMS 2261 or MAM 2261.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

##### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hardness (3.4.1.1) of each lot of bars, wire, forgings, and flash welded rings.

4.2.1.3 Tolerances (3.7) of bars, and wire.

4.2.2 Periodic Tests: Tests for the following requirements are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.2.1 Stress-rupture properties (3.4.1.2) of bars, wire, forgings, and flash welded rings.

4.2.2.2 Ability of forging stock (3.4.2) and stock for flash welded rings or heading (3.4.3) to develop required properties.

##### 4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars, Wire, Flash Welded Rings, and Stock for Forgings, Flash Welded Rings, or Heading: AMS 2371

4.3.2 Forgings: AMS 2374

##### 4.4 Reports:

4.4.1 The vendor of bars, wire, forgings, and flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for hardness of each lot and, when performed, the results of tests for stress-rupture properties. This report shall include the purchase order number, heat and lot number, AMS 5768J, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.