



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS 5771A

Superseding AMS 5771

Issued 5-15-71  
Revised 7-16-79

UNS N10003

ALLOY BARS, FORGINGS, AND RINGS, CORROSION AND HEAT RESISTANT  
74Ni - 7.0Cr - 16.5Mo

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.
- 1.2 Application: Primarily for parts such as turbine air-sealing components requiring moderate strength up to 1400° F (760° C) and oxidation resistance up to 1600° F (870° C), particularly where a low coefficient of expansion is desirable.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2261 - Tolerances, Nickel, Nickel Base, and Cobalt Base Alloy Bars and Forging Stock  
AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys  
AMS 2350 - Standards and Test Methods  
AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings  
AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock  
AMS 2375 - Control of Forgings Requiring First-Article Approval  
AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys  
AMS 2808 - Identification, Forgings  
AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E10 - Brinell Hardness of Metallic Materials  
ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials  
ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and published, are advisory only. Their use by anyone engaged in industry or trade or the use of any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.3 Government Publications: Available from Commanding Officer, Naval Publication and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.04	0.08
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.015
Sulfur	--	0.020
Chromium	6.00	8.00
Molybdenum	15.75	17.25
Cobalt	--	0.20
Tungsten	--	0.50
Aluminum + Titanium	--	0.50
Boron	--	0.01
Iron	--	5.00
Copper	--	0.35
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated and descaled.

3.2.1.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment: Bars, forgings, and flash welded rings shall be solution heat treated by heating to 2150°F ± 25 (1175°C ± 15), holding at heat for 30 - 60 min., and cooling rapidly in air.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Hardness: Shall be not higher than 255 HB or equivalent, determined in accordance with ASTM E10.

- 3.4.1.2 Stress-Rupture Properties at 1500° F (816° C): A tensile test specimen, maintained at 1500° F  $\pm$  3 (816° C  $\pm$  2) while a load sufficient to produce an initial axial stress of 13,500 psi (93 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 4D. Test shall be conducted in accordance with ASTM E139.
- 3.4.1.2.1 The test of 3.4.1.2 may be conducted using a load higher than required to produce an initial axial stress of 13,500 psi (93 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.1.2.
- 3.4.1.2.2 When permitted by purchaser, the test of 3.4.1.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 13,500 psi (93 MPa) shall be used to rupture or for 23 hr, whichever occurs first. After the 23 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 2,000 psi (13.8 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.1.2.
- 3.4.2 Stock for Forging or Flash Welded Rings: When a sample of stock is forged to a test coupon and solution heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1 and 3.4.1.2. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1 and 3.4.1.2, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 24 ft (1.8 - 7.3m) but not more than 25% of any shipment shall be supplied in lengths of 6 - 9 ft (1.8 - 2.7m) except that for bars weighing over 25 lb per ft (37.2 kg/m), short lengths down to 2 ft (610 mm) may be supplied.
- 3.7 Tolerances: Unless otherwise specified, tolerances for bars and forging stock shall conform to all applicable requirements of AMS 2261.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot.
- 4.2.1.1 Composition (3.1) of the product.
- 4.2.1.2 Hardness (3.4.1.1) and stress-rupture properties (3.4.1.2) of bars and forgings.
- 4.2.1.3 Tolerances (3.6) of bars and forging stock.
- 4.2.2 Periodic Tests: Tests of forging stock to demonstrate ability to develop required properties (3.4.1.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of forgings to a purchaser, when a change in material or processing requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars, Flash Welded Rings and Stock for Flash Welded Rings: AMS 2371.

4.3.1.1 Specimens for stress-rupture tests of flash welded rings shall be cut from parent metal not including the weld-heat-affected zone.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and the results of tests for hardness and stress-rupture properties of each size from each heat. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat. If forgings are supplied, the part number and size of stock used to make the forgings shall also be included.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: Shall be in accordance with the following:

4.6.1 Bars, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.

4.6.2 Forgings and Forging Stock: AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars: In accordance with AMS 2806.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Flash Welded Rings and Stock for Forging or Flash Welded Rings: As agreed upon by purchaser and vendor.

5.2 Packaging: