



AEROSPACE MATERIAL SPECIFICATION

AMS 5777A

Superseding AMS 5777

Issued 1-15-57

Revised 12-15-74

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

WELDING ELECTRODES, COATED, STEEL, CORROSION RESISTANT 12.5Cr

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel wire in the form of coated welding electrodes.

1.2 Application: Primarily for welding corrosion-resistant steels of composition similar to that of the deposited metal.

1.3 Classification: The electrodes covered by this specification are classified as follows:

Type A - DC

Type B - DC-AC

1.3.1 When DC is specified, reverse polarity (electrode positive) is required.

1.3.2 If no type is specified, Type B shall be supplied.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pennsylvania 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 5504 - Steel Sheet, Strip, and Plate, Corrosion and Moderate Heat Resistant,
12.5Cr (SAE 51410)

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other
Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.4 AWS Publication: Available from American Welding Society, 2501 Northwest 7th Street, Miami, Florida 33125.

AWS A5.4 - Corrosion Resisting Chromium and Chromium-Nickel Steel Covered Welding
Electrodes

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Weld metal deposited from electrodes shall conform to the following in percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

∅	min	max
Carbon	--	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.025
Sulfur	--	0.015
Phosphorus + Sulfur	--	0.030
Chromium	11.50 - 13.50	
Nickel	--	0.75
Molybdenum	--	0.50
Aluminum	--	0.05
Copper	--	0.50
Tin	--	0.05

- 3.1.1 Weld Pads for Chemical Analysis: The referee procedure for making pads of weld metal and removing samples for chemical analysis shall be AWS A5.4 except that samples shall not be removed from within 1/2 in. (12.7 mm) of the base plate, unless the base plate is similar in composition to the core wire, in which case samples may be removed from as close as 1/4 in. (6.4 mm) to the base plate.

3.2 Properties:

- 3.2.1 Weldability: Electrodes shall flow evenly and smoothly under the conditions shown in 1.3 and shall be capable of producing acceptable welds determined by a procedure agreed upon by purchaser and vendor.
- 3.2.2 Response to Heat Treatment: Weld metal deposits approximately 0.250 in. (6.35 mm) in thickness deposited on AMS 5504 sheet shall attain hardness of 35 - 45 HRC or equivalent, determined in accordance with ASTM E18, after being heated to 1750° F ± 15 (954.4° C ± 8.3), hold at heat for 15 - 30 min., and cooled in still air.
- 3.2.3 Burn-Off: The coating shall be consumed uniformly on all sides and shall not burn back from the core wire under proper welding conditions. Heating of the electrode during welding shall not cause injurious blistering of the coating within the ranges of current values recommended by the manufacturer.
- 3.2.4 Grip Portion and Arc Ends: A portion of the electrode 0.75 - 1.25 in. (19.0 - 31.8 mm) long on end grip rods and 1.5 - 2.0 in. (38 - 51 mm) long on center grip rods shall be bare to permit good electrical contact with the electrode holder. The arc end of the electrodes shall be sufficiently bare to permit easy striking of the arc, but the length of this bare section as measured from the end of the electrode to the point where the full cross-section of the coating begins shall not exceed the diameter of the bare wire, and in no case shall it exceed 1/8 in. (3.2 mm).
- 3.2.5 Cleaning: Slag produced during welding shall be readily removable with hand tools.
- ### 3.3 Quality:
- 3.3.1 Core Wire: Shall be uniform in quality and condition, cylindrical, clean, sound and free from foreign materials and from imperfections detrimental to weld quality.

3.3.2 Coating: Shall be uniform in quality, tightly adherent, and free from abnormal scabs, blisters, pock-marks, bruises, and other surface defects and shall withstand normal handling without damage. It shall not be harmfully hygroscopic and shall not adversely affect weld quality.

3.4 Standard Sizes and Lengths: Shall be as shown in Table I.

TABLE I

Nominal Diameter of Core Wire Inch	Length Inches
3/64	6
1/16, 5/64, 3/32	9, 12, and 18
1/8, 5/32, 3/16, 1/4	14

TABLE I (SI)

Nominal Diameter of Core Wire Millimetres	Length Millimetres
1.2	152
1.6, 2.0, 2.4	229, 305, 457
3.2, 4.0, 4.8, 6.4	356

3.4.1 Unless otherwise specified, end grip electrodes shall be supplied in all lengths except 18 in. (457 mm), where center grip electrodes are required.

3.5 Tolerances:

3.5.1 Unless otherwise specified, electrodes shall not vary in length more than $\pm 1/8$ in. (± 3.2 mm) from the length ordered.

3.5.2 Electrode core wire shall not vary in diameter more than ± 0.002 in. (± 0.05 mm) from the size ordered.

3.5.3 Over-all diameter of the coated electrodes shall not vary more than 4% from that of the approved sample.

3.5.4 Coating shall be concentric with the core wire to the extent that the maximum core-plus-one-coating dimension shall not exceed the minimum core-plus-one-coating dimension by more than 5% of the minimum core-plus-one-coating dimension.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the electrodes shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the electrodes conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), response to heat treatment (3.2.2), grip portion and arc ends (3.2.4), size (3.4), and tolerance (3.5) requirements are classified as acceptance or routine control tests.

4.2.2 Qualification Tests: Tests to determine conformance to weldability (3.2.1), burn-off (3.2.3), and
Ø cleaning (3.2.5) requirements are classified as qualification or periodic control tests.

Ø 4.3 Sampling: Shall be as agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample electrodes shall be approved by purchaser before electrodes for production use are supplied, unless such approval be waived.

4.4.2 Vendor shall use materials, manufacturing procedures, processes, and methods of inspection on production electrodes which are essentially the same as those used on the approved sample electrodes. If necessary to make any change in coating formulation or in manufacturing procedures, processes,
Ø or methods of inspection which could affect quality or properties of the electrodes, vendor shall submit for reapproval a statement of the revised procedures and, when requested, sample electrodes. No production electrodes incorporating the revised procedures shall be shipped prior to receipt of reapproval.

4.5 Reports:

4.5.1 The vendor of the electrodes shall furnish with each shipment three copies of a report stating that the electrodes conform to the technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, control number, size, and quantity. Control number shall be a designation indicating batch processing and core wire heat number. When requested by the purchaser, the vendor shall also include in the report the composition of the deposited weld metal for each heat in the shipment.

4.5.2 When assemblies requiring use of these electrodes are to be supplied, the assembly manufacturer shall inspect each lot of electrodes to determine conformance to the requirements of this specification and shall furnish with each shipment three copies of a report stating that the electrodes conform. This report shall include the purchase order number, material specification number and its revision letter, assembly number, and quantity.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the electrodes may be based on the results of testing three additional specimens
Ø for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the electrodes represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 Individual Electrodes:

5.1.1.1 At least one legible imprint of the AWS classification (E410) shall be applied to the electrode coating as near as practical to the grip end of the core wire and within 2-1/2 in. (63.5 mm) of the grip
Ø end. In the case of center grip electrodes, the imprint shall be applied to the electrode coating as above and upon both sides of the center grip (bare core wire) area. The prefix letter E in the electrode classification may be omitted from the imprint on the electrode coating.

5.1.1.2 The numbers of the imprinted electrode classification shall be of bold block type and of sufficient
Ø size and color contrast to be legible before and after normal welding applications.

5.1.2 Electrode Packages: Each package or container shall be legibly marked with the following information: Purchase order number, AMS 5777A, control number, size, quantity, type designation, recommended current value, and manufacturer's designation.