



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS5805™</b>	<b>REV. K</b>
	Issued 1962-01 Reaffirmed 2006-10 Revised 2024-03  Superseding AMS5805J	
Steel, Corrosion- and Heat-Resistant, Welding Wire 15Cr - 25.5Ni - 1.2Mo - 2.1Ti - 0.004B - 0.30V Vacuum Induction Melted, Environment Controlled Packaging (Composition similar to UNS S66286)		

### RATIONALE

AMS5805K is the result of a Five-Year Review and update of the specification. The revision updates composition testing and reporting (see 3.1, 3.1.2, and 3.1.3), adds country of origin to reporting requirements (see 4.4), and updates the exceptions requirements (see 8.4).

#### 1. SCOPE

##### 1.1 Form

This specification covers a corrosion- and heat-resistant steel in the form of welding wire.

##### 1.2 Application

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of critical weldments of precipitation-hardenable, corrosion- and heat-resistant steels of similar composition where the weld area is required to have strength and corrosion resistance comparable to those of the parent metal, but usage is not limited to such application.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2248 Chemical Check Analysis Limits, Corrosion- and Heat-Resistant Steels and Alloys, Maraging and Other Highly Alloyed Steels, and Iron Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS2814 Packaging and Marking of Packages of Welding Wire, Premium Quality

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/contentAMS5805K>

AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition, Inspection of Welding Wire
AS7766	Terms Used in Aerospace Metals Specifications

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM A751 Chemical Analysis of Steel Products

## 2.3 Definitions

Terms used in AMS are defined in AS7766.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Wire Composition

Wire shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751 or by other analytical methods acceptable to the purchaser.

**Table 1 - Composition**

Element	Min	Max
Carbon (3.1.1)	--	0.04
Manganese	--	0.35
Silicon	--	0.25
Phosphorus	--	0.01
Sulfur	--	0.005
Chromium	13.50	16.00
Nickel	24.00	27.00
Molybdenum	1.00	1.50
Titanium	1.90	2.30
Boron	0.003	0.005
Vanadium	0.10	0.50
Cobalt	--	1.00
Aluminum	--	0.35
Oxygen (3.1.2)	--	0.005 (50 ppm)
Nitrogen (3.1.2)	--	0.005 (50 ppm)
Hydrogen (3.1.2)	--	0.0005 ( 5 ppm)

3.1.1 Carbon content shall be determined on finished wire.

3.1.2 Except for hydrogen, nitrogen, and oxygen, chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements. Hydrogen, nitrogen, and oxygen shall be determined on each lot at finished diameter.

3.1.3 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection, unless limits of acceptability are specified by the purchaser.

#### 3.1.4 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248. No variation is permitted for oxygen, nitrogen, or hydrogen.

#### 3.2 Melting Practice

Alloy shall be vacuum induction melted; it may be vacuum arc remelted, but remelting is not required.

#### 3.3 Condition

Cold finished, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

#### 3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not tear the wire surfaces are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 Butt welding is permissible only at diameters larger than final finished product size provided both ends to be joined are alloy verified using a method capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.

3.4.3 In-process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or protective atmospheres to ensure freedom from surface oxidation and absorption of other extraneous materials.

3.4.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed by cleaning processes that will neither result in pitting nor cause gas adsorption by the wire or deposition of substances harmful to welding operations.

#### 3.5 Properties

Wire shall conform to the following requirements:

##### 3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds determined by a procedure agreed upon by the purchaser and producer. The referee method of ARP1876 may be used to resolve weldability disputes.

##### 3.5.2 Spooled Wire

Shall conform to 3.5.2.1, 3.5.2.2, and 3.5.2.3.

###### 3.5.2.1 Winding

Filler metal in coils and on spools shall be wound so that kinks, waves, sharp bends, overlapping, or wedging are not encountered, leaving the filler metal free to unwind without restriction. The outside end of the electrode (the end where welding is to begin) shall be identified so it can be located readily and shall be fastened to avoid unwinding. The winding shall be level winding.

## 3.5.2.2 Cast

Wire, wound on standard diameter spools as shown in Table 2 shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle (cast) within the limits shown in Table 2.

## 3.5.2.3 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than shown in Table 2.

**Table 2A - Cast and helix requirements, inch-pound units**

Spool Diameter Inches	Cast-Diameter Inches		Helix Inches
	Min	Max	Max
4	2.5	15	0.5
8	8	50	1
12	15	50	1

**Table 2B - Cast and helix requirements, SI units**

Spool Diameter Millimeters	Cast Millimeters		Helix Millimeters
	Min	Max	Max
100	65	380	13
200	200	1300	25
300	380	1300	25

## 3.6 Quality

Wire, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

## 3.7 Sizes and Tolerances

Wire shall be furnished in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

## 3.7.1 Diameter

Shall be as shown in Table 3.

**Table 3A - Sizes and diameter tolerances, inch/pound units**

Form	Nominal Diameter Inches	Tolerance
		Inch Plus and Minus
Cut Lengths	0.030, 0.035, 0.045	0.001
Cut Lengths	0.062, 0.078, 0.094, 0.125, 0.156, 0.187	0.002
Spools	0.007, 0.010, 0.015	0.0005
Spools	0.020, 0.030, 0.035, 0.045	0.001
Spools	0.062, 0.078, 0.094	0.002

**Table 3B - Sizes and diameter tolerances, SI units**

Form	Nominal Diameter Millimeters	Tolerance Millimeter Plus and Minus
Cut Lengths	0.76, 0.89, 1.14	0.025
Cut Lengths	1.57, 1.98, 2.39, 3.18, 3.96, 4.75	0.05
Spools	0.18, 0.25, 0.38	0.013
Spools	0.51, 0.76, 0.89, 1.14	0.025
Spools	1.57, 1.98, 2.39	0.05

### 3.7.2 Length

Cut Lengths shall be furnished in 18-, 27-, or 36-inch (457-, 686-, or 914-mm) lengths, or other lengths when specified by the purchaser, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

### 3.8 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of wire shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

### 4.2 Classification of Tests

4.2.1 Composition (see 3.1), sizes and tolerances (see 3.7), and alloy verification (see 5.2) are acceptance tests and shall be performed on each heat or lot as applicable.

### 4.2.2 Periodic Tests

Weldability (see 3.5.1), cast (see 3.5.2.2), and helix (see 3.5.2.3) are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

### 4.3 Sampling and Testing

Shall be in accordance with AMS2371.

### 4.4 Reports

The producer of wire shall furnish with each shipment a report showing the producer's name, country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations), the results of tests for chemical composition of each heat or lot as applicable, and stating that the wire conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5805K, nominal size, form, and quantity.

4.4.1 When material produced to this specification has exceptions authorized by the purchaser taken to the technical requirements listed in Section 3 (see 5.3.1), the report shall contain a statement "This material is certified as AMS5805K(EXC) because of the following exceptions:" and the specific exceptions shall be listed.