



AEROSPACE MATERIAL SPECIFICATION	AMS5811™	REV. E
	Issued 1984-07 Revised 2018-04 Reaffirmed 2022-11	
Superseding AMS5811D		
Steel, Corrosion- and Heat-Resistant, Welding Wire 15Cr - 30Ni - 1.2Mo - 2.2Ti - 0.25Al - 0.001B - 0.030V (0.01 - 0.03C) Vacuum Induction Melted, Environment Controlled Packaging		

RATIONALE

AMS5811E revises chemical analysis standard (3.1), fabrication (3.4.2), length (3.7.2), reports (4.4 and 4.4.1), and identification (5.3.1), and results from a Five-Year Review and update to this document.

AMS5811E has been reaffirmed to comply with the SAE Five-Year Review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat resistant steel in the form of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-metal-arc welding or gas-tungsten-arc of critical weldments of precipitation-hardenable, corrosion and heat resistant steels of similar composition where the weld area is required to have strength and corrosion resistance comparable to those of the parent metal, but usage is not limited to such applications. This filler metal provides joints with increased crack resistance over those using AMS5805 wire when welding similar steels.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2248 Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5811E/>

AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
AMS5805	Steel, Corrosion and Heat Resistant, Welding Wire, 15Cr - 25.5Ni - 1.20Mo - 2.1Ti - 0.004B - 0.30V, Vacuum Induction Melted, Environment Controlled Packaging
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

3. TECHNICAL REQUIREMENTS

3.1 Composition

Wire shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	0.01	0.03
Manganese	--	0.20
Silicon	--	0.10
Phosphorus	--	0.006
Sulfur	--	0.005
Chromium	13.50	16.00
Nickel	29.00	31.00
Molybdenum	1.00	1.50
Titanium	2.00	2.30
Aluminum	0.15	0.35
Boron	0.0005	0.002
Vanadium	0.10	0.50
Oxygen	--	0.005 (50 ppm)
Nitrogen	--	0.005 (50 ppm)
Hydrogen	--	0.0005 (5 ppm)

3.1.1 Except for hydrogen, nitrogen, and oxygen, chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements. Hydrogen, nitrogen, and oxygen shall be determined on each lot at finished diameter.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248. No variation over maximum is permitted for oxygen, nitrogen, or hydrogen.

3.2 Melting Practice

Alloy shall be vacuum induction melted; it may be vacuum arc remelted, but remelting is not required.

3.3 Condition

Cold drawn, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not tear the wire surfaces are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 Butt welding is permissible only at diameters larger than final finished product size provided both ends to be joined are alloy verified using a method capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.

3.4.3 In-process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or protective atmospheres to ensure freedom from surface oxidation and absorption of other extraneous materials.

3.4.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed by cleaning processes that will neither result in pitting nor cause gas adsorption by the wire or deposition of substances harmful to welding operations.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds determined by a procedure agreed upon by purchaser and producer. The referee method of ARP1876 may be used to resolve weldability disputes.

3.5.2 Spooled Wire

Shall conform to 3.5.2.1, 3.5.2.2, and 3.5.2.3.

3.5.2.1 Winding

Filler metal in coils and on spools shall be wound so that kinks, waves, sharp bends, overlapping, or wedging are not encountered, leaving the filler metal free to unwind without restriction. The outside end of the electrode (the end where welding is to begin) shall be identified so it can be located readily and shall be fastened to avoid unwinding. The winding shall be level winding.

3.5.2.2 Cast

Wire, wound on standard diameter spools as shown in Table 2 shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle (cast) within the limits shown in Table 2.

3.5.2.3 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than shown in Table 2.

Table 2**Table 2A - Cast and helix requirements – inch-pound units**

Spool Diameter Inches	Cast-Diameter Inches		Helix Inches Max
	Min	Max	
4	2.5	15	0.5
8	8	50	1
12	15	50	1

Table 2B - Cast and helix requirements – SI units

Spool Diameter Millimeters	Cast Millimeters		Helix Millimeters Max
	Min	Max	
100	65	380	13
200	200	1300	25
300	380	1300	25

3.6 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances

Wire shall be furnished in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter

Shall be as shown in Table 3.

Table 3**Table 3A - Sizes and diameter tolerances, inch/pound units**

Form	Nominal Diameter Inch	Tolerance
		Inch Plus and Minus
Cut Lengths	0.030, 0.035, 0.045	0.001
Cut Lengths	0.062, 0.078, 0.094, 0.125, 0.156, 0.187	0.002
Spools	0.007, 0.010, 0.015	0.0005
Spools	0.020, 0.030, 0.035, 0.045	0.001
Spools	0.062, 0.078, 0.094	0.002

Table 3B - Sizes and diameter tolerances, SI units

Form	Nominal Diameter Millimeters	Tolerance Millimeter Plus and Minus
Cut Lengths	0.76, 0.89, 1.14	0.025
Cut Lengths	1.57, 1.98, 2.39, 3.18, 3.96, 4.75	0.05
Spools	0.18, 0.25, 0.38	0.013
Spools	0.51, 0.76, 0.89, 1.14	0.025
Spools	1.57, 1.98, 2.39	0.05

3.7.2 Length

Cut lengths shall be furnished in 18, 27, or 36-inch (457, 686, or 914-mm) lengths, or other lengths when specified by purchaser, and shall not vary more than +0, 0.5 inch (13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of wire shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), sizes and tolerances (3.7), and alloy verification (5.2) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Weldability (3.5.1), cast (3.5.2.2), and helix (3.5.2.3) are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2371.

4.4 Reports

The producer of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat or lot as applicable and stating that the wire conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5811E, nominal size, form, and quantity.

4.4.1 When material produced to this specification has exceptions taken to the technical requirements listed in Section 3 (see 5.3.1), the report shall contain a statement "This material is certified as AMS5811E(EXC) because of the following exceptions." and the specific exceptions shall be listed.

4.5 Resampling and Retesting

Shall be in accordance with AMS2371.