

AEROSPACE MATERIAL SPECIFICATION



AMS 5825F

Issued JAN 1962
Revised OCT 2000

Superseding AMS 5825E

Steel, Corrosion Resistant, Welding Wire
16.4Cr - 4.8Ni - 0.22Cb - 3.6Cu

UNS S17480

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of welding wire.

1.2 Application:

This wire has been used typically as bare wire filler metal for gas-tungsten-arc or gas-metal-arc welding of parts fabricated from steels having composition similar to that of this wire, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS 2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS 2816	Identification, Welding Wire, Tab Marking Method
AMS 2819	Identification, Welding Wire, Direct Color Code System

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 5643 Steel Bars, Forgings, Tubing, and Rings, Corrosion Resistant, 16Cr - 4.0Ni - 0.30(Cb+Ta) - 4.0Cu, Solution Heat Treated

ARP1876 Weldability Test for Weld Filler Metal Wire

ARP4926 Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2969.

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Wire Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.05
Manganese	0.25	0.75
Silicon	--	0.75
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	16.00	16.75
Nickel	4.50	5.00
Columbium	0.15	0.30
Copper	3.25	4.00
Molybdenum	--	0.75

3.1.1 Chemical analysis of initial bar or rod stock before drawing is acceptable provided the process used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.

3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

Cold worked, bright finished, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

- 3.2.1 All wire shall have a smooth finish that is free from slivers, depressions, scratches, scale, seams, laps, and foreign matter that would adversely affect welding characteristics, operation of the welding equipment, or properties of the weld metal.

3.3 Fabrication:

- 3.3.1 In-process annealing between cold rolling or drawing operations shall be performed in vacuum or a protective atmosphere to avoid surface oxidation and absorption of other extraneous elements.
- 3.3.2 Butt welding is permissible provided both ends to be joined are alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed within the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.
- 3.3.3 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or properties of the weld metal, shall be removed by a cleaning process that will not result in pitting or gas absorption by the wire nor deposit substances harmful to welding operations.

3.4 Properties:

Wire shall conform to the following requirements:

- 3.4.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.
- 3.4.2 Response to Heat Treatment: Weld metal, approximately 1/4 inch (6.4 mm) in thickness, deposited on AMS 5643 steel shall attain hardness not lower than 38 HRC, or equivalent (See 8.2), determined in accordance with ASTM E 18, after being solution heat treated by heating to 1900 °F ± 25 (1038 °C ± 14), holding at heat for not less than 30 minutes, and cooling to below 60 °F (16 °C) and precipitation heat treated by heating to 900 °F ± 10 (482 °C ± 6), holding at heat for 60 minutes ± 5, and cooling in air.
- 3.4.3 Spooled Wire: Shall conform to 3.4.3.1 and 3.4.3.2.
- 3.4.3.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1 inch (25 mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.4.3.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in Table 2 and 3.6.2.

3.6.1 Diameter:

TABLE 2A - Standard Diameters and Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance	Tolerance
		Inch Plus	Inch Minus
Cut Lengths	0.030, 0.035, 0.045	0.001	0.001
Cut Lengths	0.062, 0.078, 0.094, 0.125, 0.156, 0.187	0.002	0.002
Spools	0.007, 0.010, 0.015	0.0005	0.0005
Spools	0.020, 0.030, 0.035, 0.045	0.001	0.001
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE 2B - Standard Diameters and Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance	Tolerance
		Millimeter Plus	Millimeter Minus
Cut Lengths	0.76, 0.89, 1.14	0.025	0.025
Cut Lengths	1.57, 1.98, 2.39, 3.18, 3.96, 4.75	0.05	0.05
Spools	0.18, 0.25, 0.38	0.013	0.013
Spools	0.51, 0.76, 0.89, 1.14	0.025	0.025
Spools	1.57, 1.98, 2.39	0.05	0.05

3.6.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.