

AMS 5826

ADOPTION NOTICE

AMS 5826 "Steel, Corrosion and Heat Resistant, Welding Wire 15Cr - 5.1Ni - 0.30Cb - 3.2Cu" was adopted on 14 September 1994 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Air Force, ASC/ENOSD, Building 125, 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH 45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:
Army - MR
Navy - AS
Air Force - 11

Adopting Activity:
Air Force - 11
(Proj No. 3439-0856)

Review activities:
AF - 99

SAENORM.COM : Click to view the full PDF of [ams5826b](#)

AMSC N/A

FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 5826B

Issued JAN 1982

Revised APR 1994

Superseding AMS 5826A

Submitted for recognition as an American National Standard

STEEL, CORROSION AND HEAT RESISTANT, WELDING WIRE
15Cr - 5.1Ni - 0.30Cb - 3.2Cu

UNS S15500

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of steels of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248 Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS 2813 Packaging and Marking of Packages of Welding Wire, Standard Method

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5826B

SAE

AMS 5826B

2.1 (Continued):

AMS 2814 Packaging and Marking of Packages of Welding Wire, Premium Quality
 AMS 2816 Identification, Welding Wire, Tab Marking Method
 AMS 2819 Identification, Welding Wire, Direct Color Code System

ARP1876 Weldability Test for Weld Filler Metal Wire

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.025	0.050
Manganese	0.25	0.75
Silicon	--	0.60
Phosphorus	--	0.020
Sulfur	--	0.010
Chromium	14.40	15.30
Nickel	4.75	5.50
Columbium	5XC	0.40
Copper	3.00	3.50
Molybdenum	--	0.30
Tantalum (3.1.1)	--	0.05
Aluminum	--	0.025
Oxygen	--	0.01 (100 ppm)
Nitrogen	--	0.040 (400 ppm)
Hydrogen	--	0.0006 (6 ppm)

3.1.1 Determination not required for routine acceptance.
 (R)

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

AMS 5826B

SAE

AMS 5826B

3.2 Condition:

(R)

Cold worked, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.2.2 In-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.

3.2.3 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.3 Properties:

Wire shall conform to the following requirements:

3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.3.2.2.

3.3.2.1 Cast: Wire, wound on standard 12-inch (308-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.

AMS 5826B

SAE

AMS 5826B

3.5.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Sizes and Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerances Inch Plus	Tolerance Inch Minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE 2B - Sizes and Diameter Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerances Millimeter Plus	Tolerance Millimeter Minus
Cut Lengths	0.76, 1.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than + 0, - 0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), sizes and tolerances (3.5), and alloy verification (5.2.1) are acceptance tests and shall be performed on each heat or lot as applicable.

(R)

4.2.2 Periodic Tests: Tests for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.