

AEROSPACE MATERIAL SPECIFICATION



AMS 5826C

Issued JAN 1982
Revised SEP 2000

Superseding AMS 5826B

Steel, Corrosion and Heat Resistant, Welding Wire 15Cr - 5.1Ni - 0.30Cb - 3.2Cu

UNS S15500

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of steels of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

| | |
|----------|---|
| AMS 2248 | Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock |
| AMS 2813 | Packaging and Marking of Packages of Welding Wire, Standard Method |
| AMS 2814 | Packaging and Marking of Packages of Welding Wire, Premium Quality |
| AMS 2816 | Identification, Welding Wire, Tab Marking Method |
| AMS 2819 | Identification, Welding Wire, Direct Color Code System |
| ARP1876 | Weldability Test for Weld Filler Metal Wire |
| ARP4926 | Alloy Verification and Chemical Composition Inspection of Welding Wire |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Wire shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element | min | max |
|------------------|-------|-----------------|
| Carbon (3.1.4) | 0.025 | 0.050 |
| Manganese | 0.25 | 0.75 |
| Silicon | -- | 0.60 |
| Phosphorus | -- | 0.020 |
| Sulfur | -- | 0.010 |
| Chromium | 14.40 | 15.30 |
| Nickel | 4.75 | 5.50 |
| Columbium | 5XC | 0.40 |
| Copper | 3.00 | 3.50 |
| Molybdenum | -- | 0.30 |
| Tantalum (3.1.1) | -- | 0.05 |
| Aluminum | -- | 0.025 |
| Oxygen | -- | 0.01 (100 ppm) |
| Nitrogen | -- | 0.040 (400 ppm) |
| Hydrogen | -- | 0.0006 (6 ppm) |

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.1.3 Chemical analysis of initial ingot, bar, or rod stock before drawing, other than those analyses required to be done on the finished wire, is acceptable provided the processes used for drawing or rolling, annealing, and cleaning, are controlled to ensure continued conformance to chemical composition requirements.

3.1.4 Shall be determined on finished wire.

3.2 Condition:

Cold worked, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3 Fabrication:

- 3.3.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not tear the wire surfaces are acceptable provided the wire conforms to the tolerances of 3.6.
- 3.3.2 Butt welding is permissible provided both ends to be joined are alloy verified using a method capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.
- 3.3.3 In-process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or protective atmospheres to ensure freedom from surface oxidation and absorption of other extraneous elements.
- 3.3.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Properties:

Wire shall conform to the following requirements:

- 3.4.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.
- 3.4.2 Spooled Wire: Shall conform to 3.4.2.1 and 3.4.2.2.
 - 3.4.2.1 Cast: Wire, wound on standard 12-inch (308-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.
 - 3.4.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter: Shall be as shown in Table 2.

TABLE 2A - Sizes and Tolerances, Inch/Pound Units

| Form | Nominal Diameter Inch | Tolerances | |
|-------------|--|--------------|---------------|
| | | Inch Plus | Inch Minus |
| Cut Lengths | 0.030, 0.045 | 0.001 | 0.001 |
| Cut Lengths | 0.062, 0.078, 0.094, 0.125, 0.156, 0.188 | 0.002 | 0.002 |
| Spools | 0.007, 0.010, 0.015 | 0.0005 | 0.0005 |
| Spools | 0.020, 0.030, 0.035, 0.045 | 0.001 | 0.002 |
| Spools | 0.062, 0.078, 0.094 | 0.002 | 0.002 |

TABLE 2B - Sizes and Diameter Tolerances, SI Units

| Form | Nominal Diameter Millimeters | Tolerances | |
|-------------|------------------------------------|--------------------|---------------------|
| | | Millimeter Plus | Millimeter Minus |
| Cut Lengths | 0.76, 1.14 | 0.025 | 0.025 |
| Cut Lengths | 1.57, 1.98, 2.39, 3.18, 3.96, 4.78 | 0.05 | 0.05 |
| Spools | 0.18, 0.25, 0.38 | 0.013 | 0.013 |
| Spools | 0.51, 0.76, 0.89, 1.14 | 0.025 | 0.025 |
| Spools | 1.57, 1.98, 2.39 | 0.05 | 0.05 |

3.6.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than + 0, - 0.5 inch (-13 mm) from the length ordered.