



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

AMS5828A
Superseding AMS 5828

Issued 7-15-63
Revised 5-1-70

ALLOY WIRE, WELDING, CORROSION AND HEAT RESISTANT
Nickel Base - 19.5Cr - 13.5Co - 4.3Mo - 3.0Ti - 1.4Al
Vacuum Induction Melted

SAE Technical Board rules provide that: "All technical reports, including standards applications, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for inert gas arc welding of precipitation hardenable nickel base alloys of similar composition.
- 3. COMPOSITION:**

	min	max
Ø Carbon	0.03	0.10
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.010
Chromium	18.00	21.00
Cobalt	12.00	15.00
Molybdenum	3.50	5.00
Titanium	2.75	3.50
Aluminum	1.20	1.60
Boron	0.003	0.010
Iron	--	2.00
Copper	--	0.10
Zirconium	--	0.04
Nickel		remainder

- 3.1 Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2269; check analysis limit for zirconium shall be 0.01 over maximum.
- 4. CONDITION:** Cold drawn, solution heat treated, bright finish, unless otherwise specified. Wire shall be furnished on disposable spools for machine welding and in cut lengths for manual welding, as ordered.
 - 4.1** Solution heat treatment and in-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.
 - 4.2** Oxides, dirt, and drawing compounds shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.
- 5. TECHNICAL REQUIREMENTS:**
 - 5.1 Welding:** Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds.
 - 5.2 Spooled Wire:** Shall conform to the following, unless otherwise agreed upon by purchaser and vendor:

- 5.2.1 Cast: Wire shall have imparted to it a curvature such that a specimen sufficient in length to form one \emptyset loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. and not greater than 30 in. in diameter.
- 5.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch.
- 5.2.3 Layer Winding: Wire shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching; shall be wound so as to avoid producing kinks, waves, and sharp bends; and shall be free to unwind without restriction caused by overlapping or wedging. The outside end of the spooled wire shall be so treated that it may be readily located.
- 5.3 Heat: Wire on each spool shall be of one continuous length from the same heat of material. Cut lengths in any one package shall be from the same heat of material.
6. QUALITY: Material shall be produced by vacuum induction melting; it may be remelted using consumable electrode vacuum process but remelting is not required. Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.
7. SIZES AND TOLERANCES: Unless otherwise specified, wire shall be supplied in the following sizes and to the tolerances shown:

7.1 Diameter:

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.030, 0.045, 0.062, 0.093, 0.125	0.003	0.003
Spools	0.062, 0.093	0.002	0.002
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005

- 7.2 Length: Cut lengths shall be furnished in 18, 27, or 36 in. lengths, as ordered, and shall not vary more than $\pm 1/4$ in. from the length ordered.

8. REPORTS:

- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and a statement that the product conforms to the technical requirements of this specification. When consumable electrode \emptyset remelted alloy is supplied, a heat shall be the consumable electrode remelted ingots produced from alloy originally melted as a single furnace charge. This report shall include the purchase order number, heat number, material specification number and its revision letter, nominal size, and quantity from each heat.
- 8.2 Unless otherwise specified, when parts made of this wire or assemblies requiring the use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to this specification, and shall furnish with each shipment three copies of a report stating that the wire conforms to the requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, part or assembly number, and quantity.