

ALLOY WELDING WIRE, CORROSION AND HEAT RESISTANT
72Ni - 3.2Mn - 20Cr - 2.5Cb - 0.48Ti
Vacuum Induction Melted, Environment Controlled Packaging

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of welding wire.

1.2 Application: Primarily for use as filler metal for gas-tungsten-arc or gas-metal-arc welding of nickel-chromium alloys.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

AMS 2814 - Packaging of Welding Wire, Premium Quality

AMS 2815 - Identification, Welding Wire, Line Code System

AMS 2816 - Identification, Welding Wire, Color Code System

2.1.2 Aerospace Recommended Practices:

ARP1313 - Determination of Trace Elements in High Temperature Alloys

ARP1876 - Weldability Test for Weld Filler Metal Wire

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM E 354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser except that selenium, lead, and bismuth shall be determined in accordance with ARP1313 and oxygen and nitrogen shall be determined by Leco Analyzer or equivalent:

	min	max
Carbon	---	0.03
Manganese	3.00	3.50
Silicon	---	0.10
Phosphorus	---	0.010
Sulfur	---	0.007
Chromium	18.00 -	22.00
Nickel	67.00	--
Columbium	2.00 -	3.00
Titanium	0.20 -	0.75
Cobalt	---	0.10
Tantalum	---	0.30
Aluminum	---	0.10
Boron	---	0.001
Iron	---	1.00
Copper	---	0.25
Tin	---	0.005
Lead	---	0.001 (10 ppm)
Bismuth	---	0.0002 (2 ppm)
Selenium	---	0.0006 (6 ppm)
Magnesium	---	0.05
Oxygen	---	0.0050 (50 ppm)
Nitrogen	---	0.010 (100 ppm)

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269. No variation is permitted for lead, bismuth, selenium, oxygen, and nitrogen.

3.2 Condition: Cold drawn, bright finish, in a temper which will provide proper feeding of the wire in machine welding equipment.

- 3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.
- 3.2.2 In-process annealing between cold rolling or drawing operations shall be performed in vacuum or inert gas atmosphere.
- 3.2.3 Drawing compounds, oxides, dirt, and oil shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.
- 3.2.4 Residual elements and dissolved gases deposited on, or absorbed by, the welding wire as a result of cleaning or drawing operations shall be removed.
- 3.3 Properties: Wire shall conform to the following requirements:
- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor. The referee method of ARP1876 may be used to resolve weldability disputes.
- 3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.2.2.2.
- 3.3.2.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length, 4 - 8 feet (1219 - 2438 mm), to form one loop, when cut from the spool and laid on a flat surface, shall form a circle 15 - 30 inches (381 - 762 mm) in diameter.
- 3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).
- 3.4 Quality:
- 3.4.1 Alloy shall be vacuum induction melted; it may be multiple melted using consumable electrode practice in the remelt cycle but remelting is not required.
- 3.4.2 Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.
- 3.5 Sizes and Tolerances: Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.

3.5.1 Diameter:

TABLE I

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	0.76, 1.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.03	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1) and sizes and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.