

ALLOY BARS, CORROSION AND HEAT RESISTANT
19Cr - 36Co - 25Ni - 7.0Mo - 0.50Cb - 2.9Ti - 0.20Al - 9.0Fe
Vacuum Induction Plus Vacuum Consumable Electrode Melted
Solution Heat Treated for Work Strengthening

1. SCOPE:

1.1 Form: This specification covers a high strength, corrosion and heat resistant cobalt-chromium-nickel alloy in the form of bars.

1.2 Application: Primarily for applications requiring a combination of high strength up to 1100°F (595°C), good tension-tension fatigue strength, toughness, and ductility. This alloy exhibits exceptionally good resistance to corrosion, crevice-corrosion, stress-corrosion cracking, and elevated temperature relaxation.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2261 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars and Forging Stock

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

AMS 2806 - Identification, Bars, Wire, Mechanical Tubing and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E8 - Tension Testing of Metallic Materials
- ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
- ASTM E21 - Elevated Temperature Tension Tests of Metallic Materials
- ASTM E112 - Estimating the Average Grain Size of Metals
- ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
- ASTM E292 - Conducting Time-for-Rupture Notch Tension Tests of Materials
- ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.04
Manganese	--	0.20
Silicon	--	0.20
Phosphorus	--	0.020
Sulfur	--	0.010
Chromium	18.00 -	20.00
Cobalt	34.00 -	38.00
Molybdenum	6.00 -	8.00
Columbium	0.25 -	0.75
Titanium	2.50 -	3.25
Aluminum	0.10 -	0.30
Iron	8.00 -	10.00
Boron	--	0.03
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: Solution heat treated and centerless ground.

3.3 Solution Heat Treatment: Bars shall be solution heat treated by heating to a temperature within the range 1900° - 1925°F (1040° - 1050°C), holding at the selected temperature within +25°F (+15°C) for 4 - 8 hr, and quenching in water.

3.4 Properties: Bars shall conform to the following requirements:

3.4.1 As Solution Heat Treated:

3.4.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, max	160,000 psi (1105 MPa)
Yield Strength at 0.2% Offset, max	70,000 psi (485 MPa)
Elongation in 4D, min	50%
Reduction of Area, min	65%

3.4.1.2 Hardness: Should be not higher than 20 HRC, or equivalent, determined in accordance with ASTM E18 but bars shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.1.1 are met.

3.4.1.3 Grain Size: Predominantly 4 or finer with occasional grains as large as 2 permissible, determined by comparison of a polished and etched specimen with the chart in ASTM E112.

3.4.2 After Cold Working and Aging: Specimens as in 4.3.1 from bars 1-3/4 in. (45 mm) and under in nominal diameter, solution heat treated as in 3.3, shall have the following properties after being cold reduced 48% + 1 of original cross-section area (See 8.2) and aged by heating to a temperature within the range 1200° - 1250°F (650° - 675°C), holding at the selected temperature within +25°F (+15°C) for 4 - 4-1/2 hr, and cooling at a rate equivalent to an air cool (See 8.3).

3.4.2.1 Tensile Properties:

3.4.2.1.1 At Room Temperature: Shall be as follows, determined in accordance with ASTM E8 on specimens as in 4.3.1:

Tensile Strength, min	260,000 psi (1795 MPa)
Yield Strength at 0.2% Offset, min	250,000 psi (1725 MPa)
Elongation in 4D, min	6%
Reduction of Area, min	22%

3.4.2.1.2 At 1100°F (595°C): Shall be as follows, determined in accordance with ASTM E21 on specimens as in 4.3.1 heated to 1100°F \pm 10 (595°C \pm 5), held at heat for 20 - 30 min. before testing, and tested at 1100°F \pm 10 (595°C \pm 5):

Tensile Strength, min	205,000 psi (1415 MPa)
Yield Strength at 0.2% Offset, min	190,000 psi (1310 MPa)
Elongation in 4D, min	5%
Reduction of Area, min	15%

3.4.2.2 Hardness: Shall be not lower than 44 HRC, or equivalent, determined in accordance with ASTM E18.

3.4.2.3 Stress-Rupture Properties at 1200°F (650°C): Shall be as follows; testing of notched specimens and of combination smooth-and-notched specimens shall be in accordance with ASTM E292 and of smooth specimens as in 4.3.1 in accordance with ASTM E139:

3.4.2.3.1 A combination smooth-and-notched specimen machined to the dimensions shown in Fig. 1 and Table I, maintained at 1200°F \pm 3 (650°C \pm 2) while a load sufficient to produce an initial axial stress of 140,000 psi (965 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. After the 23 hr, if rupture occurs in the notch, the smooth section shall, by suitable means, be continued to rupture or a separate smooth specimen shall be tested to rupture under the above conditions. Elongation of the smooth section after rupture, measured at room temperature, shall be not less than 5% in 4D.

3.4.2.3.2 As an alternate procedure, separate smooth and notched specimens, machined from adjacent sections of the same piece with gage sections conforming to the respective dimensions of Table I, may be tested individually under the conditions of 3.4.2.3.1. The smooth specimen shall not rupture in less than 23 hr and elongation after rupture, measured at room temperature, shall be not less than 5% in 4D. The notched specimen shall not rupture in less than 23 hr but need not be tested to rupture.

3.4.2.3.3 The tests of 3.4.2.3.1 and 3.4.2.3.2 may be conducted using a load higher than required to produce an initial axial stress of 140,000 psi (965 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.2.3.1.

3.4.2.3.4 When permitted by purchaser, the tests of 3.4.2.3.1 and 3.4.2.3.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 140,000 psi (965 MPa) shall be used to rupture or for 23 hr, whichever occurs first. After the 23 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 5,000 psi (35 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.2.3.1.

3.5 Quality:

3.5.1 Alloy shall be produced by multiple melting using vacuum induction followed by vacuum consumable electrode melting practice.

3.5.2 Bars, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the bars.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.7 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of bars shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bars conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties 3.4.1.1, hardness (3.4.1.2), and grain size (3.4.1.3) of each lot as solution heat treated.

4.2.1.3 Tolerances (3.7).

4.2.2 Periodic Tests: Tests to determine conformance to requirements for tensile properties (3.4.2.1), hardness (3.4.2.2), and stress-rupture properties (3.4.2.3) after cold working and aging are classified as periodic tests, and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2371 and the following; a heat shall be the consumable electrode remelted ingots produced from alloy originally melted as a single furnace charge:

AMS 5841A

4.3.1 Specimens for tensile and smooth-bar stress-rupture testing shall be of standard proportions in accordance with ASTM E8 with either 0.250 in. (6.25 mm) diameter at the reduced parallel gage section or smaller specimens proportional to the standard when required. Other stress-rupture specimens shall be as specified in 3.4.2.3. All specimens shall be machined from the center of bars 0.800 in. (20.00 mm) and under in nominal diameter or distance between parallel sides and from mid-radius of larger size bars.

4.4 Reports:

4.4.1 The vendor of bars shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile properties, hardness, and grain size of each lot as solution heat treated and, when performed, the results of tests to determine conformance to the periodic test requirements. This report shall include the purchase order number, heat number, AMS 5841A, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5841A, contractor or other direct supplier of bars, part number, and quantity. When bars for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of bars to determine conformance to the requirements of this specification and shall include in the report either a statement that the bars conform or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Shall be in accordance with AMS 2806.

5.2 Packaging:

5.2.1 Bars shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the bars to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Bars not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.
8. NOTES:
- 8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.
- 8.2 The referee procedure to confirm ability of the bars to meet the requirements of 3.4.2 shall use a straight draw bench at room temperature in which a round bar is cold reduced $48\% \pm 1$ in cross-sectional area to a smaller size round bar.
- 8.3 This alloy depends on combinations of cold working and aging to attain a variety of combinations of strength and ductility. Mill capabilities currently are limited to cold drawing bars 1-3/4 in. (45 mm) and under in nominal diameter to attain the properties specified in 3.4.2.1.
- 8.4 For direct U.S. Military procurement, purchase documents should specify not less than the following:
- Title, number, and date of this specification
Size of bars desired
Quantity of bars desired
Applicable level of packaging (See 5.2.2)
- 8.5 Bars meeting the requirements of this specification have been classified under Federal Supply Classification (FSC) 9530.

This specification is under the jurisdiction of AMS Committee "F".