

AMS 5865

ADOPTION NOTICE

AMS 5865, "Nickel, Corrosion and Heat Resistant, Sheet and Strip Thoria Dispersion Strengthened 2.2ThO₂" was adopted on 8 August 1994 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Air Force, ASC/ENOSD, Building 125, 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH 45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:
 Army - MR
 Navy - AS

Adopting Activity:
 Air Force - 11
 (Proj No. 9535-0576)

Review activities:
 AF - 99

SAENORM.COM : Click to view the full PDF of ams5865c

AMSC N/A FSC 9535
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 5865C

Issued JUL 1976

Revised MAY 1994

Superseding AMS 5865B

Submitted for recognition as an American National Standard

NICKEL, CORROSION AND HEAT RESISTANT, SHEET AND STRIP Thoria Dispersion Strengthened 2.2ThO₂

UNS N03260

1. SCOPE:

1.1 Form:

This specification covers thoria-dispersion-strengthened nickel in the form of sheet and strip.

1.2 Application:

These products have been used typically for parts required to operate in the temperature range 1800 to 2400 °F (982 to 1316 °C), but usage is not limited to such applications. A protective coating is required for operation at such temperatures. Fusion welding of structural members is not recommended but the product can be brazed and resistance welded satisfactorily.

1.3 Products covered by this specification are radioactive. Applicable rules and regulations pertaining to handling of radioactive material should be observed.

1.4 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5865C

SAE

AMS 5865C

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2262 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
- MAM 2262 Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
- AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM E 8 Tension Testing of Metallic Materials
- ASTM E 8M Tension Testing of Metallic Materials (Metric)
- ASTM E 21 Elevated Temperature Tension Tests of Metallic Materials
- ASTM E 139 Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
- ASTM E 290 Semi-Guided Bend Test for Ductility of Metallic Materials
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

- MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser; the method of determining thoria (ThO_2) shall be agreed upon by purchaser and vendor.

AMS 5865C

SAE

AMS 5865C

TABLE 1 - Composition

Element	min	max
Thoria	1.80	2.60
Carbon	--	0.02
Sulfur	--	0.0025
Chromium	--	0.05
Cobalt	--	0.20
Titanium	--	0.05
Iron	--	0.05
Copper	--	0.15
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269 except that chromium, titanium, and iron shall each vary not more than 0.001 over maximum; permissible variation for thoria shall be 0.01 under minimum or over maximum.

3.2 Condition:

Cold-rolled, stress-relieved, descaled, and leveled.

3.3 Stress-Relieving:

The product shall be stress-relieved by heating, in vacuum, argon, or hydrogen, to a temperature not lower than 2000 °F (1093 °C) holding at heat for not less than 20 minutes, and cooling to below 500 °F (260 °C) in vacuum, argon, or hydrogen.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Tensile Properties:

3.4.1.1 At Room Temperature: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M using a strain rate of 0.003 to 0.007 inch/inch per minute (0.003 to 0.007 mm/mm per minute) through the 0.6% offset and a crosshead speed of 0.03 to 0.07 inch per minute (0.8 to 1.8 mm/minute) from the 0.6% offset to rupture.

TABLE 2 - Minimum Room Temperature Tensile Properties

Property	Value
Tensile Strength	60.0 ksi (414 MPa)
Yield Strength at 0.2% Offset	40.0 ksi (276 MPa)
Elongation in 1 Inch (25 mm)	10%

AMS 5865C

SAE

AMS 5865C

- 3.4.1.2 At 2000 °F (1093 °C): Shall be as shown in Table 3, determined in accordance with ASTM E 21 on specimens heated to 2000 °F \pm 10 (1093 °C \pm 6), held at heat for 10 to 30 minutes before testing, and tested at 2000 °F \pm 10 (1093 °C \pm 6) using a crosshead speed of 0.03 to 0.07 inch per minute (0.8 to 1.8 mm/minute).

TABLE 3 - Minimum Elevated Temperature Tensile Properties

Property	Value
Tensile Strength	12.0 ksi (83 MPa)
Yield Strength at 0.2% Offset	9.5 ksi (66 MPa)
Elongation in 1 Inch (25 mm)	2%

- 3.4.2 Bending: Product 0.020 to 0.250 inch (0.51 to 6.35 mm), inclusive, in nominal thickness shall withstand, without cracking when examined at 10X magnification, bending in accordance with ASTM E 290 through an angle of 105 degrees around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 4 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.020 to 0.125, incl	0.51 to 3.18, incl	2
Over 0.125 to 0.250, incl	Over 3.18 to 6.35, incl	3

- 3.4.2.1 Bending requirements for product under 0.020 inch (0.51 mm) in nominal thickness shall be agreed upon by purchaser and vendor.
- 3.4.3 Stress-Rupture Properties at 2000 °F (1093 °C): A tensile specimen, maintained at 2000 °F \pm 10 (1093 °C \pm 6) while a load sufficient to produce an initial axial stress of 5.5 ksi (38 MPa) is applied continuously, shall not rupture in less than 20 hours. The test shall be continued to rupture without change of load. The elongation in 1 inch (25 mm) after rupture, measured at room temperature, shall be reported. Test shall be conducted in accordance with ASTM E 139.
- 3.4.3.1 The test of 3.4.3 may be conducted using a load higher than required to produce an initial axial stress of 5.5 ksi (38 MPa) but load shall not be changed while test is in progress. Time to rupture requirement shall be as specified in 3.4.3. The elongation in 1 inch (25 mm) after rupture, measured at room temperature, shall be reported.

AMS 5865C

SAE

AMS 5865C

3.4.3.2 (R) The test of 3.4.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 5.5 ksi (38 MPa) shall be maintained to rupture or for 20 hours, whichever occurs first. After the 20 hours and at intervals of 1 hour thereafter, the stress shall be increased in increments of 1.0 ksi (7 MPa). Time to rupture requirement shall be as specified in 3.4.3. The elongation in 1 inch (25 mm), measured at room temperature, shall be reported.

3.4.4 Structure: The product shall have a substantially uniform structure essentially free from porosity, determined by macroscopic or microscopic examination. Standards for acceptance shall be agreed upon by purchaser and vendor.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 (R) Surface Condition: Mars, gouges, scratches, pits, and similar imperfections which reduce the thickness of the product below the minimum allowable by the thickness tolerance are not acceptable; such imperfections, if more than 0.0005 inch (0.013 mm) deep but not of such depth that their removal would reduce thickness below the minimum, are acceptable provided the number is not more than five per square foot (0.09 m²). Superficial scratches, individual pits, and roughened areas which appear under magnification as a scattering of pits will be acceptable if they are under 0.0005 inch (0.013 mm) in depth; the number of such imperfections is not restricted. The product shall be free of contamination, determined by visual inspection; differences in reflectivity will not be considered evidence of contamination.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2262 or MAM 2262 except that the deviation from flat shall not exceed 6%, determined as in 3.6.1.

3.6.1 The deviation from flat shall be determined from the expression $100 H/L$ where H is equal to the maximum distance between a flat surface and the highest surface of the product and L is the distance between the highest point of the product and the nearest point of contact of the product with the flat surface. A general bow in the product which can be eliminated by slight pressure without the ends coiling or an "oil-can" effect resulting is acceptable.