

AEROSPACE MATERIAL SPECIFICATION

Steel, Corrosion and Heat Resistant, Forgings 12.5Cr (SAE 51410) Enhanced Fracture Toughness, Annealed

UNS S41000

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of forgings and forging stock.

1.2 Application:

These forgings have been used typically, for structural parts requiring oxidation resistance up to 1000 °F (538 °C) and enhanced fracture toughness, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2303	Aircraft-Quality Steel Cleanliness, Martensitic Corrosion Resistant Steels, Magnetic Particle Inspection Procedure
MAM 2303	Aircraft-Quality Steel Cleanliness, Martensitic Corrosion Resistant Steels, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2315	Determination of Delta Ferrite Content
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
AMS 2808	Identification, Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

Distributed under license from the IHS Archive

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 399	Plane-Strain Fracture Toughness of Metallic Materials

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition::

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.10	0.13
Manganese	--	0.50
Silicon	--	1.00
Phosphorus	--	0.020
Sulfur	--	0.030
Chromium	11.50	13.50
Nickel	--	0.75
Molybdenum	--	0.50
Aluminum	--	0.05
Copper	--	0.50
Vanadium	--	0.04
Tin	--	0.05
Nitrogen	--	0.08

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

- 3.2.1 Forgings: Annealed having hardness not higher than 241 HB, or equivalent; hardness shall be determined in accordance with ASTM A 370.
- 3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Forgings:

- 3.3.1.1 Properties After Heat Treatment: Forgings shall have the following properties, determined on full-section specimens from forgings 0.500 inch (12.70 mm) and under in nominal diameter or distance between parallel sides or on 0.500 inch \pm 0.010 (12.70 mm \pm 0.25) diameter specimens cut from larger forgings after being heat treated as follows: Heat to 1825 °F \pm 25 (996 °C \pm 14), hold at heat for not less than one hour, and cool to room temperature. Cooling rate between 1550 °F and 1000 °F (843 and 538 °C) shall be 50 F (28 C) degrees per minute or faster, except oil or water quenching is prohibited. Temper at 1015 °F \pm 15 (546 °C \pm 8) for not less than one hour and cool.

- 3.3.1.1.1 Hardness: Shall be 30 - 38 HRC, or equivalent.

- 3.3.1.1.2 Microstructure: When required, shall be in accordance with standards established by purchaser.

- 3.3.1.1.3 Ferrite Content: Shall be not more than 2%, determined in accordance with AMS 2315.

- 3.3.2 Forgings Stock: A sample of forging stock forged to a test coupon shall be annealed to a hardness not exceeding 241 HB, or equivalent, heated to 1375 °F \pm 25 (746 °C \pm 14), held at heat for not less than three hours, cooled and then heat treated as in 3.3.1.1. Room temperature fracture toughness (K_{1C}), determined in accordance with ASTM E 399 shall be not less than 40 ksi $\sqrt{\text{inch}}$ (44 MPa $\sqrt{\text{m}}$)

3.4 Quality:

Forgings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the forgings.

- 3.4.1 Steel shall be aircraft quality conforming to AMS 2303 or MAM 2303.

- 3.4.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2374.

4.4 Reports:

4.4.1 The vendor of forgings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for response to heat treatment of each lot. This report shall include the purchase order number, lot number, AMS 5867, part number, size, quantity, and melt source of stock used to make the forgings.

4.4.2 The vendor of forging stock shall furnish with each shipment a report showing the results of tests for chemical composition and fracture toughness of each heat. This report shall include the purchase order number, heat number, AMS 5867, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

Shall be as follows:

5.1.1 Forgings: In accordance with AMS 2808.

5.1.2 Forging Stock: As agreed upon by purchaser and vendor.