



AEROSPACE MATERIAL SPECIFICATION	AMS5871™	REV. F
	Issued 1972-05 Revised 2015-08	
Superseding AMS5871E		
Alloy, Corrosion and Heat-Resistant, Sheet, Strip and Plate 21Cr - 32.5Ni - 0.38Ti - 0.38Al - 45Fe Solution Heat Treated (Composition similar to UNS N08800)		

RATIONALE

AMS5871F revises Properties (3.3.1.1) and Reports (4.4), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant iron-nickel-chromium alloy in the form of sheet, strip, and plate 0.010 to 2.00 inches (0.25 to 50.8 mm), inclusive, in nominal thickness (See 8.4).

1.2 Application

These products have been used typically for low-stressed parts requiring corrosion and oxidation resistance particularly where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

- AMS2262 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
- AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
- AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS5871F>

- AMS2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
- AS4194 Sheet and Strip Surface Finish Nomenclature

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

- ASTM A480/A480M Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
- ASTM E8/ E8M Tension Testing of Metallic Materials
- ASTM E290 Bend Testing of Material for Ductility
- ASTM E354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	min	max
Carbon	--	0.10
Manganese	--	1.50
Silicon	--	1.00
Phosphorus	--	0.035
Sulfur	--	0.015
Chromium	19.00	23.00
Nickel	30.00	35.00
Titanium	0.15	0.60
Aluminum	0.15	0.60
Copper	--	0.75
Iron	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes in accordance with ASTM A480/A480M and AS4194 and 3.2.1.1 or 3.2.1.2, as applicable:

3.2.1.1 Sheet

Shall be No. 2D finish.

3.2.1.2 Strip

Shall be No. 1 strip finish.

3.2.2 Plate

Hot rolled and solution heat treated; plate shall be descaled.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Tensile Properties

Shall be as specified in Table 2 for product 0.010 to 2.00 inches (0.25 to 50.8 mm), inclusive, in nominal thickness, determined in accordance with ASTM E8/E8M.

3.3.1.1 Mechanical property requirements for product outside the range covered by 1.1 shall be agreed upon between purchaser and producer.

Table 2 - Minimum tensile properties

Property	Value
Tensile Strength	65 ksi (448 MPa)
Yield Strength at 0.2% Offset	25.0 ksi (172 MPa)
Elongation in 2 inches (50.8) or 4D	30%

3.3.2 Bending

Product shall be tested in accordance with ASTM E290 using a specimen prepared nominally 0.75 inch (19.0 mm) in width with the axis of bend parallel to the direction of rolling, and shall withstand, without cracking, when bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product. In case of dispute, the results of tests using the guided bend test of ASTM E290 shall govern.

Table 3 - Bending parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1
Over 0.050 to 0.1875, excl	Over 1.27 to 4.762, excl	2

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of AMS2262.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with AMS2371.

4.4 Reports

The producer of the product shall furnish with each shipment a report showing the producer's name and country where the metal was melted (e.g., the final melt in the case of metal processed by multiple melting operations) and the results of tests for composition of each heat and for tensile and bending properties on each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5871F, size, product form and quantity.

4.4.1 When the product is outside the range covered by 1.1, the report shall contain a statement to that effect.

4.5 Resampling and Retesting

Shall be in accordance with AMS2371.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with AMS2807.

5.2 Packaging

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A producer shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.