

AEROSPACE MATERIAL SPECIFICATION



AMS 5895C

Issued OCT 1979
Revised NOV 2000

Superseding AMS 5895B

Steel, Corrosion and Heat Resistant, Bars, Wire, Forgings, Tubing, and Rings
15Cr - 25.5Ni - 1.2Mo - 2.1Ti - 0.006B - 0.30V
Consumable Electrode Melted, 1750 °F (954 °C) Solution Heat Treated, Welding Grade
Precipitation Hardenable

UNS S66286

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging, flash welded rings, or heading.

1.2 Application:

These products have been used typically for parts requiring high strength up to 1300 °F (704 °C) and oxidation resistance up to 1500 °F (816 °C), particularly those which are welded and then heat treated to develop required properties, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2241	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
MAM 2241	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2243	Tolerances, Corrosion and Heat Resistant Steel Tubing
MAM 2243	Tolerances, Metric, Corrosion and Heat Resistant Steel Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
AMS 2750	Pyrometry
AMS 2806	Identification, Bars, Wire, Mechanical Tubing and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining the Average Grain Size
ASTM E 139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E 292	Conducting Time-for-Rupture Notch Tension Tests of Materials
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	0.35
Silicon	--	0.30
Phosphorus	--	0.020
Sulfur	--	0.010
Chromium	13.50	16.00
Nickel	24.00	27.00
Molybdenum	1.00	1.50
Titanium	1.90	2.35
Boron	0.0030	0.010
Vanadium	0.10	0.50
Cobalt	--	1.00
Aluminum	--	0.35
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Melting Practice:

Steel shall be produced by multiple melting using consumable electrode practice in the remelt cycle.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Bars, Wire, Forgings, and Flash Welded Rings: Solution heat treated.

3.3.1.1 Bars and Wire:

3.3.1.1.1 All hexagons, other bars 2.750 inches (69.85 mm) and under in nominal diameter or least distance between parallel sides, and wire shall be cold finished.

3.3.1.1.2 Bars, other than hexagons, over 2.750 inches (69.85 mm) in nominal diameter or least distance between parallel sides shall be hot finished and descaled.

3.3.1.2 Forgings: Shall be descaled.

3.3.1.3 Flash Welded Rings: Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.3.1.4 Mechanical Tubing: Cold finished.

3.3.2 Stock for Forgings, Flash Welded Rings, or Heading: As ordered by the forging, flash welded ring, or heading manufacturer.

3.4 Heat Treatment:

Bars, wire except as specified in 3.4.1, forgings, mechanical tubing, and flash welded rings shall be solution heat treated by heating to 1750 °F ± 25 (954 °C ± 14), holding at heat for not less than one hour, and quenching in oil or water. Pyrometry shall be in accordance with AMS 2750.

3.4.1 Wire 0.1874 inch (4.760 mm) and under in nominal diameter shall be solution heat treated by heating to 1750 °F ± 25 (954 °C ± 14), holding at heat for a time commensurate with wire diameter, and cooling rapidly.

3.5 Properties:

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A 370:

3.5.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings:

3.5.1.1 As Solution Heat Treated:

3.5.1.1.1 Tensile Properties: Wire shall have tensile strength not higher than 105 ksi (724 MPa) or equivalent hardness (See 8.2).

3.5.1.1.2 Hardness: Shall be as follows:

3.5.1.1.2.1 Bars and Mechanical Tubing: Not higher than 201 HB, or equivalent, (See 8.3) determined approximately midway between outer surface and center or inner surface as applicable.

3.5.1.1.2.2 Forgings and Flash Welded Rings: Not higher than 201 HB, or equivalent (See 8.3).

3.5.1.1.3 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

3.5.1.2 After Precipitation Heat Treatment: Product, 5.0 inches (127 mm) and under in nominal diameter or least distance between parallel sides, shall have the following properties after being precipitation heat treated by heating to 1325 °F ± 15 (718 °C ± 8), holding at heat for not less than 16 hours, and cooling in air.

3.5.1.2.1 Longitudinal Tensile Properties: Shall be as shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	130 ksi (896 MPa)
Yield Strength at 0.2% Offset	85 ksi (586 MPa)
Elongation in 4D	15%
Reduction of Area	20%

- 3.5.1.2.1.1 The requirements of 3.5.1.2.1 apply to specimens taken with the axis approximately parallel to the grain flow and to specimens taken in the radial direction and in the tangential direction at the rim of disc forgings.
- 3.5.1.2.1.2 Specific locations of specimens from forgings and flash welded rings shall be as agreed upon by purchaser and vendor.
- 3.5.1.2.2 Hardness: Should be 248 to 341 HB, or equivalent (See 8.3). The product shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.1.2.1 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness, or from another sample with similar nonconforming hardness.
- 3.5.1.2.3 Stress-Rupture Properties at 1200 °F (649 °C): Shall be as follows; testing of notched specimens and of combination smooth-and-notched specimens shall be performed in accordance with ASTM E 292 and of smooth specimens in accordance with ASTM E 139:
- 3.5.1.2.3.1 A standard cylindrical combination smooth-and-notched specimen conforming to ASTM E 292, maintained at 1200 °F \pm 3 (649 °C \pm 2) while a load sufficient to produce an initial axial stress of 65.0 ksi (448 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Rupture shall occur in the smooth section and elongation of this section after rupture, measured at room temperature, shall be not less than 5% in 4D if the specimen ruptures in 48 hours or less and not less than 3% in 4D if the specimen ruptures in more than 48 hours.
- 3.5.1.2.3.2 As an alternate procedure, separate smooth and notched specimens, machined from adjacent sections of the same piece with gage sections conforming to the applicable dimensions shown in ASTM E 292, may be tested individually under the conditions of 3.5.1.2.3.1. The smooth specimen shall not rupture in less than 23 hours and elongation after rupture, measured at room temperature, shall be as specified in 3.5.1.2.3.1. The notched specimen shall not rupture in less time than the companion smooth specimen but need not be tested to rupture.
- 3.5.1.2.3.3 The tests of 3.5.1.2.3.1 and 3.5.1.2.3.2 may be conducted using a load higher than required to produce an initial axial stress of 65.0 ksi (448 MPa) but the load shall not be changed while test is in progress. Time to rupture, rupture location, and elongation requirements shall be as specified in 3.5.1.2.3.1.

3.5.1.2.3.4 When permitted by purchaser, the tests of 3.5.1.2.3.1 and 3.5.1.2.3.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 65.0 ksi (448 MPa) shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at interval of 8 to 16 hours, preferably 8 to 10 hours, thereafter, the stress shall be increased in increments of 5.0 ksi (34.5 MPa). Time to rupture, rupture location, and elongation requirements shall be as specified in 3.5.1.2.3.1.

3.5.1.2.3.5 For tubing from which a solid round specimen cannot be cut, a full section of tubing shall be tested and shall meet the smooth bar requirements of 3.5.1.2.3.1.

3.5.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.4 and 3.5.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, and 3.5.1.2.3. If specimens taken from the stock after heat treatment as in 3.4 and 3.5.1.2 conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, and 3.5.1.2.3, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5.3 Stock for Flash Welded Rings or Heading: A sample of stock heat treated as in 3.4 and 3.5.1.2 shall conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, and 3.5.1.2.3.

3.6 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.7 Tolerances:

Shall be as follows:

3.7.1 Bars and Wire: In conformance with AMS 2241 or MAM 2241.

3.7.2 Mechanical Tubing: In conformance AMS 2243 or MAM 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: The following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.5.1.1.1) of each lot of wire as solution heat treated.

4.2.1.3 Hardness (3.5.1.1.2) of each lot of bars, forgings, mechanical tubing, and flash welded rings as solution heat treated.

4.2.1.4 Tensile properties (3.5.1.2.1), hardness (3.5.1.2.2), and stress-rupture properties (3.5.1.2.3) of each lot of bars, wire, forgings, mechanical tubing, and flash welded rings after precipitation heat treatment.

4.2.1.5 Tolerances (3.7) of bars, wire, and mechanical tubing.

4.2.2 Periodic Tests: Tests for forging stock (3.5.2) and of stock for flash welded rings or heading (3.5.3) to demonstrate ability to develop required properties, and grain flow of die forgings (3.6.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Forging, Flash Welded Rings, or Heading: In accordance with AMS 2371.

4.3.2 Forgings: In accordance AMS 2374.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness solution heat treated and for tensile properties, hardness, and stress-rupture properties after precipitation heat treatment of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5895C, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting:

Shall be as follows: