



AEROSPACE MATERIAL SPECIFICATION

AMS5929

Issued 2008-10
Reaffirmed 2014-06

Steel, Corrosion-Resistant, Bars and Forgings
11.5Cr -10Ni – 1.0Al – 0.5Ti – 1.0Cu – 1.0W
Vacuum Induction Plus Vacuum Consumable Electrode Melted
Solution Heat Treated, Precipitation Hardenable

RATIONALE

This document has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of bars, forgings, and forging stock.

1.2 Application

These products have been used typically for heat-treated parts requiring stress corrosion resistance, along with a combination of high strength and high toughness up to 800 °F (427 °C) with good ductility and strength in the transverse direction, but usage is not limited to such applications.

1.2.1 Certain design, processing procedures, or environmental conditions may cause these products to become susceptible to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

| | |
|---------|---|
| AMS2241 | Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire |
| AMS2248 | Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS2300 | Steel Cleanliness, Premium Aircraft-Quality, Magnetic Particle Inspection Procedure |
| AMS2371 | Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock |
| AMS2374 | Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS5929>

| | |
|---------|---|
| AMS2750 | Pyrometry |
| AMS2806 | Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys |
| AMS2808 | Identification, Forgings |
| AS1182 | Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing |

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

| | |
|------------|---|
| ASTM A 370 | Mechanical Testing of Steel Products |
| ASTM A 604 | Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets |
| ASTM E 353 | Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys |
| ASTM E 399 | Plane-Strain Fracture Toughness of Metallic Materials |

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

| Element | min | max |
|------------|-------|-------|
| Carbon | -- | 0.03 |
| Manganese | -- | 0.25 |
| Silicon | -- | 0.25 |
| Phosphorus | -- | 0.010 |
| Sulfur | -- | 0.010 |
| Chromium | 11.00 | 12.50 |
| Nickel | 9.25 | 10.75 |
| Molybdenum | 1.0 | 1.75 |
| Tungsten | 0.5 | 1.5 |
| Titanium | 0.20 | 0.50 |
| Aluminum | 0.7 | 1.5 |
| Copper | 0.5 | 1.5 |
| Nitrogen | -- | 0.01 |

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Melting Practice

Product shall be multiple melted using vacuum induction melting followed by vacuum consumable electrode remelt practice.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars

3.3.1.1 Rounds

Solution heat treated and turned, centerless ground, and polished.

3.3.1.2 Hexagons

Solution heat treated and descaled.

3.3.1.3 Squares and Flats

Hot finished, solution heat treated, and machined or descaled.

3.3.1.4 Forgings

Solution heat treated and descaled.

3.3.2 Forging Stock

As ordered by the forging manufacturer.

3.4 Heat Treatment

Bars and forgings shall be solution heat treated by heating to $1700\text{ }^{\circ}\text{F} \pm 25$ ($927\text{ }^{\circ}\text{C} \pm 14$), holding at heat for 60 minutes ± 15 , water quenching to $300\text{ }^{\circ}\text{F}$ ($149\text{ }^{\circ}\text{C}$) or cooler then further cooling to $40\text{ }^{\circ}\text{F}$ ($4\text{ }^{\circ}\text{C}$) or colder, holding at that temperature for not less than four hours, and warming in air to room temperature. Pyrometry shall be in accordance with AMS2750.

3.5 Properties

The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A 370.

3.5.1 All Products

3.5.1.1 Macrostructure

Visual examination of transverse full cross-sections from bars, billets, and forging stock, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections for product 36 squares inches (232 cm^2) and under in nominal cross-sectional area shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - MACROSTRUCTURE LIMITS

| Class | Condition | Severity |
|-------|--------------------|----------|
| 1 | Freckles | A |
| 2 | White Spots | A |
| 3 | Radial Segregation | A |
| 4 | Ring Pattern | B |

3.5.2 Bars and Forgings

3.5.2.1 As Solution Heat Treated

3.5.2.1.1 Hardness

3.5.2.1.1.1 Bars

Not higher than 35 HRC, or equivalent (See 8.2), determined at mid-radius or quarter thickness.

3.5.2.1.1.2 Forgings

Not higher than 35 HRC, or equivalent (See 8.2).

3.5.2.2 After Precipitation Heat Treatment

The solution heat treated product, 8 inches (203 mm) and under in nominal diameter or maximum cross-sectional dimension, precipitation heat treated to the temperature and time shown in Table 3 and cooled in air, oil, or other suitable liquid quench (See 8.3), shall have the properties specified in 3.5.2.2.1, 3.5.2.2.2, and 3.5.2.2.3. Tensile and hardness tests need only be made in the H1000 condition unless purchaser specifies another heat treated condition for testing.

TABLE 3 - PRECIPITATION HEAT TREATING PARAMETERS

| Condition | Temperature | Time |
|-----------|---------------------------|---------------|
| H950 | 950 °F ± 10 (510 °C ± 6) | 4 hours ± 0.3 |
| H1000 | 1000 °F ± 10 (538 °C ± 6) | 4 hours ± 0.3 |

3.5.2.2.1 Tensile Properties

Shall be as shown in Table 4.

TABLE 4A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

| Condition | Specimen Orientation | Tensile Strength ksi | Yield Strength at 0.2% Offset ksi | Elongation in 2 Inches or 4D % | Reduction of Area % |
|-----------|----------------------|-------------------------|---|--------------------------------------|---------------------------|
| H950 | Longitudinal | 238 | 224 | 10 | 42 |
| | Transverse | 238 | 224 | 8 | 31 |
| H1000 | Longitudinal | 215 | 205 | 11 | 49 |
| | Transverse | 215 | 205 | 11 | 45 |

TABLE 4B - MINIMUM TENSILE PROPERTIES, SI UNITS

| Condition | Specimen Orientation | Tensile Strength MPa | Yield Strength at 0.2% Offset MPa | Elongation in 50.8 mm or 4D % | Reduction of Area % |
|-----------|----------------------|-------------------------|---|-------------------------------------|---------------------------|
| H950 | Longitudinal | 1 641 | 1 544 | 10 | 42 |
| | Transverse | 1 634 | 1 544 | 8 | 31 |
| H1000 | Longitudinal | 1 482 | 1 413 | 11 | 49 |
| | Transverse | 1 482 | 1 413 | 11 | 45 |

3.5.2.2.1.1 Longitudinal tensile property requirements apply to specimens taken in the longitudinal direction from bars and to specimens taken from forgings with axis of specimen in the area of gage length varying not more than 15 degrees from parallel to the forging flow lines.

3.5.2.2.1.2 Transverse tensile property requirements apply to specimens taken approximately perpendicular to the longitudinal direction of bars and to specimens taken from forgings with axis of specimens in the area of gage length varying not more than 15 degrees from perpendicular to the forging flow lines.

3.5.2.2.1.3 Transverse tensile property requirements apply only to products from which a test specimen not less than 2-1/2 inches (63.5 mm) long or 1/2 × 1/2 inch (12.7 × 12.7 mm) cross-section can be taken.

3.5.2.2.1.4 Products tested in the transverse direction need not be tested in the longitudinal direction.

3.5.2.2.2 Hardness

Shall not be lower than shown in Table 5, or equivalent (See 8.2). Product shall not be rejected on the basis of hardness if the tensile property requirements of Table 4 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness.

TABLE 5 - MINIMUM HARDNESS

| Condition | Hardness, HB | HRC |
|-----------|--------------|-----|
| H950 | 442 | 47 |
| H1000 | 400 | 43 |

3.5.2.2.3 Fracture Toughness

Shall not be lower than shown in Table 6, determined in accordance with ASTM E 399 on specimens in the longitudinal LT or LR orientation from product 3.00 inches (76.2 mm) and over in nominal section thickness. If product size precludes use of specimens which will provide valid K_{IC} results, use of K_Q values for acceptance is permissible.

TABLE 6 - MINIMUM FRACTURE TOUGHNESS, K_{IC}

| Condition | Fracture Toughness | Fracture Toughness |
|-----------|--------------------------|-----------------------|
| | ksi $\sqrt{\text{inch}}$ | MPa $\sqrt{\text{m}}$ |
| H950 | 70 | 77 |
| H1000 | 95 | 104.5 |

3.5.3 Forging Stock

When a sample of stock is forged to a test coupon and heat treated as in 3.4 and 3.5.2.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.2.2.1, 3.5.2.2.2, and 3.5.2.2.3. If specimens taken from the stock after heat treatment as in 3.4 and 3.5.2.2 conform to the requirements of 3.5.2.2.1, 3.5.2.2.2 and 3.5.2.2.3, the tests shall be accepted as equivalent to tests of a forged coupon.

3.6 Quality

3.6.1 Steel shall be premium aircraft quality conforming to AMS2300.

3.6.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.3 Bars ordered hot rolled or cold drawn, or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.6.4 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.7 Tolerances

Bars shall conform to all applicable requirements of AMS2241.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) and macrostructure rating (3.5.1.1) of each heat.

4.2.1.2 Hardness (3.5.2.1.2) of bars and forgings, as solution heat treated.

4.2.1.3 Tensile properties (3.5.2.2.1) and hardness (3.5.2.2.2) of bars and forgings after precipitation heat treatment at 1000 °F (538 °C).

4.2.1.4 Tolerances (3.7) of bars.

4.2.2 Periodic Tests

The following requirements are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.2.1 Tensile properties (3.5.2.2.1) and hardness (3.5.2.2.2) of all product forms in other than the specified precipitation hardened condition.

4.2.2.2 Fracture toughness (3.5.2.2.3) of bars and forgings after precipitation heat treatment.

4.2.2.3 Frequency-severity cleanliness rating (3.6.1).

4.2.2.4 Grain flow of die forgings (3.6.4).

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars and Forging Stock

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the following results of tests and relevant information:

4.4.1 For each heat

Composition
Macrostructure.

4.4.2 For each lot of bars and forgings

As solution heat treated:

Hardness

After precipitation heat treatment to the H1000 hardened condition.

Tensile properties