



400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 6242C

Issued 1-23-40
Revised 10-1-82

STEEL BARS AND FORGINGS, CARBURIZING 5.0Ni (0.15 - 0.20C)

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 8-1-46. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "C" revision of the subject specification.

.....

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of 10-1-82. By this action, subject specification number and title will be deleted from the active specification index of Aerospace Material Specifications.

SAENORM.COM : Click to view the full PDF of ams6242c

This specification is under the jurisdiction of AMS Committee "E".

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6242C

Issued 1-23-40

Revised 5-1-45

STEEL - CARBURIZING 5 Ni (.15 - .20 C)

1. ACKNOWLEDGMENT: Vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Bars, billets, forgings, or as ordered.

3. COMPOSITION:

Individual Bar
Check Analysis
Over and Under

Carbon	0.15 - 0.20	0.01
Manganese	0.35 - 0.65	0.03
Phosphorus	0.040 max	0.005
Sulphur	0.040 max	0.005
Silicon	0.20 - 0.35	0.02
Nickel	4.75 - 5.25	0.07

4. GRAIN SIZE: 5 or finer, ASTM E19-39T, method a, unless otherwise specified. A heat of steel predominately 5 or finer, with grains as large as 3, is permissible.

5. HARDENABILITY: The hardenability shall be J46 max. and J26=8 min. when determined by the standard end-quench test specimen in accordance with the SAE Method of Determining Hardenability published in the latest revision of the SAE Handbook, except that the steel shall be normalized at 1700°F ± 10 and the test specimen austenitized at 1500°F ± 10.

6. CONDITION: (a) Unless otherwise specified, bar stock shall be supplied in a machinable condition with a hardness of not more than Brinell 229, except that if cold drawn stock is ordered, a hardness of Brinell 241 is permissible.

(b) Stock ordered for forging shall be supplied in the condition and finish ordered by the forging manufacturer.

(c) Forgings shall be supplied as ordered.

7. QUALITY: (a) This steel shall be aircraft quality. It shall be uniform in quality and condition, clean, sound, and free from foreign material and from internal and external defects which adversely affect its strength or machinability. Material revealing defects during fabrication shall be subject to rejection.

(b) Visual examination of deep acid etched bars in the as-furnished condition shall show no evidence of abnormal segregation, pipes, cracks, seams, or abnormal change in structure from the surface to the center.

(c) Unless otherwise stated, finished parts are subject to magnetic inspection.