

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 6275 A

Issued 12-1-51

Revised 3-1-55

### STEEL

0.4Cr - 0.45Ni - 0.1Mo - B (0.15-0.20C) (94B17)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, forgings, forging stock, and mechanical tubing.
3. **APPLICATION:** Carburized parts which require high minimum core hardness and allow wide hardness range in sections 0.50 in. and less in thickness. The core may or may not be machinable after hardening.
4. **COMPOSITION:**

#### Check Analysis Under Min or Over Max

Carbon	0.15 - 0.20	0.01	0.01
Manganese	0.75 - 1.00	0.04	0.04
Silicon	0.20 - 0.35	0.02	0.02
Phosphorus	0.040 max	--	0.005
Sulfur	0.040 max	--	0.005
Chromium	0.30 - 0.50	0.03	0.03
Nickel	0.30 - 0.60	0.03	0.03
Molybdenum	0.08 - 0.15	0.01	0.01
Boron	Present, but not exceeding 0.007		

5. **CONDITION:**
  - 5.1 **Bars:** In a machinable condition having hardness not higher than Brinell 229 or equivalent.
  - 5.2 **Tubing:** In a machinable condition.
  - 5.3 **Forgings:** As ordered.
  - 5.4 **Forging Stock:** As ordered by the forging manufacturer.
6. **TECHNICAL REQUIREMENTS:**
  - 6.1 **Hardenability:** The hardenability shall be  $J_{46}=1$  max and  $J_{29}=5$  min when determined by the standard end-quench test specimen in accordance with the SAE Method of Determining Hardenability published in the latest issue of the SAE Handbook, except that the steel shall be normalized at  $1700 F + 10$  and the test specimen austenitized at  $1550 F + 10$ . The hardenability test is not required on a product which will not yield a suitable specimen but the steel from which the product is made shall conform to the hardenability specified in this paragraph.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."