



# AEROSPACE MATERIAL SPECIFICATIONS

## AMS6275B

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

Issued 12-1-51  
Revised 3-15-66

### STEEL BARS, FORGINGS, AND TUBING 0. 40Cr - 0. 45Ni - 0. 12Mo - B (0. 15 - 0. 20C) (SAE 94B17)

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. FORM:** Bars, forgings, mechanical tubing, and forging stock.
- 3. APPLICATIONS:** Primarily for carburized parts which require moderately high core hardness and allow wide hardness range in sections 0.50 in. and less in thickness. The core may or may not be machinable after hardening.
- 4. COMPOSITION:**

	min	max
Carbon	0. 15	0. 20
Manganese	0. 75	1. 00
Silicon	0. 20	0. 35
Phosphorus	--	0. 025
Sulfur	--	0. 025
Chromium	0. 30	0. 50
Nickel	0. 30	0. 60
Molybdenum	0. 08	0. 15
Copper	--	0. 35
Boron	Present but not exceeding 0. 007	

- 4. 1 Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels".
- 5. CONDITION:**
  - 5. 1 Bars:** Unless otherwise specified, in a machinable condition and hot finished having hardness not higher than Brinell 229 or equivalent, except that bars ordered cold finished may have hardness as high as Brinell 248 or equivalent.
  - 5. 2 Forgings:** As ordered.
  - 5. 3 Mechanical Tubing:** In a machinable condition and cold finished, having hardness not higher than Rockwell C 25 or equivalent, except that tubing ordered hot finished shall be furnished in a machinable condition having hardness not higher than Rockwell B 99 or equivalent.
  - 5. 4 Forging Stock:** As ordered by the forging manufacturer.
- 6. TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.

SAE Technical Board rules provide that: "All technical reports, including standards applications and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."