

# AEROSPACE MATERIAL SPECIFICATION



AMS 6299D

Issued JAN 1964  
Revised FEB 2000

Superseding AMS 6299C

Steel Bars, Forgings, and Tubing  
0.50Cr - 1.8Ni - 0.25Mo (0.17 - 0.23C) (SAE 4320H)

UNS H43200

## 1. SCOPE:

### 1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock.

### 1.2 Application:

These products have been used typically for parts to be carburized requiring high minimum core hardness with wide range in sections 0.375 inch (9.5 mm) and under in thickness, but usage is not limited to such applications. The core may or may not be machinable after hardening.

## 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2251 Tolerances, Low-Alloy Steel Bars
- MAM 2251 Tolerances, Metric, Low-Alloy Steel Bars
- AMS 2253 Tolerances, Carbon and Alloy Steel Tubing
- MAM 2253 Tolerances, Metric, Carbon and Alloy Steel Tubing
- AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2301 Cleanliness, Aircraft Quality Steel, Magnetic Particle Inspection Procedure
- MAM 2301 Cleanliness, Aircraft Quality Steel, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
- AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2.1 (Continued):

- AMS 2372 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings  
 AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys  
 AMS 2808 Identification, Forgings
- AS1182 Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Bars and Mechanical Tubing

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM A 255 End-Quench Test for Hardenability of Steel  
 ASTM A 370 Mechanical Testing of Steel Products  
 ASTM E 112 Determining the Average Grain Size  
 ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron  
 ASTM E 381 Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350 or by spectrographic or other analytical methods approved by purchaser:

TABLE 1 - Composition

Element	Min	Max
Carbon	0.17	0.23
Manganese	0.40	0.70
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.35	0.65
Nickel	1.55	2.00
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

## 3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

## 3.2.1 Bars:

3.2.1.1 Bars 0.500 Inch (12.50 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides: Cold finished having tensile strength not higher than 125 ksi (860 MPa) or equivalent hardness (See 8.2).

3.2.1.2 Bars Over 0.500 Inch (12.50 mm) in Nominal Diameter or Least Distance Between Parallel Sides: Hot finished and annealed, unless otherwise ordered, having hardness not higher than 229 HB, or equivalent (See 8.3). Bars ordered cold finished may have hardness as high as 248 HB, or equivalent.

3.2.2 Forgings: As ordered.

3.2.3 Mechanical Tubing: Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.3). Tubing ordered hot finished and annealed shall have hardness not higher than 99 HB, or equivalent.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

## 3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Square Inches	Square Centimeters	Macrographs
Up to 36, incl	Up to 230, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 230 to 645, incl	S2 - R2 - C3

3.3.2 Average Grain Size: Shall be ASTM 5 or finer determined in accordance with ASTM E 112 (See 8.4).

3.3.3 Hardenability: Shall be J1/16 inch (1.5 mm) = HRC 48 maximum and J4/16 (6 mm) = 32 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255, except that the steel shall be normalized at 1675 °F ± 10 (915 °C ± 5) and the test specimen austenitized at 1500 °F ± 10 (815 °C ± 5) (See 8.5).

#### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft quality conforming to AMS 2301 or MAM 2301.

3.4.2 Bars and tubing ordered hot rolled or cold drawn, or ground, turned, or polished, shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

#### 3.5 Tolerances:

Shall be as follows:

3.5.1 Bars: In accordance with AMS 2251 or MAM 2251.

3.5.2 Mechanical Tubing: In accordance with AMS 2253 or MAM 2253.

### 4. QUALITY ASSURANCE PROVISIONS:

#### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

#### 4.2 Classification of Tests:

4.2.1 All technical requirements of this specification are acceptance tests and shall be performed on each heat or lot as applicable.

#### 4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.3.2 Forgings: In accordance with AMS 2372.