

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 6305C

Issued MAY 1973
Revised APR 1997

Superseding AMS 6305B

Submitted for recognition as an American National Standard

STEEL, HEAT RESISTANT, BARS, FORGINGS, AND TUBING
0.95Cr - 0.55Mo - 0.30V (0.40 - 0.50C)
Vacuum Arc Remelted

UNS K14675

1. SCOPE:

1.1 Form:

This specification covers a premium aircraft-quality, low-alloy, heat-resistant steel in the form of bars, forgings, mechanical tubing, and forging stock.

1.2 Application:

These products have been used typically for parts, such as compressor discs, turbine discs, shafts, and fasteners, for use in service up to 1000 °F (538 °C) and subject to stringent magnetic particle inspection standards, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1997 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT: (412) 772-7154 FAX (412) 776-0243
TO PLACE A DOCUMENT ORDER: (412) 776-4970 FAX (412) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2251	Tolerances, Low-Alloy Steel Bars
MAM 2251	Tolerances, Metric, Low-Alloy Steel Bars
AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
MAM 2253	Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
MAM 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AS1182	Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370	Mechanical Testing of Steel Products
ASTM A 604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E112	Determining the Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.40	0.50
Manganese	0.40	0.70
Silicon	0.15	0.35
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	0.80	1.10
Molybdenum	0.45	0.65
Vanadium	0.25	0.35
Nickel	--	0.25
Copper	--	0.35
Lead	--	0.001 (10 ppm)

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Melting Practice:

Steel shall be multiple melted using consumable electrode vacuum practice (VAR) in the remelt cycle.

3.3 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.3.1 Bars:

3.3.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 125 ksi (862 MPa) or hardness not higher than 27 HRC.

3.3.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Distance Between Parallel Sides:
(R) Hot finished and annealed, unless otherwise ordered, having hardness not higher than 229 HB, or equivalent (See 8.2). Bars ordered cold finished may have hardness as high as 248 HB, or equivalent.

3.3.2 Forgings: Annealed having hardness not higher than 248 HB, or equivalent (See 8.2).

3.3.3 Mechanical Tubing: Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.2). Tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent.

3.3.4 Forging Stock: As ordered by the forging manufacturer.

3.4 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

- 3.4.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds or tubes, and forging stock, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Except as specified in 3.4.1.1, porosity, segregation, inclusions, and other imperfections for product 36 square inches (232 cm²) and under in nominal cross-sectional area shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - Macrostructure Limits

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

- 3.4.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

- 3.4.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with (R) ASTM E 112 (See 8.3).

3.4.3 Decarburization:

- 3.4.3.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.4.3.2 Allowable decarburization of bars, billets, and tube rounds ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.4.3.3 Decarburization of bars to which 3.4.3.1 or 3.4.3.2 is not applicable shall be not greater than shown in Table 3.

TABLE 3A - Maximum Decarburization, Inch/Pound Units

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.015
Over 0.375 to 0.500, incl	0.017
Over 0.500 to 0.625, incl	0.019
Over 0.625 to 1.000, incl	0.022
Over 1.000 to 1.500, incl	0.025
Over 1.500 to 2.000, incl	0.030
Over 2.000 to 2.500, incl	0.035
Over 2.500 to 3.000, incl	0.040
Over 3.000 to 4.000, incl	0.045

TABLE 3B - Maximum Decarburization, SI Units

Nominal Diameter or Distance Between Parallel Sides Millimeters	Depth of Decarburization Millimeters
Up to 9.52, incl	0.38
Over 9.52 to 12.70, incl	0.43
Over 12.70 to 15.88, incl	0.48
Over 15.88 to 25.40, incl	0.56
Over 25.40 to 38.10, incl	0.64
Over 38.10 to 50.80, incl	0.76
Over 50.80 to 63.50, incl	0.89
Over 63.50 to 76.20, incl	1.02
Over 76.20 to 101.60, incl	1.14

3.4.3.4 Decarburization of tubing to which 3.4.3.1 or 3.4.3.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4A - Maximum Decarburization, Inch/Pound Units

Nominal Wall Thickness Inches	Depth ID Inch	Depth OD Inch
Up to 0.109, incl	0.008	0.020
Over 0.109 to 0.203, incl	0.010	0.025
Over 0.203 to 0.400, incl	0.012	0.030
Over 0.400 to 0.600, incl	0.015	0.035
Over 0.600 to 1.000, incl	0.017	0.040
Over 1.000	0.020	0.045

TABLE 4B - Maximum Decarburization, SI Units

Nominal Wall Thickness Millimeters	Depth ID Millimeter	Depth OD Millimeter
Up to 2.77, incl	0.20	0.51
Over 2.77 to 5.16, incl	0.25	0.64
Over 5.16 to 10.16, incl	0.30	0.76
Over 10.16 to 15.24, incl	0.38	0.89
Over 15.24 to 25.40, incl	0.43	1.02
Over 25.40	0.51	1.14

3.4.3.5 Decarburization shall be measured by the microscopic method or the HR30N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization thereon.

3.4.3.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300 or MAM 2300.

3.5.2 Bars and mechanical tubing ordered hot rolled or cold drawn or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.5.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.6 Tolerances:

Shall be as follows:

3.6.1 Bars: In accordance with AMS 2251 or MAM 2251.

3.6.2 Mechanical Tubing: In accordance with AMS 2253 or MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), condition (3.3.1, 3.3.2, and 3.3.3), macrostructure (R) rating (3.4.1), average grain size (3.4.2), decarburization (3.4.3), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Frequency-severity cleanliness rating (3.5.1) and grain flow of die forgings (R) (3.5.3) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.