

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 6323H

Issued 1 NOV 1944
Revised 1 OCT 1991

Superseding AMS 6323G

Submitted for recognition as an American National Standard

STEEL TUBING, MECHANICAL
0.50Cr - 0.55Ni - 0.25Mo (0.38 - 0.43C) (SAE 8740)

UNS G87400

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of mechanical tubing.

1.2 Application:

This tubing has been used typically for parts, 0.375 inch (9.52 mm) and under in section thickness at time of heat treatment, requiring a through-hardening steel capable of developing hardness as high as 50 HRC when properly hardened and tempered and also parts of greater thickness but requiring proportionately lower hardness, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 6323H

SAE

AMS 6323H

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2253 Tolerances, Carbon and Alloy Steel Tubing
- MAM 2253 Tolerances, Metric, Carbon and Alloy Steel Tubing
- AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2301 Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
- AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AS1182 Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM A 255 End-Quench Test for Hardenability of Steel
- ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
- ASTM E 112 Determining Average Grain Size
- ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
- ASTM E 381 Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

AMS 6323H

SAE

AMS 6323H

3. TECHNICAL REQUIREMENTS:

3.1 Composition:
(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.38	0.43
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

Cold finished having hardness not higher than 25 HRC, or equivalent, except that tubing ordered hot finished and annealed or tempered shall have hardness not higher than 99 HRB, or equivalent; hardness shall be determined in accordance with ASTM E 18.

3.3 Properties:

Tubing shall conform to the following requirements:

AMS 6323H

SAE

AMS 6323H

3.3.1 Macrostructure: Visual examination of transverse sections from bars, (R) billets, tube rounds, or tubes, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Except as specified in 3.3.1.1, porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure

Section Size Square Inches	Section Size Square Centimeters	Macrographs
Up to 36, incl	Up to 232, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 232 to 645, incl	S2 - R2 - C3
Over 100	Over 645	As agreed upon

3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

3.3.2 Grain Size: Predominately 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E 112.

3.3.3 Hardenability: Shall be J50=5 minimum and J40=8 minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at $1700\text{ }^{\circ}\text{F} \pm 10$ ($927\text{ }^{\circ}\text{C} \pm 6$) and the test specimen austenitized at $1500\text{ }^{\circ}\text{F} \pm 10$ ($816\text{ }^{\circ}\text{C} \pm 6$). The hardenability test is not required on tubing which will not yield a suitable specimen but the steel from which the tubing is made shall conform to the hardenability specified.

3.3.4 Decarburization:

3.3.4.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.4.2 Allowable decarburization of pierced billets, of tube rounds and tubing for redrawing or forging, or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.4.3 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 3.

AMS 6323H

SAE

AMS 6323H

TABLE 3A - Decarburization, Inches

Nominal Wall Thickness	Maximum Depth ID	Maximum Depth OD
Up to 0.109, incl	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

TABLE 3B - Decarburization, Millimeters

Nominal Wall Thickness	Maximum Depth ID	Maximum Depth OD
Up to 2.77, incl	0.20	0.38
Over 2.77 to 5.16, incl	0.25	0.51
Over 5.16 to 10.16, incl	0.30	0.64
Over 10.16 to 15.24, incl	0.38	0.76
Over 15.24 to 25.40, incl	0.43	0.89
Over 25.40	0.51	1.02

3.3.4.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.4.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits of Table 3 by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

AMS 6323H

SAE

AMS 6323H

3.4 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 Mechanical tubing ordered hot rolled or cold drawn or ground,
(R) turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2253 or MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R) The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

(R) Shall be in accordance with AMS 2370.

4.4 Reports:

The vendor of tubing shall furnish with each shipment a report showing the results of tests for chemical composition, hardness, macrostructure, grain size, hardenability, and frequency-severity cleanliness rating of each heat. This report shall include the purchase order number, lot number, AMS 6323H, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.