

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6358

Issued 10-1-43

Revised

STEEL PLATE, SHEET AND STRIP .55 Ni .5 Cr .25 Mo (.38-.43 C)

1. ACKNOWLEDGMENT: A vendor must mention this specification number in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

		<u>Individual Sheet</u> <u>Check Analysis</u> <u>Over or Under</u>
Carbon	0.38 - 0.43	0.02
Manganese	0.75 - 1.00	0.04
Phosphorus	0.040 max	0.005
Sulphur	0.040 max	0.005
Silicon	0.20 - 0.35	0.02
Nickel	0.40 - 0.70	0.03
Chromium	0.40 - 0.60	0.03
Molybdenum	0.20 - 0.30	0.03

3. GRAIN SIZE: 5 or finer as determined on the rerolling slab, ASTM E19-39T, method a, unless otherwise ordered. A heat of steel predominately 5 or finer with grains as large as 3 is permissible.

4. CONDITION: (a) Cold-finished and clean annealed, unless otherwise ordered, to conform to a maximum tensile strength of 90,000 lb per sq in.

(b) Test specimens cut in any direction shall withstand cold bending, without cracking, through the angle indicated below over a diameter equal to the thickness of the specimen, bend tests not being required on plates 3/4 inch or over in thickness:

<u>Thickness of Material, inch</u>	<u>Angle of Bend, degrees</u> <u>(min)</u>
0.249 and less	180
Over 0.249 to 0.749, incl.	90

5. QUALITY: (a) This material must be aircraft quality, uniform in condition, free from surface or internal defects, and must not reveal injurious defects during heat treatment or fabrication.

(b) The surface shall not be decarburized to the extent of affecting the Rockwell hardness (A scale) after heat treating.

(c) All plates, sheets and strips shall be commercially straight, flat, clean, smooth and free from seams, laminations, blisters, scale, and other injurious defects.

(d) Unless otherwise specified, finished parts are subject to magnetic inspection.