

AEROSPACE MATERIAL SPECIFICATION



AMS 6360K

Issued DEC 1939
Revised JUN 2000

Superseding AMS 6360J

Steel Tubing, Seamless
0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)
Normalized or Stress Relieved

UNS G41300

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of seamless tubing.

1.2 Application:

This tubing has been typically used in thin-walled sections where minimum tensile strength up to 160,000 psi (1103 MPa) is required and where parts may be welded during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2253 Tolerances, Carbon and Alloy Steel Tubing
MAM 2253 Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301 Cleanliness, Aircraft Quality Steel, Magnetic Particle Inspection Procedure
MAM 2301 Cleanliness, Aircraft Quality Steel, Magnetic Particle Inspection Procedure, Metric (SI)
Measurements

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock

AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 112 Determining the Average Grain Size

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 1444 Magnetic Particle Examination

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

TABLE 1 - Composition

Element	min	max
Carbon	0.28	0.33
Manganese	0.40	0.60
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The tubing shall be supplied cold finished and either normalized and tempered, stress relieved, or otherwise heat treated.

3.3 Properties:

Tubing shall conform to the following requirements; tensile testing shall be performed in accordance with ASTM A 370:

3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

Nominal OD Inch	Nominal Wall Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches % Full Tube	Elongation in 2 Inches % Strip
Up to 0.500, excl	Up to 0.188, incl	95	75	10	-
Up to 0.500, excl	Over 0.188	90	70	10	-
0.500 and over	Up to 0.188, incl	95	75	12	7
0.500 and over	Over 0.188	90	70	15	10

TABLE 2B - Minimum Tensile Properties, SI Units

Nominal OD Millimeters	Nominal Wall Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm % Full Tube	Elongation in 50.8 mm % Strip
Up to 12.70, excl	Up to 4.78, incl	655	517	10	-
Up to 12.70, excl	Over 4.78	621	483	10	-
12.70 and over	Up to 4.78, incl	655	517	12	7
12.70 and over	Over 4.78	621	483	15	10

3.3.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112 (See 8.3).

3.3.3 Decarburization:

3.3.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Decarburization on tubing ID shall not exceed the maximum depth specified in Table 3.

3.3.3.2 Allowable decarburization of pierced billets, of tubing for redrawing, or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.3.3 Tubing to which 3.3.3.1 or 3.3.3.2 is not applicable shall be free from complete decarburization. Partial decarburization shall not exceed the limits specified in Table 3.

TABLE 3A - Maximum Decarburization, Inch/Pound Units

Nominal Wall Thickness (T) Inch	Depth of Partial Decarburization	Depth of Partial Decarburization	Depth of Partial Decarburization
	Inch ID	Inch OD	Inch ID+OD
Up to 0.040, incl	0.18T	0.18T	0.25T
Over 0.040 to 0.050, incl	0.009	0.009	0.012
Over 0.050 to 0.070, incl	0.010	0.010	0.014
Over 0.070 to 0.080, incl	0.012	0.012	0.016
Over 0.080 to 0.090, incl	0.014	0.014	0.018
Over 0.090 to 0.100, incl	0.015	0.015	0.020
Over 0.100 to 0.150, incl	0.017	0.017	0.022
Over 0.150 to 0.200, incl	0.020	0.020	0.026

TABLE 3B - Maximum Decarburization, SI Units

Nominal Wall Thickness (T) Millimeters	Depth of Partial Decarburization	Depth of Partial Decarburization	Depth of Partial Decarburization
	Millimeter ID	Millimeter OD	Millimeter ID+OD
Up to 1.02, incl	0.18T	0.18T	0.25T
Over 1.02 to 1.27, incl	0.23	0.23	0.30
Over 1.27 to 1.78, incl	0.25	0.25	0.36
Over 1.78 to 2.03, incl	0.30	0.30	0.41
Over 2.03 to 2.29, incl	0.36	0.36	0.46
Over 2.29 to 2.54, incl	0.38	0.38	0.51
Over 2.54 to 3.81, incl	0.43	0.43	0.56
Over 3.81 to 5.08, incl	0.51	0.51	0.66

3.3.3.4 Decarburization shall be measured by the microscopic method, by HR30N scale hardness testing method, or by the microhardness traverse method on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization on the adjacent surface. In case of dispute, the depth of decarburization determined using the microhardness traverse method shall govern.

3.3.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 When specified, the tubing, either with or without machining of the surface, shall be subjected to magnetic particle inspection in accordance with ASTM E 1444. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2253 or MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.