



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

AMS 6365E

Superseding AMS 6365D

Issued 6-1-42

Revised 5-1-68

STEEL TUBING, SEAMLESS
0.95Cr - 0.20Mo (0.33 - 0.38C) (SAE 4135)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for general use where welding and moderate tensile properties are required. Extensively used when minimum tensile strength of 160,000 psi is required.
3. COMPOSITION:

	min	max
Carbon	0.33	0.38
Manganese	0.70	0.90
Silicon	0.20	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

- 3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels".
4. CONDITION: Normalized and tempered, stress relieved, or otherwise heat treated after the last cold drawing operation.
5. TECHNICAL REQUIREMENTS: When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.
 - 5.1 Tensile Properties:

Nominal OD Inches	Nominal Wall Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 30,000,000)		Elongation % in 2 In. min	
			psi, min	Extension Under Load in. in 2 in.	Full Tube	Strip
Up to 0.499, incl	Up to 0.188, incl	100,000	85,000	0.0097	8	--
Up to 0.499, incl	Over 0.188	95,000	80,000	0.0093	10	--
Over 0.499	Up to 0.188, incl	100,000	85,000	0.0097	12	7
Over 0.499	Over 0.188	95,000	80,000	0.0093	15	10

- 5.2 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, ASTM E112, McQuaid-Ehn test.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.3 Decarburization:

- 5.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Inside decarburization of such tubing shall not exceed the maximum depth specified in 5.3.3.
- 5.3.2 Allowable decarburization of pierced billets or of tubing for redrawing or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 5.3.3 Unless otherwise agreed upon between purchaser and vendor, tubing to which 5.3.1 or 5.3.2 is not applicable shall be free from complete decarburization. Partial decarburization shall not exceed the following:

Nominal Wall Thickness Inch	<u>Maximum Depth of Partial Decarburization, Inch</u>		
	Inside	Outside	Inside + Outside
Up to 0.040, incl	0.008	0.008	0.010
Over 0.040 to 0.050, incl	0.009	0.009	0.012
Over 0.050 to 0.070, incl	0.010	0.010	0.014
Over 0.070 to 0.080, incl	0.012	0.012	0.016
Over 0.080 to 0.090, incl	0.014	0.014	0.018
Over 0.090 to 0.100, incl	0.015	0.015	0.020
Over 0.100 to 0.150, incl	0.017	0.017	0.022
Over 0.150 to 0.200, incl	0.020	0.020	0.026

- 5.3.4 Unless otherwise agreed upon by purchaser and vendor, decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale hardness method, or equivalent hardness testing method, on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization when measured by a hardness method, is defined as the perpendicular distance from the surface to the nondecarburized depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.
- 5.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits above by more than 0.005 in. and the width is 0.065 in. or less.
6. QUALITY: Steel shall be aircraft quality and shall conform to the latest issue of AMS 2301. Tubing shall be uniform in quality and condition and shall have a good workmanlike finish conforming to the best practice for high quality material. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for diameter and wall thickness. The removal of surface imperfections is not required.
- 6.1 When specified, the tubing, either with or without machining of the surfaces, shall be capable of passing magnetic particle inspection in accordance with AMS 2640. Standards for acceptance shall be as agreed upon by purchaser and vendor.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2253.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition, tensile properties, grain size, and AMS 2301 frequency-severity rating of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.