

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6371C

Issued 12-1-42

Revised 10-1-51

STEEL TUBING, MECHANICAL
0.95Cr - 0.2Mo (0.28-0.33C) (SAE 4130)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Heavy wall tubing for machining.
3. **APPLICATION:** Parts with sections 0.50 in. or less in thickness at the time of heat treatment which require a through-hardening steel capable of developing hardness as high as Rockwell C 35 when properly hardened and tempered and also parts of greater thickness but requiring proportionately lower hardness.

4. **COMPOSITION:**

		Check Analysis	
		Under Min	or Over Max
Carbon	0.28 - 0.33	0.02	0.02
Manganese	0.40 - 0.60	0.03	0.03
Silicon	0.20 - 0.35	0.02	0.02
Phosphorus	0.040 max	--	0.005
Sulfur	0.040 max	--	0.005
Chromium	0.80 - 1.10	0.05	0.05
Molybdenum	0.15 - 0.25	0.02	0.02

5. **CONDITION:** In a machinable condition, and, unless otherwise specified, cold finished.
6. **TECHNICAL REQUIREMENTS:**
 - 6.1 **Hardenability:** The hardenability shall be J35=5 min and J28=8 min when determined by the standard end-quench test specimen in accordance with the SAE Method of Determining Hardenability published in the latest issue of the SAE Handbook, except that the steel shall be normalized at 1700 F \pm 10 and the test specimen austenitized at 1600 F \pm 10. The hardenability test is not required on tubing which will not yield a suitable specimen but the steel from which the tubing is made shall conform to the hardenability specified in this paragraph.
 - 6.2 **Grain Size:** Five or finer as determined on the billet, ASTM E19-46, method a. A heat of steel predominantly five or finer with grains as large as three is permissible.
 - 6.3 **Decarburization:**
 - 6.3.1 Tubing ordered ground, turned, or polished shall be free from outside decarburization on such ground, turned or polished surfaces. Inside decarburization shall not exceed the maximum depth specified in 6.3.3.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committee will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."