



AEROSPACE MATERIAL SPECIFICATION	AMS6371™	REV. M
	Issued 1942-12 Reaffirmed 2008-04 Revised 2022-10	
Superseding AMS6371L		
Steel, Mechanical Tubing 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130) (Composition similar to UNS G41300)		

RATIONALE

AMS6371M is the result of a Five-Year Review and update of the specification. The revision updates composition testing and reporting (3.1, 3.1.2), clarifies exceptions requirements (3.6, 8.6), adds exception for Jominy testing (3.3.2), revises the decarburization requirements (3.3.3.3.1, 3.3.3.3.2), incorporates the requirements of AMS2301 (4.2.1, 4.4.3), adds finish guidance (8.4), and allows prior revisions (8.5).

1. SCOPE

1.1 Form

This specification covers an aircraft-quality, low-alloy steel in the form of mechanical tubing.

1.2 Application

This tubing has been used typically for parts, 0.375 inch (9.52 mm) and under in nominal wall thickness at time of heat treatment requiring a through-hardening steel capable of developing hardness as high as 40 HRC when properly hardened and tempered and for parts of greater wall thickness but requiring proportionately lower hardness, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

- AMS2253 Tolerances, Carbon and Alloy Steel Tubing
- AMS2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS2301 Steel Cleanliness, Aircraft Quality Magnetic Particle Inspection Procedure

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS6371M/>

- AMS2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
- AMS2806 Identification Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion- and Heat-Resistant Steels and Alloys
- AS1182 Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing
- AS7766 Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

- ASTM A255 Determining Hardenability of Steel
- ASTM A370 Mechanical Testing of Steel Products
- ASTM A751 Chemical Analysis of Steel Products
- ASTM E112 Determining Average Grain Size
- ASTM E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness
- ASTM E1077 Estimating the Depth of Decarburization of Steel Specimens

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751 or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	0.28	0.33
Manganese	0.40	0.60
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

- 3.1.1 Aluminum, vanadium, and columbium (niobium) are optional grain refining elements and need not be determined or reported unless used to satisfy the average grain size requirements of 3.3.2.2.
- 3.1.2 Producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.3 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Condition

Cold finished unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (see 8.2). Tubing ordered hot finished and annealed or tempered shall have hardness not higher than 99 HRB, or equivalent (see 8.2). Hardness shall be determined in accordance with ASTM A370.

3.3 Properties

Tubing shall conform to the following requirements:

3.3.1 Grain Size

Average grain size shall be determined by either 3.3.1.1 or 3.3.1.2.

3.3.1.1 Shall be ASTM No. 5 or finer, determined in accordance with ASTM E112.

3.3.1.2 The product of a heat shall be considered to have an ASTM No. 5 or finer austenitic grain size if one or more of the following are determined by heat analysis (see 8.3):

3.3.1.2.1 A total aluminum content of 0.020 to 0.050%.

3.3.1.2.2 An acid soluble aluminum content of 0.015 to 0.050%.

3.3.1.2.3 A vanadium content of 0.02 to 0.08%.

3.3.1.2.4 A columbium (niobium) content of 0.02 to 0.05%.

3.3.2 Hardenability

Shall be J 5/16 inch (7.9 mm) = 35 HRC minimum and J 8/16 inch (13 mm) = 28 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A255 except that the steel shall be normalized at 1700 °F ± 10 °F (927 °C ± 6 °C) and the test specimen austenitized at 1600 °F ± 10 °F (871 °C ± 6 °C). Cast specimens do not need to be normalized.

3.3.3 Decarburization

3.3.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.3.2 Decarburization of tubing that 3.3.3.1 is not applicable shall be not greater than shown in Table 2.

Table 2A - Maximum depth of decarburization, inch/pound units

Nominal Wall Thickness Inches	Total Depth of Decarburization	Total Depth of Decarburization
	Inches ID	Inches OD
Up to 0.109, incl	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

Table 2B - Maximum depth of decarburization, SI units

Nominal Wall Thickness Millimeters	Total Depth of Decarburization	Total Depth of Decarburization
	Millimeters ID	Millimeters OD
Up to 2.77, incl	0.20	0.38
Over 2.77 to 5.16, incl	0.25	0.51
Over 5.16 to 10.16, incl	0.30	0.64
Over 10.16 to 15.24, incl	0.38	0.76
Over 15.24 to 25.40, incl	0.43	0.89
Over 25.40	0.51	1.02

3.3.3.3 Decarburization shall be evaluated by one of the two methods of 3.3.3.3.1 or 3.3.3.3.2.

3.3.3.3.1 Metallographic (Microscopic) Method

A cross section taken perpendicular to the surface shall be etched and examined metallographically at a magnification not to exceed 200X in accordance with ASTM E1077. The product shall not show a layer of complete (ferrite) or partial decarburization exceeding the limits of Table 2.

3.3.3.3.2 Hardness Traverse (Microindentation) Method

The total depth of decarburization shall be determined by a traverse method using microindentation hardness testing in accordance with ASTM E1077. Samples shall be hardened in a protective atmosphere to prevent changes in surface carbon content. Samples may be tempered at the option of the producer. Measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization on the adjacent surface. Acceptance shall be as listed in Table 2.

3.3.3.3.3 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.3.3.3.4 In case of dispute, the total depth of decarburization determined using the microindentation hardness traverse method shall govern.

3.4 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Steel shall be aircraft quality conforming to AMS2301.

3.4.2 Mechanical tubing shall be free from seams, laps, tears, and cracks after removal of the standard stock removal allowance in accordance with AS1182.

3.5 Tolerances

Shall conform to all applicable requirements of AMS2253.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), condition (3.2), average grain size (3.3.1), hardenability (3.3.2), decarburization (3.3.3), and frequency-severity cleanliness (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable. If grain refining elements (3.3.1.2) are not present, the ASTM E112 grain size test (3.3.1.1) shall be conducted on each lot. If process qualification in accordance with AMS2301 has been met, the frequency-severity cleanliness rating shall be conducted on a periodic basis as defined in AMS2301.

4.2.2 Periodic Tests

If grain refining elements (3.3.1.2) are present, the ASTM E112 grain size test (3.3.1.1) shall be conducted on a periodic basis and shall be performed at a frequency selected by the producer (not to exceed 1 year) unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

In accordance with AMS2370.

4.4 Reports

4.4.1 The producer of tubing shall furnish with each shipment a report showing producer identity, country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations), the results of composition, hardenability, and frequency-severity rating (see 4.4.3) for each heat and for hardness and average grain size for each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS6371M, size, and quantity. If the grain size requirement of 3.3.1 is met by the aluminum, vanadium and/or columbium (niobium) content, the aluminum, vanadium and/or columbium (niobium) content shall be reported and a statement that the chemistry satisfies the grain size requirement shall be included.

4.4.2 When material produced to this specification has exceptions taken to the technical requirements listed in Section 3, (see 5.2.1) the report shall contain a statement "This material is certified as AMS6371M(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

4.4.3 Reduced Testing

If the producer has qualified for periodic testing for frequency-severity cleanliness rating in accordance with AMS2301, then the frequency severity cleanliness rating is not required to be reported for each shipment. In this circumstance the report shall read "Process qualification in accordance with AMS2301 has been completed."