



# AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.  
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

# SPECIFICATION

## AMS 6373A

Superseding AMS 6373

Issued 11/1/69

Revised 5-1-70

STEEL TUBING, WELDED  
0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for general use where parts are fabricated by welding and moderate tensile properties are required. Extensively used in applications requiring a minimum tensile strength of 160,000 psi after proper heat treatment.
- 3. COMPOSITION:**

	min	max
Carbon	0.28	0.33
Manganese	0.40	0.60
Silicon	0.20	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

- 3.1 Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels".
- 4. CONDITION:** Normalized and tempered, stress relieved, or otherwise heat treated after the last cold drawing operation.
- 5. TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.

**5.1 Tensile Properties:**

Nominal Wall Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 29,000,000)		Elongation % in 2 in. min	
		psi, min	Extension Under Load in. in 2 in.	Full Tube	Strip
Up to 0.035, incl	95,000	75,000	0.0092	10	5
Over 0.035 to 0.187, incl	95,000	75,000	0.0092	12	7
Over 0.187 to 0.200, incl	90,000	70,000	0.0088	15	10

- 5.2 Grain Size:** Predominantly 5 or finer with occasional grains as large as 3 permissible, ASTM E112, McQuaid-Ehn test.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.3 Decarburization:

- 5.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Inside decarburization of such tubing shall not exceed the maximum depth specified in 5.3.3.
- 5.3.2 Allowable decarburization of tubing for redrawing or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 5.3.3 Unless otherwise agreed upon by purchaser and vendor, tubing to which 5.3.1 or 5.3.2 is not applicable shall be free from complete decarburization. Partial decarburization shall not exceed the following:

Nominal Wall Thickness (T) Inch	Depth of Partial Decarburization, Inch		
	ID	OD	ID + OD
Up to 0.040, incl	0.25T	0.25T	0.30T
Over 0.040 to 0.050, incl	0.009	0.009	0.012
Over 0.050 to 0.070, incl	0.010	0.010	0.014
Over 0.070 to 0.080, incl	0.012	0.012	0.016
Over 0.080 to 0.090, incl	0.014	0.014	0.018
Over 0.090 to 0.100, incl	0.015	0.015	0.020
Over 0.100 to 0.150, incl	0.017	0.017	0.022
Over 0.150 to 0.200, incl	0.020	0.020	0.026

- 5.3.4 Unless otherwise agreed upon by purchaser and vendor, decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale hardness method, or equivalent hardness testing method, on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.
- 5.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits above by more than 0.005 in. and the width is 0.065 in. or less.
- 6. QUALITY: Steel shall be aircraft quality and shall conform to the latest issue of AMS 2301. Tubing shall be uniform in quality and condition and shall have a workmanlike finish conforming to the best practice for high quality material. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified herein for wall thickness. The removal of surface imperfections is not required.
- 6.1 When specified, the tubing, either with or without machining of the surfaces, shall be capable of passing magnetic particle inspection in accordance with AMS 2640. Standards for acceptance shall be as agreed upon by purchaser and vendor.
- 7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2253.
- 8. QUALITY ASSURANCE SAMPLING AND TESTING: Shall be in accordance with all applicable requirements of the latest issue of AMS 2370.