

AEROSPACE
MATERIAL
SPECIFICATION

AMS 6378B
Superseding AMS 6378A

Issued 7-15-61
Revised 10-1-81

STEEL BARS

0.95Cr - 0.20Mo - 0.015Te (0.39 - 0.48C) (4142H Modified)
Die-Drawn and Tempered, 130,000 psi (895 MPa) Yield Strength
Free Machining

1. SCOPE:

1.1 Form: This specification covers a free-machining, low-alloy steel in the form of round bars 3.50 in. (90 mm) and under in nominal diameter.

1.2 Application: Primarily for parts such as shafts, axles, pins, fasteners, gears, and screw machine parts which are normally used at hardness of 30 - 36 HRC and which do not require a high degree of ductility.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Materials Specifications (AMS) and Aerospace Standards (AS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2251 - Tolerances, Low-Alloy Steel Bars

AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2350 - Standards and Test Methods

AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 6378B

2.1.2 Aerospace Standards:

AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E112 - Estimating the Average Grain Size of Metals

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E381 - Rating Macroetched Steel

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

Ø

	min	max
Carbon	0.39	0.48
Manganese	0.70	1.10
Silicon	0.15	0.35
Phosphorus	--	0.040
Sulfur (3.1.1)	0.04	0.060
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Tellurium (3.1.1)	0.01	0.02
Nickel	--	0.25
Copper	--	0.35

3.1.1 Selenium may be substituted for tellurium. In such event, selenium shall be Ø 0.03 - 0.06 and sulfur shall be 0.040 maximum.

3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: Bars shall be elevated-temperature die-drawn, straightened, and tempered.

3.2.1 Temperatures for die drawing shall be selected significantly above room temperature but below the transformation range to produce a uniform structure of deformed pearlite and ferrite providing good machinability.

3.3 Properties: Bars shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.3.1 Grain Size: Predominantly 5 or finer with occasional grains as large as ϕ 3 permissible, determined in accordance with ASTM E112.

3.3.2 Macrostructure: Visual examination of transverse sections from bars and billets, etched in accordance with ASTM E381 in hot hydrochloric acid (1:1) at 160° - 180°F (70° - 80°C) for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the following macrographs of ASTM E381:

Section Size		Macrographs
Square Inches	(Square Centimetres)	
Up to 36, incl	(Up to 230, incl)	S2 - R1 - C2
Over 36 to 100, incl	(Over 230 to 645, incl)	S2 - R2 - C3
Over 100	(Over 645)	As agreed upon

3.3.3 Decarburization:

3.3.3.1 Bars ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.3.2 Decarburization of bars to which 3.3.3.1 is not applicable shall be not greater than shown in Table I.

TABLE I

Nominal Diameter Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.012
Over 0.500 to 0.625, incl	0.014
Over 0.625 to 1.000, incl	0.017
Over 1.000 to 1.500, incl	0.020
Over 1.500 to 2.000, incl	0.025
Over 2.000 to 2.500, incl	0.030
Over 2.500 to 3.000, incl	0.035
Over 3.000 to 3.500, incl	0.040

TABLE I (SI)

Nominal Diameter Millimeters	Depth of Decarburization Millimeters
Up to 9.40, incl	0.25
Over 9.40 to 12.50, incl	0.30
Over 12.50 to 15.75, incl	0.35
Over 15.75 to 25.00, incl	0.42
Over 25.00 to 37.50, incl	0.50
Over 37.50 to 50.00, incl	0.62
Over 50.00 to 62.50, incl	0.75
Over 62.50 to 75.00, incl	0.88
Over 75.00 to 87.50, incl	1.00

3.3.3.3 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on specimens cut from bars. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.3.3.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 in. (0.13 mm) and the width is 0.065 in. (1.65 mm) or less.

3.3.4 Tensile Properties: Specimens, cut from the center of bars 1.50 in. (37.5 mm) and under in nominal diameter and at the mid-radius on sizes larger than 1.50 in. (37.5 mm), shall conform to the following:

Tensile Strength, min	150,000 psi (1035 MPa)
Yield Strength at 0.2% Offset, min	130,000 psi (895 MPa)
Elongation in 4D, min	5%
Reduction of Area, min	20%

3.3.5 Hardness: Should be 302 - 341 HB, or equivalent across the section but bars \emptyset shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4 Quality:

3.4.1 Bars, as received by purchaser, shall be uniform in quality and condition, \emptyset sound, and, consistent with the type of steel involved, free from foreign materials and from internal and external imperfections detrimental to usage of the bars.

- 3.4.2 Bars ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.
- 3.4.5 Bars ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surface. Standard machining allowance shall be in accordance with AS 1182.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Unless otherwise specified, tolerances for bars shall conform to all applicable requirements of AMS 2251, except that tolerances for diameter shall be as follows:

TABLE II

Nominal Diameter Inch	Tolerance, Inch Minus Only
Up to 0.375, incl	0.003
Over 0.375 to 1.500, incl	0.005
Over 1.500 to 2.500, incl	0.006
Over 2.500 to 3.500, incl	0.007

TABLE II (SI)

Nominal Diameter Millimetres	Tolerance, Millimetre Minus Only
Up to 9.40, incl	0.08
Over 9.40 to 37.50, incl	0.12
Over 37.50 to 62.50, incl	0.15
Over 62.50 to 87.50, incl	0.18

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of bars shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bars conform to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.