

# AEROSPACE MATERIAL SPECIFICATION



AMS 6408A

Issued JAN 1989  
Revised FEB 1994  
Reaffirmed SEP 2000

Superseding AMS 6408

Steel, Hotwork Tool, Bars and Forgings  
5.25Cr - 1.5Mo - 1.0V (0.35-0.45C)  
Electroslag Remelted (ESR) or Consumable Electrode Vacuum Arc Remelted (VAR)  
Annealed

UNS T20813

## 1. SCOPE:

### 1.1 Form:

This specification covers a premium aircraft-quality, low-alloy steel in the form of bars, forgings, and forging stock.

### 1.2 Application:

These products have been used typically for hotwork tooling or for parts requiring a steel capable of through-hardening to a minimum hardness of 50 HRC in section thicknesses up to 12 inches (305 mm) with relatively high levels of strength, fatigue resistance, ductility, and thermal stability for use in service from -100 to +1000 °F (-73 to 538 °C) and where such parts may require welding, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP1110 recommends practices to minimize such conditions.

### 1.3 Classification:

Steel covered by this specification is classified by melting practice as follows:

Type 1 - Multiple melted using electroslag (ESR) process in the final melting cycle.

Type 2 - Multiple melted using consumable electrode vacuum arc (VAR) practice in the remelt cycle.

1.3.1 Unless a specific type is ordered, either type may be supplied.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2251	Tolerances, Low-Alloy Steel Bars
MAM 2251	Tolerances, Metric, Low-Alloy Steel Bars
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
MAM 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
ARP1110	Minimizing Stress Corrosion Cracking in Heat Treatable Wrought Low-Alloy and Martensitic Corrosion Resistant Steels
AS1182	Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

### 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370	Mechanical Testing of Steel Products
ASTM A 604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E 45	Determining the Inclusion Content of Steels
ASTM E 112	Determining the Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

### 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163	Steel Mill Products, Preparation for Shipment and Storage
-------------	-----------------------------------------------------------

### 3. TECHNICAL REQUIREMENTS:

#### 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	Min	Max
Carbon	0.35	0.45
Manganese	0.20	0.50
Silicon	0.85	1.20
Phosphorus	--	0.020
Sulfur	--	0.008
Chromium	5.00	5.50
Molybdenum	1.20	1.75
Vanadium	0.85	1.20

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

#### 3.2 Melting Practice:

Steel shall be multiple melted using either electroslag or consumable electrode vacuum arc practice for the remelt cycle.

#### 3.3 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370.

##### 3.3.1 Bars:

3.3.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished and annealed having hardness not higher than 262 HB, or equivalent (see 8.2).

3.3.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot or cold finished and annealed having hardness not higher than 235 HB, or equivalent (see 8.2).

3.3.2 Forgings: Annealed having hardness not higher than 217 HB, or equivalent (see 8.2).

3.3.3 Forging Stock: As ordered by the forging manufacturer.

## 3.4 Properties:

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A 370:

- 3.4.1 Macrostructure: Visual examination of transverse sections as in 4.3.3 from bars, billets, and forging stock, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - Macrostructure Limits

Class	Condition	Severity
1	Freckles	A
2	White Spots	B
3	Radial Segregation	B
4	Ring Pattern	B

- 3.4.2 Micro-Inclusion Rating: No specimen as in 4.3.4 shall exceed the limits shown in Table 3, determined in accordance with ASTM E 45, Method D.

TABLE 3 - Micro-Inclusion Rating Limits

	A Thin	A Heavy	B Thin	B Heavy	C Thin	C Heavy	D Thin	D Heavy
Worst Field Severity	1.5	1.0	1.5	1.0	1.5	1.0	2.0	1.0
Worst Field Frequency, maximum	*	1	*	1	*	1	3	1
Total Rateable Fields, Frequency, maximum	**	1	**	1	**	1	8	1

\*Combined A+B+C, not more than 3 fields  
 \*\*Combined A+B+C, not more than 8 fields

- 3.4.2.1 A rateable field is defined as one which has a Type A, B, C, or D inclusion rating of at least No. 1.0 thin or heavy in accordance with the Jernkontoret chart, Plate III, ASTM E 45.

## 3.4.3 Decarburization:

- 3.4.3.1 Bars ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

- 3.4.3.2 Allowable decarburization of bars and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.4.3.3 Decarburization of bars to which 3.4.3.1 or 3.4.3.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4A - Maximum Decarburization, Inch/Pound Units

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.015
Over 0.500 to 0.625, incl	0.020
Over 0.625 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035
Over 2.000 to 3.000, incl	0.048
Over 3.000 to 4.000, incl	0.062
Over 4.000 to 5.000, incl	0.094
Over 5.000	0.125

TABLE 4B - Maximum Decarburization, SI Units

Nominal Diameter or Distance Between Parallel Sides Millimeters	Depth of Decarburization Millimeters
Up to 9.52, incl	0.25
Over 9.52 to 12.70, incl	0.38
Over 12.70 to 15.88, incl	0.51
Over 15.88 to 25.40, incl	0.64
Over 25.40 to 50.80, incl	0.89
Over 50.80 to 76.20, incl	1.22
Over 76.20 to 101.60, incl	1.57
Over 101.60 to 127.00, incl	2.39
Over 127.00	3.18

- 3.4.3.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization or lack of decarburization thereon.
- 3.4.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.
- 3.4.4 Response to Heat Treatment: Specimens as in 3.4.4.1 shall conform to the following requirements after being austenitized by heating to 1850 °F ± 25 (1010 °C ± 14), holding at heat for 15 to 45 minutes, cooling in air to room temperature and double tempered by heating to a temperature not lower than 1100 °F (593 °C), holding at heat for 2 to 3 hours, and cooling in air.
- 3.4.4.1 Longitudinal Tensile Properties: These requirements apply to specimens taken from bars and forging stock 25 square inches (161 cm<sup>2</sup>) and under in cross-sectional area, from forgings with axis approximately parallel to the forging flow lines, and to specimens from coupons of stock over 25 square inches (161 cm<sup>2</sup>) in cross-sectional area and forged to 25 square inches (161 cm<sup>2</sup>) in cross-sectional area prior to heat treatment as in 3.4.4.

TABLE 5 - Minimum Tensile Properties

Requirement	Value
Tensile Strength	205 ksi (1413 MPa)
Yield Strength at 0.2% Offset	180 ksi (1241 MPa)
Elongation in 4D	8%
Reduction of Area	20%

- 3.4.4.2 Hardness: Shall be 44 to 50 HRC, or equivalent (see 8.2).
- 3.4.4.3 Grain Size: Shall be as follows, determined in accordance with ASTM E 112:
- 3.4.4.3.1 Bars and Forgings Up to 2.50 Inches (63.5 mm) in Nominal Diameter, Distance Between Parallel Sides, or Cross-Sectional Dimension: Shall be ASTM No. 7 or finer (see 8.3).
- 3.4.4.3.2 Bars and Forgings Over 2.50 Inches (63.5 mm) in Nominal Diameter, Distance Between Parallel Sides, or Cross-Sectional Dimension: Shall be ASTM No. 5 or finer (see 8.3).

### 3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300 or MAM 2300.

3.5.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5.3 Bars ordered hot rolled or cold drawn or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

### 3.6 Tolerances:

Bars shall conform to all applicable requirements of AMS 2251 or MAM 2251.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

### 4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars and Forging Stock: AMS 2370 except as specified in 4.3.3 and 4.3.4.

4.3.2 Forgings: AMS 2372.

4.3.3 Samples for macrostructure rating (3.4.1) shall be full cross-sectional specimens obtained from the finished billet or suitable rerolled product representing the top and bottom of at least the first, middle, and last useable ingot of each heat.

4.3.4 Samples for micro-inclusion rating (3.4.2) shall be obtained from the finished billet or suitable rerolled product and shall consist of not less than four specimens representing the top and bottom of the first and last ingot from a heat yielding 10 or fewer ingots or not less than six specimens representing the top and bottom of the first, middle, and last useable ingot from a heat yielding more than 10 ingots.

#### 4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition macrostructure, micro-inclusion rating, grain size, and frequency-severity cleanliness rating of each heat and showing the results of tests on each lot to determine conformance to the other technical requirements. This report shall include the purchase order number, heat and lot number, AMS 6408A, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

#### 4.5 Resampling and Retesting:

Shall be in accordance with the following:

4.5.1 Bars and Forging Stock: AMS 2370.

4.5.2 Forgings: AMS 2372.

### 5. PREPARATION FOR DELIVERY:

#### 5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

#### 5.2 Identification:

Shall be as follows:

5.2.1 Bars: In accordance with AMS 2806.

5.2.2 Forgings: In accordance with AMS 2808.

5.2.3 Forging Stock: As agreed upon by purchaser and vendor.

#### 5.3 Protective Treatment:

Bars ordered cold drawn, cold rolled, ground, turned, or polished shall be coated with a suitable corrosion-preventive compound prior to shipment.