

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6413C

Issued 12-1-42

Revised 5-1-54

STEEL TUBING, MECHANICAL
0.8Cr - 1.8Ni - 0.25Mo (0.35-0.40C) (SAE 4337)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Heavy wall tubing for machining.
3. APPLICATION: Parts with sections 0.875 in. or less in thickness at the time of heat treatment which require a through-hardening steel capable of developing hardness as high as Rockwell C 50 when properly hardened and tempered and also parts of greater thickness but requiring proportionately lower hardness.
4. COMPOSITION:

		Check Analysis	
		Under	Min or Over Max
Carbon	0.35 - 0.40	0.02	0.02
Manganese	0.65 - 0.85	0.03	0.03
Silicon	0.20 - 0.35	0.02	0.02
Phosphorus	0.040 max	--	0.005
Sulfur	0.040 max	--	0.005
Chromium	0.70 - 0.90	0.03	0.03
Nickel	1.65 - 2.00	0.05	0.05
Molybdenum	0.20 - 0.30	0.02	0.02

5. CONDITION: In a machinable condition, and, unless otherwise specified, cold finished.

6. TECHNICAL REQUIREMENTS:

- 6.1 Hardenability: The hardenability shall be $J_{50}=10$ min and $J_{44}=18$ min when determined by the standard end-quench test specimen in accordance with the SAE Method of Determining Hardenability published in the latest issue of the SAE Handbook, except that the steel shall be normalized at $1700\text{ F} \pm 10$ and the test specimen austenitized at $1500\text{ F} \pm 10$. The hardenability test is not required on tubing which will not yield a suitable specimen but the steel from which the tubing is made shall conform to the hardenability specified in this paragraph.
- 6.2 Grain Size: Five or finer as determined on the billet, ASTM E19, method a. A heat of steel predominantly five or finer with grains as large as three is permissible.
- 6.3 Decarburization:
 - 6.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on such ground, turned or polished surfaces. Inside decarburization shall not exceed the maximum depth specified in 6.3.3.

Section 7C of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

- 6.3.2 Allowable decarburization of pierced billets, or of tubing for redrawing, or of tubing ordered to specified microstructural requirements, shall be as agreed upon by purchaser and vendor.
- 6.3.3 Decarburization of tubing to which 6.3.1 or 6.3.2 is not applicable shall be not greater than the following:

Nominal Wall Thickness Inch	Depth of Decarburization, Inch	
	Inside	Outside
0.109 and under	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

- 6.3.4 Unless otherwise agreed upon by purchaser and vendor, decarburization shall be measured by the microscopic method, or by Rockwell Superficial 30-N scale hardness method, or equivalent hardness testing method, on hardened specimens. Depth of decarburization when measured by a hardness method, is defined as the distance measured from the nearest original surface to the point at which no increase in hardness is found.
- 6.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits above by more than 0.005 in. and the width is 0.065 in. or less.
7. QUALITY: Steel shall be aircraft quality. Tubing shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.
8. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2253 as applicable to Mechanical Type.
9. REPORTS:
- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition, hardenability, and grain size of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat.
- 9.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.