

SAE-AMS6442

ADOPTION NOTICE

SAE-AMS6442, "Bars and Forgings, 0.50CR (0.98-1.10C), for Bearing Applications," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, Attn: DISC-E, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:
 Army - MR
 Navy - SH
 Air Force - 84

Adopting Activity
 DLA - IS

SAENORM.COM : Click to view the full PDF of SAE-AMS6442

FSC 9510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

6-45-09

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 6442E

Issued 7-1-48
Revised 4-1-87

Superseding AMS 6442D

STEEL BARS AND FORGINGS
0.50Cr (0.98 - 1.10C) (SAE 50100)
For Bearing Applications

UNS G50986

1. SCOPE:

- 1.1 Form: This specification covers a low-alloy steel in the form of bars, forgings, and forging stock.
- 1.2 Application: Primarily for parts of small cross-section, such as needle bearings, requiring a through hardening steel usually with hardness of approximately 60 HRC and subject to very rigid inspection standards.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2251 - Tolerances, Low-Alloy Steel Bars
 MAM 2251 - Tolerances, Metric, Low-Alloy Steel Bars
 AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
 AMS 2350 - Standards and Test Methods
 AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
 AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
 AMS 2375 - Control of Forgings Requiring First Article Approval
 AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
 AMS 2808 - Identification, Forgings

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E45 - Determining the Inclusion Content of Steels

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E381 - Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, \emptyset determined by wet chemical methods in accordance with ASTM E350 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.98	1.10
Manganese	0.25	0.45
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.40	0.60
Nickel	--	0.25
Molybdenum	--	0.06
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with AMS A370:

3.2.1 Bars:

3.2.1.1 Bars 0.500 In. (12.50 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished, with microstructure of spheroidized cementite in ferrite matrix, having tensile strength not higher than 120,000 psi (825 MPa) or equivalent hardness.

3.2.1.2 Bars Over 0.500 In. (12.50 mm) in Nominal Diameter or Distance Between
 ∅ Parallel Sides: Hot finished and annealed, with microstructure of spheroidized cementite in ferrite matrix, having hardness not higher than 207 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 248 HB, or equivalent.

3.2.2 Forgings: As ordered.

3.2.3 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A370:

3.3.1 Inclusion Rating: Shall be as follows:

3.3.1.1 Macrostructure: Visual examination of transverse sections as in 4.3.3 from bars, billets, and forging stock, etched in accordance with ASTM E381 in hot hydrochloric acid (1:1) at 160° - 180°F (70° - 80°C) for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E381 agreed upon by purchaser and vendor.

3.3.1.2 Micro-Inclusion Rating: At least one specimen as in 4.3.4 from each
 ∅ ingot tested, as well as two-thirds of the total number of specimens and the average of all specimens, shall not exceed the following limits, determined in accordance with ASTM E45, Method A:

Type	Inclusion Rating			
	A	B	C	D
Thin	2.0	2.0	2.0	1.5
Heavy	1.5	1.5	1.5	1.5

3.3.2 Response to Heat Treatment: Specimens as in 4.3.5, protected by suitable means or treated in a neutral atmosphere to minimize scaling and prevent either carburization or decarburization, shall have substantially uniform hardness not lower than 60 HRC at any point below any permissible decarburization after being placed in a furnace which is at 1525°F + 10 (830°C + 5), allowed to heat to 1525°F + 10 (830°C + 5), held at heat for 20 min. + 2, and quenched in commercial paraffin oil (100 SUS at 100°F (38°C)) at room temperature.

3.3.3 Decarburization:

3.3.3.1 Bars ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.3.2 Allowable decarburization of bars and billets ordered for redrawing or forging or to specified microstructural requirements other than spheroidized cementite in ferrite matrix shall be as agreed upon by purchaser and vendor.

- 3.3.3.3 Decarburization of bars for anti-friction balls and rollers to which 3.3.3.1 or 3.3.3.2 is not applicable shall be not greater than shown in Table I.

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inch	Depth of Decarburization Inch	
	Hot	Cold
	Finished	Finished
Up to 0.250, incl	0.005	0.003
Over 0.250 to 0.500, incl	0.006	0.004
Over 0.500 to 0.750, incl	0.008	0.006
Over 0.750 to 1.000, incl	0.010	0.008

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Depth of Decarburization Millimetres	
	Hot	Cold
	Finished	Finished
Up to 6.25, incl	0.12	0.08
Over 6.25 to 12.50, incl	0.15	0.10
Over 12.50 to 18.75, incl	0.20	0.15
Over 18.75 to 25.00, incl	0.25	0.20

- 3.3.3.4 Decarburization of bars to which 3.3.3.1, 3.3.3.2, or 3.3.3.3 is not applicable shall be not greater than shown in Table II.

TABLE II

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch		
	Hot	Annealed	Cold
	Finished		Finished
Up to 1.000, incl	0.012	0.015	0.012
Over 1.000 to 2.000, incl	0.017	0.022	0.015
Over 2.000 to 3.000, incl	0.025	0.030	0.025
Over 3.000 to 4.000, incl	0.035	0.045	0.035
Over 4.000 to 5.000, incl	0.055	0.065	0.055

TABLE II (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Depth of Decarburization Millimetres		
	Hot	Annealed	Cold
	Finished		Finished
Up to 25.00, incl	0.30	0.38	0.30
Over 25.00 to 50.00, incl	0.42	0.55	0.38
Over 50.00 to 75.00, incl	0.62	0.75	0.62
Over 75.00 to 100.00, incl	0.88	1.12	0.88
Over 100.00 to 125.00, incl	1.38	1.62	1.38

- 3.3.3.5 Limits for depth of decarburization of bars over 5.000 in. (125.00 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.
- 3.3.3.6 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.
- 3.3.3.6.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 in. (0.12 mm) and the width is 0.065 in. (1.65 mm) or less.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.4.1 Bars ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.
- 3.4.2 Bars ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be equal to, but not in addition to, the decarburization limits of 3.3.3 for the condition of bars ordered.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Bars shall conform to all applicable requirements of AMS 2251 or MAM 2251.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars: AMS 2370.

4.3.2 Forgings and Forging Stock: AMS 2372.

4.3.3 Samples for macrostructure (3.3.1.1) testing shall be full cross-sectional specimens obtained from the finished billet or suitable rerolled product representing the top and bottom of at least the first, middle, and last usable ingot of each heat.

4.3.4 Samples for micro-inclusion rating (3.3.1.2) shall consist of not less than six specimens from each heat selected so that the surface examined will be approximately parallel to the direction of rolling. The method of selection of specimens shall be such that a representative rating is ensured.

4.3.5 Samples for response to heat treatment (3.3.2) shall be the full cross-section of the bar ground on both faces normal to the axis so that length is 0.50 in. \pm 0.010 (12.5 mm \pm 0.25).

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of bars and forgings shall furnish with each shipment a report showing the results of tests for chemical composition and inclusion rating of each heat and for response to heat treatment of each lot. This report shall include the purchase order number, heat number, AMS 6442E, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.