

# AEROSPACE MATERIAL SPECIFICATION



AMS 6454C

Issued  
Revised

JAN 1984  
OCT 2001

Superseding AMS 6454B

Steel, Sheet, Strip, and Plate  
1.8Ni - 0.80Cr - 0.25Mo (0.38 - 0.43C) (SAE 4340)  
Consumable Electrode Melted

(Composition similar to UNS G43400)

## 1. SCOPE:

### 1.1 Form:

This specification covers a premium-aircraft-quality, low-alloy steel in the form of sheet, strip, and plate.

### 1.2 Application:

These products have been used typically for heat treated parts requiring good tensile and fatigue strengths in combination with good ductility, but usage is not limited to such applications. The product may be through-hardened to tensile strength ranges of 260 to 280 ksi (1793 to 1931 MPa) in nominal section thicknesses of 1.5 inches (38 mm) and under and 180 to 220 ksi (1241 to 1517 MPa) in nominal section thicknesses of 3 inches (76 mm) and under.

### 1.3 Classification:

Product shall be classified as follows:

Type 1 - Steel multiple melted using consumable electrode vacuum practice in the remelt cycle.

Type 2 - Steel multiple melted using electro slag process in the remelt cycle.

#### 1.3.1 Unless a specific type is ordered, either type and may be supplied.

## 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2252	Tolerances, Low-Alloy Steel Sheet, Strip, and Plate
MAM 2252	Tolerances, Metric, Low-Alloy Steel Sheet, Strip, and Plate
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
MAM 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure Metric (SI) Measurement
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor, West Conshohocken, PA 19428-2959.

ASTM A 255	Determining Hardenability of Steel
ASTM A 370	Mechanical Testing of Steel Products
ASTM A 604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E 45	Determining the Inclusion Content of Steel
ASTM E 112	Determining Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E 354	Microindentation Hardness of Materials

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

TABLE 1 - Composition

Element	min	max
Carbon	0.38	0.43
Manganese	0.60	0.90
Silicon	0.15	0.35
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	0.70	0.90
Nickel	1.65	2.00
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Melting Practice:

Shall be multiple melted using vacuum consumable electrode or electroslag process in the remelt cycle (See 1.3).

3.3 Condition:

The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM A 370:

3.3.1 Sheet and Strip: Cold finished, bright or atmosphere annealed, and descaled if necessary, or hot rolled, annealed if necessary, and descaled, having hardness not higher than 98 HRB, or equivalent (See 8.2).

3.3.2 Plate: Hot rolled, annealed if necessary, and descaled, having hardness not higher than 25 HRC, or equivalent (See 8.2).

3.3.3 If product is ordered spheroidize annealed, the degree of spheroidization shall be acceptable to purchaser.

3.4 Properties:

The product shall conform to the following requirements; hardness and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds, or forging stock, etched in hot hydrochloric acid, in accordance with ASTM A 604 shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - Macrostructure Limits

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

3.4.2 Micro-Inclusion Rating: No specimen shall exceed the limits shown in Table 3, determined in accordance with ASTM E 45, Method D, except that the length of any inclusion shall be not greater than 0.015 inch (0.38 mm):

TABLE 3 - Micro-Inclusion Rating Limits

Type	A	B	C	D
Thin	1.5	1.5	1.5	2.0
Heavy	1.0	1.0	1.0	1.5

- 3.4.3 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112 (See 8.3).
- 3.4.4 Hardenability: Shall be J6/16 inch (9.5 mm) = 53 HRC minimum and J20/16 inch (31.7 mm) = 50 HRC minimum (See 8.4), determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at 1700 °F ± 10 (927 °C ± 6) and the test specimen austenitized at 1525 °F ± 10 (829 °C ± 6).
- 3.4.5 Decarburization: Depending upon thickness of the product, decarburization may be measured by a HR30N hardness step test method, or by the microhardness traverse method. Additionally, the metallographic method shall be used, in part (See 3.4.5.4.1), to inspect product 0.025 to 0.250 inch (0.64 to 6.35 mm) thick, and it may be used to inspect product with thickness 0.375 inch (9.52 mm) and over.
- 3.4.5.1 In the case of dispute, the microhardness method, conducted in accordance with ASTM E 384, shall govern. The allowance for decarburization shall be that which would have been applicable had the step method been used (See 3.4.5.4.1 or 3.4.5.5.1, as applicable).
- 3.4.5.2 Specimens: Shall be full thickness of the product except that specimens from plate 0.250 inch (6.35 mm) and over in nominal thickness may be slices approximately 0.250 inch (6.35 mm) thick cut parallel to and preserving one original surface of the plate. Recommended minimum specimen size is 1 x 4 inches (25 x 102 mm). For product 0.025 to 0.250 inch (0.64 to 6.35 mm), a full cross section metallographic sample shall be prepared to inspect for presence of complete decarburization (ferrite).
- 3.4.5.3 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably, they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300 °F (149 °C). During heat treatment, specimens shall be protected by suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization.
- 3.4.5.4 Product 0.025 to 0.250 Inch (0.64 to 6.35 mm), Exclusive, in Nominal Thickness: Protective plating, if used to prevent any decarburization during hardening, shall be removed, and a portion of the specimen shall be ground with copious coolant to prevent thermal or mechanical effects to a depth of 0.050 inch (1.27 mm) or one-half thickness, whichever is less.

- 3.4.5.4.1 Allowance: The product shall show no layer of complete decarburization (ferrite) determined metallographically at a magnification not exceeding 100X. It shall also be free from any partial decarburization to the extent that the difference in hardness between the original surface and the surface (depth) generated by grinding as in 3.4.5.4 shall not be greater than two units on the HRA scale, or equivalent (See 8.2). Also, refer to 3.4.5.1.
- 3.4.5.5 Product 0.250 to 0.375 inch (6.35 to 9.52 mm), Exclusive, in Nominal Thickness: Specimens shall be ground to remove 0.010 inch (0.25 mm) of metal to create a test reference surface, and a portion of the specimen shall be further ground to a depth of at least one-third the original thickness of the specimen.
- 3.4.5.5.1 Allowance: Shall be free from decarburization to the extent that the difference in hardness between the two prepared steps shall be not greater than three units on the HRA scale, or equivalent (See 8.2). Also, refer to 3.4.5.1.
- 3.4.5.6 Product 0.375 Inch (9.52 mm) and Over in Nominal Thickness:
- 3.4.5.6.1 Allowance: The total depth of the decarburization, determined metallographically at a magnification not exceeding 100X, on the as-supplied plate, shall be not greater than shown in Table 4. Also, refer to 3.4.5.1. The depth of decarburization shall be that which is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness.

TABLE 4A - Maximum Decarburization Limits, Inch/Pound Units

Nominal Thickness Inches	Total Depth of Decarburization Inch
0.375 to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035

TABLE 4B - Maximum Decarburization Limits, SI Units

Nominal Thickness Millimeter	Total Depth of Decarburization Millimeters
9.52 to 12.70, incl	0.38
Over 12.70 to 25.40, incl	0.64
Over 25.40 to 50.80, incl	0.89

- 3.4.6 Bending: Product 0.749 inch (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle shown in Table 5 around a diameter equal to three times the nominal thickness of the product, with axis of bend parallel to the direction of rolling.

TABLE 5 - Bending Parameters

Nominal Thickness Inches	Nominal Thickness Millimeters	Angle Degrees, min
Up to 0.249, incl	Up to 6.32, incl	180
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	90

### 3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

- 3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300 or MAM 2300.

### 3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2252 or MAM 2252.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

### 4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

### 4.3 Sampling and Testing:

Shall be in accordance with AMS 2370.