



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 1000

AMS 6466A

Superseding AMS 6466

Issued 1-15-59

Revised 11-1-68

STEEL WIRE, WELDING 5Cr - 0.55Mo

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for use as filler metal for welding low alloy steels where response to heat treatment is required in the weld.
3. COMPOSITION:

	min	max
Carbon	--	0.10
Manganese	--	0.60
Silicon	0.25 -	0.60
Phosphorus	--	0.03
Sulfur	--	0.03
Chromium	4.50 -	6.00
Molybdenum	0.45 -	0.65
Nickel	--	0.60
Copper		0.35

- 3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels."

4. CONDITION: Unless otherwise specified, wire shall be cold drawn, bright finish, as-drawn temper.
 ∅ Wire shall be furnished on disposable spools for machine welding and in cut lengths for manual welding operations, as ordered.

- ∅ 4.1 Drawing compounds, oxides, and dirt shall be removed.

5. TECHNICAL REQUIREMENTS:

- 5.1 Welding: Melted wire shall flow smoothly and evenly during welding and be capable of producing acceptable welds.

- 5.2 Spooled Wire: Shall conform to the following unless otherwise agreed upon by purchaser and vendor.

- 5.2.1 Cast: Wire shall have imparted to it a curvature such that a specimen sufficient in length to form one loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. and not greater than 30 in. in diameter.
 ∅

- 5.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch.
 ∅

- 5.2.3 Layer Winding: Wire shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching; shall be wound so as to avoid producing kinks, waves, and sharp bends; and shall be free to unwind without restriction caused by overlapping or wedging. The outside end of the spooled wire shall be so treated that it may be readily located.

SAE Technical Board rules provide that: "All technical reports, including standards applications and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."