



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 1000

AMS 6467A
Superseding AMS 6467

Issued 1-15-59
Revised 11-1-68

WELDING ELECTRODES, COATED, STEEL 5Cr - 0.55Mo

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for use as filler metal for metal arc welding low alloy steels where response to heat treatment is required in the weld.
3. **COMPOSITION:** Electrodes shall be capable of depositing weld metal of the following composition:

	min	max
Carbon	--	0.10
Manganese	--	1.00
Silicon	0.25 -	0.60
Phosphorus	--	0.03
Sulfur	--	0.03
Chromium	4.50 -	6.00
Molybdenum	0.45 -	0.65
Nickel	--	0.60
Copper	--	0.35

- 3.1 **Weld Pads for Chemical Analysis:** The referee procedure for making pads of weld metal and removing samples for chemical analysis shall be as specified in the issue of ASTM A298 listed in the latest issue of AMS 2350, except that sample shall not be removed within 1/2 in. of the base plate, unless the base plate is similar in composition to the core wire, in which case sample may be removed from as close as 1/4 in. to the plate.

4. **TYPE:**

- 4.1 Coating shall be suitable for all position use with the following current:

Type	Current
A	DC
B	DC-AC

- 4.1.1 When DC is specified, reverse polarity (electrode positive) is required.

- 4.2 Unless otherwise specified, Type B shall be supplied.

5. **TECHNICAL REQUIREMENTS:**

- 5.1 **Weldability:** Electrodes shall demonstrate good weldability and shall flow smoothly and evenly under the conditions specified in 4.1.
- 5.2 **Burn-Off:** The coating shall be consumed uniformly on all sides and shall not burn back from the core wire under proper welding conditions. Heating of the electrode during welding shall not cause injurious blistering of the coating within the ranges of current values recommended by the manufacturer.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

5.3 Grip Portion and Arc Ends: A portion of the electrode 0.75 - 1.25 in. long at one end shall be bare to permit good electrical contact with the electrode holder. The opposite or arc end of the electrode shall be sufficiently bare to permit easy striking of the arc but the length of this bare section, as measured from the end of the electrode to the point where the full cross-section of the coating begins, shall not exceed the diameter of the bare wire, and in no case shall it exceed 1/8 inch.

5.4 Cleaning: Slag produced during welding shall be readily removable with hand tools.

6. QUALITY:

- 6.1 The core wire shall be uniform in quality and condition, clean, sound, and free from foreign materials and from imperfections detrimental to weld quality.
- 6.2 The coating shall be uniform in quality, tightly adherent, and free from abnormal scabs, blisters, pockmarks, bruises, and other surface imperfections and shall withstand normal handling without damage. It shall not be harmfully hygroscopic and shall not adversely affect weld quality.

7. STANDARD SIZES: The following diameters and lengths are standard:

	Nominal Diameter of Core Wire, Inch	Length, Inches
∅	1/16, 5/64	9
	3/32	9 or 12
	1/8, 5/32, 3/16, 1/4	14

7.1 Unless otherwise specified, end grip electrodes shall be supplied.

8. TOLERANCES:

- 8.1 Unless otherwise specified, electrodes shall not vary in length more than $\pm 1/4$ in. from the length ordered.
- 8.2 Electrode core wire shall not vary in diameter more than ± 0.002 in. from the size ordered.
- 8.3 Overall diameter of the coated electrodes shall not vary more than 4% from that of the approved sample.
- 8.4 Coating shall be concentric with the core wire to the extent that the maximum core-plus-one-coating dimension shall not exceed the minimum core-plus-one-coating dimension by more than 5% of the minimum core-plus-one-coating dimension.

9. REPORTS:

- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, control number, size, and quantity. Control number shall be a designation indicating batch processing and core wire heat number. When requested by the purchaser, the vendor shall also include in the report the composition of the deposited weld metal for each heat in the shipment.
- 9.2 Unless otherwise specified, when assemblies requiring the use of these electrodes are supplied, the assembly manufacturer shall inspect each lot of electrodes to determine conformance to the requirements of this specification and shall furnish with each shipment three copies of a report stating that the electrodes conform to this specification. This report shall include the purchase order number, material specification number and its revision letter, part number, and quantity.