

# AEROSPACE MATERIAL SPECIFICATION



AMS 6521B

Issued MAY 1969  
Revised APR 1983  
Noncurrent APR 1994  
Reaf. Noncur. OCT 2000

Superseding AMS 6521A

Steel Sheet, Strip, and Plate, Maraging  
18.5Ni - 9.0Co - 4.9Mo - 0.65Ti - 0.10Al  
Consumable Electrode Melted, Solution Heat Treated

UNS K93160

## NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April 1994. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

SAENORM.COM : Click to view the full PDF of AMS6521B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 1. SCOPE:

### 1.1 Form:

This specification covers a premium-aircraft-quality, maraging steel in the form of sheet, strip, and plate.

### 1.2 Application:

Primarily for large booster rocket applications, pressure vessels, and other components requiring through-hardening, without quenching, to a yield strength of 270,000 psi (1860 MPa) and higher and subject to very rigid inspection standards.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2252	Tolerances, Low-Alloy Steel Sheet, Strip, and Plate
AMS 2300	Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS 2350	Standards and Test Methods
AMS 2370	Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

### 2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103

ASTM A370	Mechanical Testing of Steel Products
ASTM A604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E45	Determining the Inclusion Content of Steel
ASTM E112	Estimating the Average Grain Size of Metals
ASTM E338	Sharp-Notch Tension Testing of High-Strength Sheet Materials
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E399	Plane-Strain Fracture Toughness of Metallic Materials

## 2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pa 19120.

## 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 Metals; Test Methods

## 2.3.2 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.03
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.010
Nickel	18.00	19.00
Cobalt	8.50	9.50
Molybdenum	4.60	5.20
Titanium	0.50	0.80
Aluminum	0.05	0.15

3.1.1 Prior to pouring, 0.05% calcium, 0.02% zirconium, and 0.003% boron shall be added to the melt but analysis for these elements need not be made.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

## 3.2 Condition:

Hot rolled, solution heat treated, and descaled.

## 3.3 Heat Treatment:

The product shall be solution heat treated by heating in air to 1500°F ± 25 (815°C ± 15), holding at heat for a time commensurate with the thickness and the heating procedure, and cooling in air. Continuously-rolled product may be solution heat treated at temperatures higher than 1500°F (815°C) provided the product is re-solution heat treated at 1500°F ± 25 (815°C ± 15).

## 3.4 Properties:

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

## 3.4.1 As Solution Treated:

3.4.1.1 Macrostructure: Visual examination of transverse sections as in 4.3.1 from slabs, etched in accordance with AMS A604 in hot hydrochloric acid (1:1) at 160° - 180°F (70° - 80°C) for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the following macrographs of ASTM A604:

Class	Condition	Severity
1	Freckles	B
2	White Spots	C
3	Radial Segregation	C
4	Ring Pattern	C

3.4.1.2 Micro-Inclusion Rating: Two-thirds of the total number of specimens, as well as the average of all specimens, shall not exceed the following limits, determined in accordance with ASTM E45, Method D, except that the length of any inclusion shall be not greater than 0.015 in. (0.38 mm):

Type	Inclusion Rating, Worse Field				
	A	B	C	D	E
Thin	1.5	1.5	1.5	2.0	3.0
Heavy	1.0	1.0	1.0	1.5	2.0

3.4.1.2.1 Type E is titanium nitride and shall be rated in the same manner as Type B.

3.4.1.3 Grain Size: Shall be as follows:

3.4.1.3.1 Product 0.625 In. (15.50 mm) and Under in Nominal Thickness: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined by comparison of a polished and etched specimen with the chart in ASTM E112.

3.4.1.3.2 Product Over 0.625 In. (15.50 mm) in Nominal Thickness: As agreed upon by purchaser and vendor.

3.4.1.4 Hardness: Shall be not higher than 34 HRC or equivalent.

3.4.2 After Maraging: Product, solution heat treated as in 3.3, shall have the following properties after being maraged by heating to 900°F ± 10 (480°C ± 5) holding at heat for 3 - 5 hr, and cooling in air:

3.4.2.1 Tensile Properties: Shall be as specified in Table I.

TABLE I

Tensile Strength, min	280,000 psi		
Yield Strength at 0.2% Offset, min	270,000 psi		
Elongation, min	% in Gage Length Indicated		
Nominal Thickness			
Inches	2 in. or 4D	1 in.	0.5 in.
Up to 0.030, excl	--	--	1.0
0.030 to 0.045, incl	--	--	2.0
Over 0.045 to 0.065, incl	--	2.0	--
Over 0.065 to 0.090, incl	2.5	5.0	--
Over 0.090 to 0.125, incl	3.0	6.0	--
Over 0.125 to 0.250, incl	4.0	8.0	--
Over 0.250 to 0.375, incl	5.0	--	--
Over 0.375	6.0	--	--

TABLE I (SI)

Tensile Strength, min	1930 MPa		
Yield Strength at 0.2% Offset, min	1860 MPa		
Elongation, min	% in Gage Length Indicated		
Nominal Thickness			
Millimetres	50 mm or 4D	25 mm	12.5 mm
Up to 0.75, excl	--	--	1.0
0.75 to 1.10, incl	--	--	2.0
Over 1.10 to 1.60, incl	--	2.0	--
Over 1.60 to 2.25, incl	2.5	5.0	--
Over 2.25 to 3.10, incl	3.0	6.0	--
Over 3.10 to 6.25, incl	4.0	8.0	--
Over 6.25 to 9.50, incl	5.0	--	--
Over 9.50	6.0	--	--

- 3.4.2.2 Hardness: Should be not lower than 50 HRC or equivalent but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2.1 are met.
- 3.4.2.3 Fracture Toughness: When specified, product shall be subjected to fracture toughness testing. Method of test and standards for acceptance shall be as agreed upon by purchaser and vendor. ASTM E338 is a suggested method of test for sheet. ASTM E399 is a suggested method of test for plate.
- 3.5 Quality:
- 3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300. It shall be multiple melted using consumable electrode practice in the remelt cycle; at least one of the melting cycles shall be under vacuum.
- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.6 Tolerances:
- Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2252.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection:
- The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling:
- Shall be in accordance with AMS 2370 and the following; a heat shall be the consumable electrode remelted ingots produced from steel originally melted as a single furnace charge.
- 4.3.1 Samples for macrostructure (3.4.1.1) testing shall be cross-sectional specimens obtained from the finished slab or billet or suitable rerolled product representing the top and bottom of each ingot.

4.3.2 Samples for micro-inclusion rating (3.4.1.2) shall be obtained from the finished slab or billet or suitable rerolled product and shall consist of not less than 4 specimens representing the top and bottom of the first and last ingots from a heat yielding 10 or fewer ingots or not less than 6 specimens representing the top and bottom of the first, middle, and last usable ingots from a heat yielding more than 10 ingots.

#### 4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition, macrostructure, micro-inclusion rating, grain size, and AMS 2300 frequency-severity rating of each heat and the results of tests on each lot for tensile properties, hardness, and, when specified, fracture toughness after maraging. This report shall include the purchase order number, heat number, AMS 6521B, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 6521B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

#### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.

### 5. PREPARATION FOR DELIVERY:

#### 5.1 Identification:

The product shall be identified as in 5.1.1 unless purchaser permits a method from 5.1.2.

5.1.1 Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 6521B, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the heat number may be included in the line marking or may be marked at one location on each piece.

5.1.1.1 Flat Strip 6 In. (150 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.1.2 Flat Sheet, Flat Strip Over 6 In. (150 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced not more than 6 in. (150 mm) apart and alternately staggered.