

AN AMERICAN NATIONAL STANDARD

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

AMS 6535G

Issued 9-1-42
Revised 10-1-88

Superseding AMS 6535F

STEEL TUBING, SEAMLESS
0.50Cr - 0.55Ni - 0.20Mo (0.28 - 0.33C)
(SAE 8630)

UNS G86300

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 19 April 1988. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "F" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

REAFFIRMED

APR '94

This specification is under the jurisdiction of AMS Committee "E".

SAE Technical Board Rules provide that "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AN AMERICAN NATIONAL STANDARD

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 6535F
Superseding AMS 6535E

Issued 9-1-42
Revised 4-1-82

UNS G87350

STEEL TUBING, SEAMLESS
0.50Cr - 0.55Ni - 0.25Mo (0.33 - 0.38C)(SAF 8735)

1. SCOPE:

- 1.1 Form: This specification covers an aircraft-quality, low-alloy steel in the form of seamless tubing.
- 1.2 Application: Primarily for use where welding and moderate tensile properties are required. May be used where minimum tensile strength up to 180,000 psi (1240 MPa) is required for wall thicknesses up to 0.125 in. (3 mm) and proportionately lower strength is required in heavier thicknesses.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301 - Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS 2350 - Standards and Test Methods
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
AMS 2640 - Magnetic Particle Inspection

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report in formulating and approving technical reports. The Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 6535F

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Face Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products
ASTM E112 - Estimating the Average Grain Size of Metals
ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

Ø		min	max
	Carbon	0.33	0.38
	Manganese	0.75	1.00
	Silicon	0.15	0.35
	Phosphorus	--	0.025
	Sulfur	--	0.025
	Chromium	0.40	0.60
	Nickel	0.40	0.70
	Molybdenum	0.20	0.30
	Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: Cold finished and either normalized and tempered, stress relieved, or otherwise heat treated.

3.3 Properties: Tubing shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.3.1 Tensile Properties: Shall be as specified in Table I.

TABLE I

Nominal OD Inches	Nominal Wall Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. %, min	
				Full Tube	Strip
Up to 0.500, excl	Up to 0.188, incl	100,000	85,000	8	
Up to 0.500, excl	Over 0.188	95,000	80,000	10	
0.500 and over	Up to 0.188, incl	100,000	85,000	12	7
0.500 and over	Over 0.188	95,000	80,000	15	10

TABLE I(SI)

Nominal OD Millimetres	Nominal Wall Thickness Millimetres	Tensile Strength MPa,min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm %, min	
				Full Tube	Strip
Up to 12.50, excl	Up to 4.75, incl	690	585	8	
Up to 12.50, excl	Over 4.75	655	550	10	
12.50 and over	Up to 4.75, incl	690	585	12	7
12.50 and over	Over 4.75	655	550	15	10

3.3.2 Grain Size: Predominantly 5 or finer with occasional grains as large as \emptyset 3 permissible, determined in accordance with ASTM E112.

3.3.3 Decarburization:

3.3.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Decarburization on tubing ID shall not exceed the maximum depth specified in Table II.

3.3.3.2 Allowable decarburization of pierced billets, of tubing ordered for redrawing, or of tubing ordered to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.3.3 Tubing to which 3.3.3.1 or 3.3.3.2 is not applicable shall be free from complete decarburization. Partial decarburization shall not exceed the limits specified in Table II.

TABLE II

Nominal Wall Thickness (T) Inch	Depth of Partial Decarburization, Inch		
	ID	OD	ID + OD
up to 0.040, incl	0.25T	0.25T	0.30T
Over 0.040 to 0.050, incl	0.009	0.009	0.012
Over 0.050 to 0.070, incl	0.010	0.010	0.014
Over 0.070 to 0.080, incl	0.012	0.012	0.016
Over 0.080 to 0.090, incl	0.014	0.014	0.018
Over 0.090 to 0.100, incl	0.015	0.015	0.020
Over 0.100 to 0.150, incl	0.017	0.017	0.022
Over 0.150 to 0.200, incl	0.020	0.020	0.026

TABLE II(SI)

Nominal Wall Thickness (T) Millimetres	Depth of Partial Decarburization Millimetre		
	ID	OD	ID + OD
Up to 1.00, incl	0.25T	0.25T	0.30T
Over 1.00 to 1.25, incl	0.022	0.022	0.30
Over 1.25 to 1.75, incl	0.25	0.25	0.35
Over 1.75 to 2.00, incl	0.30	0.30	0.40
Over 2.00 to 2.25, incl	0.35	0.35	0.45
Over 2.25 to 2.50, incl	0.38	0.38	0.50
Over 2.50 to 3.75, incl	0.42	0.42	0.55
Over 3.75 to 5.00, incl	0.50	0.50	0.65

3.3.3.3.1 Limits for depth of partial decarburization of tubing having nominal wall thickness over 0.200 in. (5.00 mm) shall be as agreed upon by purchaser and vendor.

3.3.3.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 in. (0.12 mm) and the width is 0.065 in. (1.62 mm) or less.

3.4 Quality:

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such imperfections is not required.

3.4.2.1 When specified, the tubing, either with or without machining of the surface, shall be subjected to magnetic particle inspection in accordance with AMS 2640. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), grain size (3.3.2), decarburization (3.3.3), AMS 2301 frequency-severity rating (3.4.1), and tolerances (3.6) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for magnetic particle inspection (3.4.2.1), when specified, are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2370.