



AEROSPACE MATERIAL SPECIFICATION	AMS6920™	REV. E
	Issued	2004-01
	Revised	2024-07
Superseding AMS6920D		
Titanium Alloy Bars, Forgings, and Forging Stock 3Al - 8V - 6Cr - 4Mo - 4Zr Solution Heat Treated (Composition Similar to UNS R58640)		

RATIONALE

AMS6920E results from a Five-Year Review and update of the specification with changes to update general agreement language related to unauthorized exceptions (see 3.5.1.1.6, 3.5.2.3, and 8.5), relocate Definitions (see 2.3) and note regarding the statistical analysis of properties (see 3.5.1.1.6), and update Applicable Documents (see Section 2) and Ordering Information (see 8.6).

1. SCOPE

1.1 Form

This specification covers a titanium alloy in the form of bars up through 4.000 inches (101.60 mm) in nominal diameter or least distance between parallel sides, inclusive, forgings of thickness up through 4.000 inches (101.60 mm), inclusive, and stock for forging of any size (see 8.6).

1.2 Application

This material has been used typically for parts, including springs, fabricated in the solution heat-treated condition and subsequently precipitation heat treated, requiring higher tensile strength than is available in alpha-beta alloys, and corrosion resistance, but usage is not limited to such applications.

1.2.1 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP982 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS6920E>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2241	Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS2368	Sampling and Testing of Wrought Titanium Raw Material, Except Forgings and Forging Stock
AMS2631	Ultrasonic Inspection, Titanium and Titanium Alloy Bar, Billet, and Plate
AMS2643	Structural Examination of Titanium Alloys, Chemical Etch Inspection Procedure
AMS2750	Pyrometry
AMS2808	Identification, Forgings
AMS2809	Identification, Titanium and Titanium Alloy Wrought Products
ARP982	Minimizing Stress-Corrosion Cracking in Wrought Titanium Alloy Products
AS6279	Standard Practice for Production, Distribution, and Procurement of Metal Stock
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E539	Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry
ASTM E1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
ASTM E1447	Determination of Hydrogen in Reactive Metals and Reactive Alloys by Inert Gas Fusion with Detection by Thermal Conductivity or Infrared Spectrometry
ASTM E1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
ASTM E2371	Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)
ASTM E2994	Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry (Performance-Based Method)

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E1941, hydrogen in accordance with ASTM E1447, oxygen and nitrogen in accordance with ASTM E1409, and other elements in accordance with ASTM E539, ASTM E2371, or ASTM E2994. Other analytical methods may be used if acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Vanadium	7.50	8.50
Chromium	5.50	6.50
Molybdenum	3.50	4.50
Zirconium	3.50	4.50
Aluminum	3.00	4.00
Iron	--	0.30
Oxygen	--	0.12
Carbon	--	0.05
Nitrogen	--	0.03 (300 ppm)
Hydrogen	--	0.020 (200 ppm)
Yttrium (3.1.1)	--	0.005 (50 ppm)
Other Elements, each (3.1.1)	--	0.10
Other Elements, total (3.1.1)	--	0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2249.

3.2 Melting Practice

Alloy shall be multiple melted. The first melt shall be made by vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice. The subsequent melt or melts shall be made using vacuum arc remelting (VAR) practice. Alloy additions are not permitted in the final melt cycle.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars

Hot finished (with or without subsequent cold reduction), solution heat treated, and descaled. A machined or ground surface is permitted unless prohibited by the purchaser. The product shall be processed to the final thickness/diameter by metallurgical working operations prior to any straightening, dimensional sizing, or surface finishing operations. Bar shall not be cut from plate.

3.3.2 Forgings

Solution heat treated and descaled.

3.3.3 Stock for Forging

As ordered by the forging manufacturer (see 8.6).

3.4 Heat Treatment

Bars and forgings shall be solution heat treated by heating to a temperature within the range 1450 to 1700 °F (788 to 927 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with section thickness and the heating equipment and procedure used, and water quenched (except that sections under 0.5 inch [12.7 mm] may be air cooled). Pyrometry shall be in accordance with AMS2750.

3.5 Properties

3.5.1 Bars and Forgings as Solution Heat Treated

3.5.1.1 Tensile Properties

Shall be as specified in Table 2, determined in accordance with ASTM E8/E8M with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through the 0.2% offset yield strain.

3.5.1.1.1 Tensile property requirements apply in both the longitudinal and transverse directions. Transverse tensile properties of Table 2 apply only to product that a test specimen not less than 2.50 inches (63.5 mm) in length can be obtained.

3.5.1.1.2 Specimens for the longitudinal requirements in Table 2 shall be taken with the axis of the specimen within 15 degrees of parallel to the grain flow.

3.5.1.1.3 Yield strength and reduction of area requirements do not apply to product under 0.125 inch (3.18 mm) in nominal diameter or least distance between parallel sides.

3.5.1.1.4 Values in brackets [] apply to the short transverse direction for short transverse dimensions of 3.00 inches (76.2 mm) or greater. When short transverse properties are determined, long transverse properties do not need to be determined.

Table 2 - Minimum tensile properties (see 3.5.1.1.6)

Nominal Diameter or Least Distance Between Parallel Sides Inches (Millimeters)	Tensile Strength ksi (MPa)	Yield Strength At 0.2% Offset ksi (MPa)	Elongation in 2 Inches (50.8 mm) or 4D % (3.5.1.1.4)	Reduction of Area % (3.5.1.1.4)
Up to 1.50 (38.10), incl	125 (861)	120 (827)	10	30
Over 1.50 (38.10) to 4.00 (101.60), incl	120 (827)	115 (793)	10 [8]	25 [20]

3.5.1.1.5 Mechanical property requirements for product outside the size range covered by 1.1 shall be agreed upon between the purchaser and producer and reported per 4.4.3 (see 8.6).

3.5.1.1.6 These mechanical properties have been taken from MIL-T-9047 and have not been substantiated by AMS statistical procedures.

3.5.1.2 Microstructure

Shall be uniform and essentially that structure resulting from beta processing. Microstructure shall not be cause for rejection unless standards have been agreed upon by the purchaser and producer (see 8.6).

3.5.1.3 Surface Contamination

Except as specified in 3.5.1.3.1, the product shall be free of any oxygen-rich layer (see 8.2), such as alpha case, or other surface contamination, determined by microscopic examination at not lower than 400X magnification or by other method agreed upon by the purchaser and producer (see 8.6).

3.5.1.3.1 When permitted by the purchaser, product to be machined all over may have an oxygen-rich layer, provided such layer is removable within the machining allowance on the product.

3.5.1.4 Macrostructure

Product shall be uniform in quality and condition, homogenous, sound, and free from foreign materials and from internal imperfections detrimental to fabrication or performance of parts.

3.5.2 After Precipitation Heat Treatment

Product shall conform to the following requirements after being precipitation heat treated by heating to 875 to 1150 °F (468 to 624 °C), holding at the selected temperature within ± 15 °F (± 8 °C) for 2 to 30 hours and cooled in air to room temperature. Precipitation heat treatment shall precede final machining of specimens. Pyrometry shall be in accordance with AMS2750.

3.5.2.1 Tensile Properties

Shall be as shown in Table 3, determined in accordance with ASTM E8/E8M with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through the 0.2% offset yield strain.

3.5.2.2 Values in brackets [] apply to the short transverse direction for short transverse dimensions of 3.00 inches (76.2 mm) or greater.

Table 3 - Minimum tensile properties (see 3.5.1.1.6)

Nominal Diameter or Least Distance Between Parallel Sides Inches (mm)	Tensile Strength ksi (MPa)	Yield Strength At 0.2% Offset ksi (MPa)	Elongation in 2 Inches (50.8 mm) or 4D % (3.5.2.2)	Reduction of Area % (3.5.2.2)
Up to 1.50 (38.10), incl	190 (1310)	180 (1241)	8	15
Over 1.50 (38.10) to 3.00 (76.20), incl	180 (1241)	170 (1172)	8 [6]	15 [5]
Over 3.00 (76.20) to 4.00 (101.60), incl	170 (1172)	160 (1103)	8 [3]	15 [5]

3.5.2.3 Mechanical property requirements for product outside the size range covered by Table 3 shall be agreed upon between the purchaser and producer and reported per 4.4.3 (see 8.6).

3.5.3 Forging Stock

When a sample of stock is forged to a test coupon and heat treated as in 3.4 and/or 3.5.2, specimens taken from the heat-treated coupon shall conform to the requirements of 3.5.1.1 and 3.5.2.1, respectively. If specimens taken from the stock after heat treatment as in 3.4 and/or conform to the requirements of 3.4 and/or 3.5.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.6 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Ultrasonic Inspection

When specified, the product shall be ultrasonically inspected in accordance with AMS2631 and shall meet the quality standards agreed upon between the purchaser and producer (see 8.6).

3.7 Tolerances

Bars shall conform to all applicable requirements of AMS2241.

3.8 Production, distribution, and procurement of metal stock shall comply with AS6279.

3.9 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (see 3.1) of each heat.

4.2.1.2 Hydrogen content (see 3.1), tensile properties (see 3.5.1.1), tensile properties after precipitation hardening (see 3.5.2.1), microstructure (see 3.5.1.2), surface contamination (see 3.5.1.3), and macrostructure (see 3.5.1.4) of each lot of bars and forgings.

4.2.1.3 When specified (see 8.6), ultrasonic quality of each bar, forging or forging stock as required by 3.6.1.

4.2.1.4 Tolerances (see 3.7) of bars.

4.2.2 Periodic Tests

Ability of forging stock (see 3.5.2) to develop specified properties is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2368 and as follows; a lot shall be all product of the same nominal size from the same heat processed at the same time:

4.3.1 For Acceptance Tests

4.3.1.1 Composition

At least one sample from each heat, except that for hydrogen determinations one sample from each lot obtained after all thermal and chemical processing is completed.

4.3.1.2 Tensile Properties

At least one sample from bars from each lot. The number, location, and orientation of samples from each lot of forgings shall be as agreed upon by the purchaser and producer (see 8.6).

4.3.1.3 Macrostructure

A specimen at least 0.5 inch (12.7 mm) long by full cross section from each end of the bars selected for sampling shall be macrostructurally examined for conformance to the quality requirements. Unless otherwise specified, macrostructural examination shall be performed in accordance with AMS2643. The number of bars selected for examination shall not be less than the amounts shown in Table 4.

Table 4 - Number of bars selected for macrostructural examination

Number of Bars in Lot	Number of Bars Selected
1 to 15	1
16 to 50	2
51 to 150	3
151 to 500	5
over 500	4 + amount shown above over 500

4.4 Reports

4.4.1 The producer shall furnish with each shipment a report showing the producer's identity, country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations), results of tests for composition of each heat and for the hydrogen content, tensile properties, and surface contamination of each lot, ultrasonic quality of all product when specified, and stating that the product conforms to the other technical requirements. The report shall include the purchase order number, heat and lot numbers, AMS6920E, product form and mill produced size (and part number, if applicable), specific solution heat treatment used, specific aging treatment used to develop precipitation hardened properties, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.4.2 Report the nominal metallurgically worked cross-sectional size and the cut size, if different (see 3.3.1).

4.4.3 When material produced to this specification is beyond the sizes allowed in the scope or tables, or exceptions authorized by the purchaser are taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS6920E(EXC) because of the following exceptions:" and the specific exceptions shall be listed (see 5.1.1).

4.4.4 The producer of stock for forging shall furnish with each shipment a report showing the producer's identity, country of origin (e.g., final melt in the case of metal processed by multiple melting operations), the results of tests for composition of each heat, hydrogen content of each lot, and ultrasonic quality of all product, when specified. This report shall include the purchase order number, heat number, AMS6920E, size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AMS2368.