

Submitted for recognition as an American National Standard

Issued 1 APR 1983
Revised 1 JUL 1991
Superseding AMS 7261/2C

**RINGS, SEALING, PHOSPHONITRILIC (FZ) FLUOROELASTOMER
High-Temperature-Fluid Resistant
75 - 85**

1. SCOPE:

- 1.1 Form: This specification covers one type of phosphonitrilic (FZ) fluoroelastomer in the form of molded rings.
- 1.2 Classification: Rings having nominal hardness of 80 Durometer A, or equivalent.

2. APPLICABLE DOCUMENTS: See AMS 7261.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the sealing rings described herein shall consist of this document and the latest issue of the basic specification, AMS 7261.

3.2 Properties: Shall be as follows:

3.2.1 As Received:

- | | | |
|---------|---|-------------------------------|
| 3.2.1.1 | Hardness, Durometer "A"
or equivalent | 80 ± 5 |
| 3.2.1.2 | Tensile Strength, minimum | 900 psi
(6.21 MPa) |
| 3.2.1.3 | Elongation, minimum | 75% |
| 3.2.1.4 | Specific Gravity | Preproduction
Value ± 0.02 |
| 3.2.1.5 | Temperature Retraction
TR ₁₀ Point, maximum | -55°C
(-67°F) |

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

3.2.2 Aromatic Fuel Resistance:ASTM Reference Fuel B
(ASTM D 471)3.2.2.1 Hardness Change, Durometer
"A" or equivalent

0 to -10

Temperature: 20° - 30°C
(68° - 86°F)
Time: 22 hours ± 0.253.2.2.2 Tensile Strength Change,
maximum

-20%

3.2.2.3 Elongation Change, maximum

-15%

3.2.2.4 Volume Change

+1 to +20%

3.2.3 Synthetic Lubricant Resistance:

Medium: AMS 3021

Ø

Temperature: 150°C ± 3
(302°F ± 5)3.2.3.1 Hardness Change, Durometer
"A" or equivalent

0 to -10

Time: 70 hours ± 0.5

3.2.3.2 Tensile Strength Change,
maximum

-20%

3.2.3.3 Elongation Change, maximum

-15%

3.2.3.4 Volume Change

+1 to +20%

3.2.3.5 Compression Set, maximum

30%

3.2.3.6 Temperature Retraction
TR₁₀ Point, maximum-55°C
(-67°F)3.2.4 Dry Heat Resistance:Temperature: 175°C ± 3
(347°F ± 5)3.2.4.1 Hardness Change, Durometer
"A" or equivalent

-10 to +10

Time: 70 hours ± 0.5

3.2.4.2 Tensile Strength Change,
maximum

-20%

3.2.4.3 Elongation Change, maximum

-20%

3.2.4.4 Weight Loss, maximum

2%

3.2.4.5 Temperature Retraction
TR₁₀ Point, maximum-55°C
(-67°F)3.2.5 Compression Set:Percent of Original
Deflection, maximum3.2.5.1 After 22 hours ± 0.25 at
175°C ± 3 (347°F ± 5)

45%