



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 7261C

Issued APR 1983
Revised FEB 1995

Submitted for recognition as an American National Standard

Superseding AMS 7261B

RINGS, SEALING, PHOSPHONITRILIC (FZ) FLUORELASTOMER High-Temperature-Fluid Resistant

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of February 1995. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "B" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CE"

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AN AMERICAN NATIONAL STANDARD

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL
400 Commonwealth Drive, Warrendale, PA 15096-0001

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE

AMS 7261B

Issued 1 APR 1983
Revised 1 JUL 1991
Superseding AMS 726IA

Submitted for recognition as an American National Standard

RINGS, SEALING, PHOSPHONITRILIC (FZ) FLUOROELASTOMER
High-Temperature-Fluid Resistant

1. SCOPE:

- 1.1 Form: This specification and its associated detail specifications cover phosphonitrilic (FZ) fluoroelastomers in the form of molded rings.
- 1.2 Application: Sealing rings for use in aircraft fuel and lubricating oil systems operating from -55° to +175°C (-67° to +347°F). The cross section of such rings is usually not over 0.275 inch (6.98 mm) in diameter or thickness.
- 1.3 Safety - Hazardous Materials: While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2817 - Packaging and Identification, Preformed Packings
AMS 3021 - Fluid, Reference, for Testing Di-Ester (Polyol) Resistant
Materials

SAE Technical Board Rules provide that : "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.1.2 Aerospace Standards:

AS568 - Aerospace Size Standard for O-Rings
AS871 - Manufacturing and Inspection Standards for Preformed Packings
(O-Rings)

2.1.3 Aerospace Information Report:

AIR851 - O-Ring Tension Testing Calculations

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 471 - Rubber Property - Effect of Liquids
ASTM D 1414 - Testing Rubber O-Rings
ASTM D 2240 - Rubber Property - Durometer Hardness

2.3 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

2.3.1 Military Standards:

MIL-STD-413 - Visual Inspection Guide for Rubber O-Rings

3. TECHNICAL REQUIREMENTS:

3.1 Detail Specifications: The requirements for a specific sealing ring shall consist of all requirements specified herein in addition to requirements specified in the applicable detail specification. In case of conflict between requirements of this basic specification and an applicable detail specification, requirements of the detail specification shall govern.

3.2 Material: Shall be a compound, based on a phosphonitrilic (FZ) fluoroelastomer, suitably cured to produce rings meeting the requirements of this specification and the applicable detail specification.

3.3 Properties: Rings shall conform to the requirements of the applicable detail specification; tests shall be performed on the rings supplied and in accordance with ASTM D 1414, insofar as practicable. If the rings are unsuitable for use as test samples, tests shall be performed on samples of identical composition and comparable cure as that of the end item, preferably a -214 O-ring. Calculations of tensile strength and elongation may be made in accordance with AIR851.

3.4 Quality: Rings, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from internal imperfections detrimental to usage of the rings. Surface imperfections shall be no greater than permitted by MIL-STD-413.

3.5 Sizes and Tolerances: Shall be as specified on the drawing. Inspection for conformance to dimensional requirements shall be made in accordance with AS871. Standard sizes are as shown in AS568.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of rings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the rings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for quality (3.4) and the following requirements of the applicable detail specification are acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity, as received	3.2.1.4
Volume Change in fuel	3.2.2.4
Compression Set	3.2.5.1

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of rings to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction rings shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient rings shall be selected at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all rings of the same nominal size produced from the same batch of compound processed in one continuous series of operations and presented for vendor's inspection at one time but shall not exceed 1000 rings or 300 pounds (136 kg), whichever is the lesser mass. A lot may be packaged in smaller quantities and delivered under the basic lot approval provided lot identification is maintained.

4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.