

ADOPTION NOTICE

SAE-AMS7262, "RINGS, SEALING, ETHYLENE PROPYLENE (EPM) RUBBER PHOSPHATE ESTER HYDRAULIC FLUID RESISTANT 58 - 95", was adopted on 29-SEP-95 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Supply Center Philadelphia, ATTN: DSCP-ITAA, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Copies of this document may be purchased from the Society of Automotive Engineers 400 Commonwealth Drive Warrendale, Pennsylvania, United States, 15096-0001. <http://www.sae.org/>

Custodians:

Army - MR
Navy - AS
Air Force - 11
DLA - IS

Adopting Activity:

DLA - IS

SAENORM.COM : Click to view the full PDF of SAE-AMS7262b

FSC 5330

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Issued OCT 1981
Revised AUG 1994
Superseding AMS 7262A

Submitted for recognition as an American National Standard

RINGS, SEALING, ETHYLENE PROPYLENE (EPM) RUBBER
Phosphate Ester Hydraulic Fluid Resistant
58 - 95

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April, 1994. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "A" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CE"

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

RINGS, SEALING, ETHYLENE PROPYLENE (EPM) RUBBER
Phosphate Ester Hydraulic Fluid Resistant
85 - 95

THIS REVISION CONTAINS ONLY EDITORIAL CHANGES

1. SCOPE:

1.1 Form: This specification covers an ethylene propylene (EPM) rubber in the form of molded rings.

1.2 Application: Sealing rings for use in phosphate ester-base, fire-resistant, hydraulic fluids from -55° to +150°C (-65° to +300°F). Standard sizes are as shown in AS 568.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications, Aerospace Standards, and Aerospace Information Reports shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2817 - Packaging and Identification, Preformed Packings

2.1.2 Aerospace Standards:

AS 568 - Aerospace Size Standard for O-Rings

AS 871 - Manufacturing and Inspection Standards for Preformed Packings
(O-Rings)

2.1.3 Aerospace Information Report:

AIR 851 - O-Ring Tension Testing Calculations

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D1414 - Testing Rubber O-Rings

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a compound, based on an ethylene propylene (EPM) elastomer, suitably cured to produce sealing rings meeting the requirements of 3.2.

3.2 Properties: Rings shall conform to the following requirements; tests shall be performed on the rings supplied and in accordance with ASTM D1414, insofar as practicable. Testing for tensile strength and tensile stress is not required on rings which are too small to permit assembly on rollers and are, after cutting, too short to permit testing as a single strand. Eliminating testing for tensile strength and tensile stress does not eliminate testing for elongation; elongation test can be made by stretching a ring over a mandrel of a size which will stretch the ring sufficiently to produce the required elongation when figured on the ID of the ring. Calculations of tensile strength, elongation, and tensile stress may be made in accordance with AIR 851.

3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equiv.	90 ± 5
3.2.1.2	Tensile Strength, min	1400 psi (9.65 MPa)
3.2.1.3	Elongation, min	120%
3.2.1.4	Tensile Stress at 100% Elongation, min	800 psi (5.50 MPa)
3.2.1.5	Corrosion	Nil
3.2.1.6	Specific Gravity	Preproduction Value ±0.02

- | | | | |
|---------|---|-------------------------|--|
| 3.2.2 | <u>Phosphate Ester Fluid Resistance:</u>
(Immediate Deteriorated Properties) | Medium: | SAE Phosphate Ester Standard Test Fluid No. 1A (See 8.1) |
| 3.2.2.1 | Hardness Change, Durometer "A" or equiv. | -15 to 0 | Temperature: 125°C ± 3 (255°F ± 5) |
| 3.2.2.2 | Tensile Strength Change, max | -15% | Time: 70 hr ± 0.5 |
| 3.2.2.3 | Elongation Change, max | -15% | |
| 3.2.2.4 | Volume Change | 0 to +15% | |
| 3.2.3 | <u>Dry Heat Resistance:</u> | Temperature: | 150°C ± 3 (300°F ± 5) |
| 3.2.3.1 | Hardness Change, Durometer "A" or equiv. | 0 to +10 | Time: 70 hr ± 0.5 |
| 3.2.3.2 | Tensile Strength Change, max | -25% | |
| 3.2.3.3 | Elongation Change, max | -20% | |
| 3.2.3.4 | Rend (flat) | No cracking or checking | |
| 3.2.4 | <u>Compression Set:</u> | Temperature: | 125°C ± 3 (255°F ± 5) |
| | Percent of Original Deflection, max | 25 | Time: 70 hr ± 0.5 |
| 3.2.5 | <u>Low-Temperature Resistance:</u> | | |
| | Temperature Retraction, TR ₁₀ point, max | -44°C (-48°F) | |
- 3.3 Quality: Rings, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from internal imperfections detrimental to usage of the rings. Surface imperfections shall be no greater than permitted by AS 871 for minor defects.
- 3.4 Sizes and Tolerances: Shall be as specified on the drawing. Inspection for conformance to dimensional requirements shall be made in accordance with AS 871.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of rings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the rings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement	Reference Paragraph
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Tensile Stress, as received	3.2.1.4
Specific Gravity, as received	3.2.1.6
Volume Change in phosphate ester	3.2.2.4
Compression Set	3.2.4

4.2.2 Periodic Tests: Tests to determine conformance to the following requirements are classified as periodic tests and shall be performed at a frequency selected by vendor unless frequency of testing is specified by purchaser:

Requirement	Reference Paragraph
Corrosion, as received	3.2.1.5
Tensile Strength Change in phosphate ester	3.2.2.2
Elongation Change in phosphate ester	3.2.2.3
Hardness Change after dry heat exposure	3.2.3.1
Bend after dry heat exposure	3.2.3.4
Low Temperature Resistance, (TR ₁₀ point)	3.2.5

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of rings to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient rings shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.