

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 7295/2B

Issued APR 1978
Revised APR 1993
Noncurrent JUL 1998

Superseding AMS 7295/2A

Radiographic Film 5-60

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July 1998. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each "NONCURRENT" specification is available from SAE upon request.

SAENORM.COM : Click to view the full PDF of AMS 7295-2B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7154
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:**1.1 Form:**

This specification covers one type of high-contrast, medium-grain radiographic film in the form of cut sheets or rolls.

1.2 Application:

This film will provide a radiographic quality level of 1-2T sensitivity when properly utilized, (See AMS 7295).

1.3 Classification:

High contrast with gradient of 5.0 or better and exhibiting resolution of 40 to 79 lines per millimeter.

2. APPLICABLE DOCUMENTS:

See AMS 7295.

3. TECHNICAL REQUIREMENTS:**3.1 Basic Specification:**

The complete requirements for film described herein and its procurement shall consist of this document and the latest issue of the basic specification, AMS 7295.

3.1.1 Definition: Properties shall be as defined in AMS 7295.**3.2 Properties of Radiographic Film:****3.2.1 Thickness:** Shall be 0.007 inch $\pm$ 0.001 (0.18 mm $\pm$ 0.03).**3.2.2 Net Optical Density:** Shall be not greater than 0.30 H&D units.**3.2.3 Gradient or Contrast:** Shall be 5.0 or greater at 1.5 to 3.5 H&D units.**3.2.4 Resolution:** Shall be medium, showing 40 to 79 lines per millimeter.**4. QUALITY ASSURANCE PROVISIONS:**

See AMS 7295.

5. PREPARATION FOR DELIVERY:

See AMS 7295.