

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 7473B

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 8-15-55
Revised 6-30-60

BOLTS AND SCREWS, ROLL THREADED

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: High quality bolts and screws of steel or heat and corrosion resistant alloys for special purposes. Parts of corrosion and heat resistant steels and alloys are generally for use at temperatures over 700 F where stresses are low. Parts of AMS 5061 are generally for use at temperatures up to 800 F where stresses are low. Parts of AMS 5624 or AMS 5625 are generally for use at lower temperatures when high expansion is required.
3. MATERIAL: Shall be as specified on drawing.
4. FABRICATION:
 - 4.1 Blanks: Heads shall be formed by cold upsetting or machining.
 - 4.1.1 The metal removed from the bearing surface of the head of upset-head parts shall be as little as practicable to obtain a clean, smooth surface.
 - 4.2 Thread Rolling: Threads shall be formed on the finished blanks by a single rolling.
 - 4.3 Cleaning: Parts of corrosion resistant steels and alloys, after finishing, shall be degreased and then immersed for not less than 20 min. in a solution of 1 volume of nitric acid (sp gr 1.42) and 9 volumes of water at room temperature. Parts of AMS 5061, AMS 5624, AMS 5625, and other carbon or low alloy steels shall not be so treated.
5. TECHNICAL REQUIREMENTS:
 - 5.1 Flow Lines: Flow lines of upset heads shall conform to the general arrangement shown in Figure 1A, 1B, or 1C. The intersection of the longitudinal axis of the part and the approximate transverse axis of the flow lines shall be not less than $D/4$ in. from the bearing surface for hexagonal, round, and square head bolts and screws and not less than $D/7$ in. from the bearing surface for 12 point head bolts and screws where D is the nominal diameter of the shank after heading.
 - 5.1.1 Examination for Internal Defects: Visual examination of a longitudinal section of a head and $1/4$ in. or more of the shank, after etching in suitable etchant, shall reveal no cracks, laps, or porosity.
 - 5.2 Threads:
 - 5.2.1 Flow lines at threads shall be continuous, shall follow the general thread contour, and shall be of maximum density at root of thread (see Figure 2).

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no attempt to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.2.2 Root defects such as notches, slivers, folds, roughness, or oxide scale are not permitted (see Figure 3).
∅
- 5.2.3 Multiple laps on the sides of threads are not permissible regardless of location. Single laps on the sides of threads that extend toward the root are not permissible (see Figures 4 and 5).
∅
- 5.2.4 A single lap is permissible along the side of the thread below the pitch diameter on the non-pressure side provided the lap does not originate closer than 20% of the basic thread height from the root and extends toward the crest and generally parallel to the side (see Figure 6). A single lap is permissible along the side of the thread above the pitch diameter on either the pressure or non-pressure side (one lap per thread) provided it extends toward the crest and generally parallel to the side (see Figure 7). Basic thread height is defined as being equivalent to 0.650 times the pitch (see Table I).
∅
- 5.2.5 Crest craters, crest laps, or a crest lap in combination with a crest crater are permissible, provided the imperfection does not extend deeper than 20% of the basic thread height (see Table I) as measured from the thread crest when the thread major diameter is at minimum size (see Figure 8). The major diameter of the thread shall be measured prior to sectioning. As the major diameter of the thread approaches maximum size, values for crest crater or crest lap imperfections listed in Table I may be increased by 1/2 the difference between the minimum major diameter and the actual major diameter as measured on the part.
∅
- 5.2.6 Slight deviations from thread contour are permissible at the crest of the thread within the major diameter limits as shown in Figure 9 and at the incomplete thread at each end of the threaded section.
∅
- 5.2.7 Parts having holes for locking devices are permitted to have slight ovalization of the hole and the countersink and slight flattening of the crest of the thread at the countersink, provided the diameter of the hole is within specified tolerances.
∅
- 5.2.8 Parts shall have a minimum thread run-out of one thread and a maximum of two threads. The run-out shall fair onto the shank eliminating any abrupt change in cross sectional area. Bottom and sides of threads contained in run-out shall be filleted, smooth, and devoid of abrupt tool stop marks.
∅
- 5.2.9 All thread elements shall be within specified limits starting at a length 2 times the pitch from the end, including chamfer, and extending for the specified full thread length.
- 5.3 Straightness, Concentricity, and Squareness: For purposes of these inspections, shank and threads shall be included but shall be considered as separate elements of the bolt.
- 5.3.1 Straightness of Shank and Threads: Shank and threads shall be straight within the limits specified on the drawing for the total length (L) of the bolt under the head (see Figure 10). Visibly abrupt changes in diameter or shape of the shank and threads which might cause stress concentrations are not permissible.

- 5.3.2 Concentricity of Thread Pitch Diameter: The concentricity of thread pitch diameter in relation to shank diameter shall be within the limits specified on the drawing for a distance of not less than 1.5 times the nominal bolt diameter away from the last full thread along the shank (see Figure 11). For bolts having a shank length less than 1.5 times the nominal bolt diameter the concentricity of the shank diameter over its full length in relation to the thread pitch diameter shall be within the limits specified on the drawing.
- 5.3.3 Concentricity of Head: The concentricity of the head in relation to the shank diameter shall be within the limits specified on the drawing for a distance of not less than 1.5 times the nominal bolt diameter away from the washer face along the shank (see Figure 12). For bolts threaded to the head and for bolts having shank length less than 1.5 times the nominal bolt diameter, concentricity of head shall be measured in relation to thread pitch diameter in lieu of shank diameter.
- 5.3.4 Squareness of Washer Face: The squareness of the washer face with the shank diameter shall be within the limits specified on the drawing for a distance of not less than 1.5 times the nominal bolt diameter away from the washer face along the shank (see Figure 12). For bolts threaded to the head and for bolts having a shank length less than 1.5 times the nominal bolt diameter, squareness of washer face shall be measured in relation to thread pitch diameter in lieu of shank diameter.
6. QUALITY: Parts shall be uniform in quality and condition, clean, sound, smooth, and free from burrs and foreign materials and from internal and external imperfections detrimental to their performance.
- 6.1 Parts subject to fluorescent penetrant inspection shall conform to the following \emptyset standards:
- 6.1.1 \emptyset Discontinuities transverse to grainflow such as pipes, grinding checks, and quench cracks shall be cause for rejection.
- 6.1.2 \emptyset Longitudinal indications of surface seams and forming laps parallel to grainflow are acceptable within the following limits, provided the separation between indications is not less than 1/16 in. in all directions.
- 6.1.2.1 \emptyset Sides of Head: A maximum of 3 surface indications is permitted and the length of each indication may be the full height of the surface. No indication shall break over either edge to a depth greater than 1/32 in. or the equivalent of the basic thread height (see Table I), whichever is less.
- 6.1.2.2 \emptyset Top of Head and End of Stem: A maximum of 3 surface indications in each area is permitted provided the length or diameter of any individual indication does not exceed 1/32 in. or the equivalent of the basic thread height (see Table I), whichever is less.
- 6.1.2.3 \emptyset Shank or Stem: A maximum of 5 indications is permitted. The length of any indication may be the full length of the surface but the total length of all indications shall not exceed twice the length of the surface. No indication shall break into a fillet or over an edge.
- 6.1.2.4 Threads: Shall not reveal indications of cracks, seams, pipes, or rolling laps as shown by Figures 3, 4, and 5 except that indications of slight laps as shown by Figures 6, 7, and 8 will be permitted.

- 6.2 Parts subject to magnetic particle inspection shall conform to the following
∅ standards.
- 6.2.1 Discontinuities transverse to grainflow such as pipes, grinding checks, and
∅ quench cracks shall be cause for rejection.
- 6.2.2 Longitudinal indications of seams, forming laps, and nonmetallic inclusions
∅ parallel to grainflow are acceptable within the following limits, provided
the separation between indications is not less than 1/16 in. in all directions.
- 6.2.2.1 Sides of Head: A maximum of 6 surface or subsurface indications per head
∅ is permitted and the length of each indication may be the full height of
the surface. No indication shall break over either edge to a depth greater
than 1/32 in. or the equivalent of the basic thread height (see Table I),
whichever is less.
- 6.2.2.2 Top of Head and End of Stem: A maximum of 6 surface or subsurface indica-
∅ tions in each area is permitted provided the length or diameter of any
individual indication does not exceed 1/32 in. or the equivalent of the basic
thread height (see Table I), whichever is less.
- 6.2.2.3 Shank or Stem: A maximum of 10 subsurface and hairline surface indications
∅ is permitted. The length of any indication may be the full length of the
surface but the total length of all indications shall not exceed twice the
length of the surface. No indication shall break into a fillet or over an
edge.
- 6.2.2.4 Threads: Threads shall not reveal indications of cracks, seams, pipes, or
∅ rolling laps as shown by Figures 3, 4, and 5 except that indications of
slight laps as shown by Figures 6, 7, and 8 will be permitted.
- 6.2.3 Any method of magnetic particle inspection may be used to determine conformance
∅ of the parts to the above requirements, but resolution of disputed rejections
shall be based upon the wet, residual black oxide suspension method using
amperages shown in 6.2.3.1 and 6.2.3.2.
- 6.2.3.1 Circular Magnetization: 800 - 1000 amp per sq in. of contact area passed
∅ through the part longitudinally.
- 6.2.3.2 Longitudinal Magnetization: Sufficient to produce 5000 amp-turns per inch
∅ of shank diameter with the part placed in a standard solenoid of appropriate
size.
7. REJECTIONS: Parts not conforming to this specification or to authorized
modifications will be subject to rejection.





FIGURE 2
FLOW LINES
ROLLED THREAD




FIGURE 3
ROLLED THREAD




FIGURE 4
ROLLED THREAD







FIGURE 5
ROLLED THREAD



∅ FIGURE 6
ROLLED THREAD



∅ FIGURE 7
ROLLED THREAD



NOTE A: DEPTH OF DEFECT EQUALS 20% OF BASIC THREAD HEIGHT PLUS 1/2 THE DIFFERENCE OF THE ACTUAL MAJOR DIAMETER AND MINIMUM MAJOR DIAMETER.

∅ FIGURE 8
ROLLED THREAD




FIGURE 9
ROLLED THREAD