



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc. SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENOALE, PA. 15096

AMS 7510/2

Issued 1-15-77

Revised

MAGNETS, RARE-EARTH/COBALT, PERMANENT Samarium/Cobalt, 33/67 - 18 (143) 250

1. SCOPE:

- 1.1 **Form:** This specification covers one type of samarium/cobalt permanent magnet.
- 1.2 **Application:** Primarily for components of electrical, electronic, and magnetic devices requiring an energy level of 18 MGOe (143 kT·A/m) for use at service temperatures up to 250°C.
- 1.3 **Classification:** Nominal composition of 33% samarium and 67% cobalt with an energy level of 18 MGOe (143 kT·A/m) with 250°C maximum service rating.

2. APPLICABLE DOCUMENTS: Shall be as shown in AMS 7510.

3. TECHNICAL REQUIREMENTS:

- 3.1 **Basic Specification:** The complete requirements for procuring the magnets described herein shall consist of this document and the latest issue of the basic specification, AMS 7510.
- 3.2 **Composition:** Shall be nominally 33% samarium and 67% cobalt. Composition variations will be permitted if the magnetic properties are met.
- 3.3 **Condition:** Shall be unmagnetized, unless otherwise ordered.

3.4 Magnetic Characteristics: Hysteresis data, determined at 25°C ± 5, shall be as follows:

3.4.1	Required magnetizing field, H _S , min	15 kOe	1194 kA/m
3.4.2	Energy product level, (BH) _m , nominal	18 MGOe	143 kT·A/m
3.4.3	Residual flux density (induction), B _r	8.3 - 8.8 kG	0.83 - 0.88 T
3.4.4	Induction coercive force, H _c	7.8 - 8.2 kOe	621 - 652 kA/m
3.4.5	Intrinsic coercive force, H _{ci} , min	16 kOe	1273 kA/m

3.5 Permanent Magnet Performance as a Function of Temperature: Shall be as follows:

3.5.1 Reversible coefficient, nominal, when B/H = 1.0:

25° to 100°	0.040% per deg C
25° to 250°C	0.048% per deg C

3.5.2 Irreversible loss after exposure to temperature noted, nominal

100°C, when B/H = 1.0	0.8%
100°C, when B/H = 0.25	1.8%
250°C, when B/H = 1.0	3.0%
250°C, when B/H = 0.25	10.0%

SAE Technical Board rules provide that: "All technical reports, including standards applications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."