

MAGNETIC ALLOY SHEET AND STRIP
Nickel-Iron Alloy
Annealed

1. SCOPE:

- 1.1 Form: This specification covers two types of magnetic nickel-iron alloy in the form of sheet and strip.
- 1.2 Application: Primarily for parts used in magnetic circuits requiring high magnetic permeability at low flux densities after high temperature annealing in hydrogen.
- 1.3 Classification: The magnetic alloys covered by this specification are classified as follows:
- Type 1 - Nickel plus iron and other alloying elements, usually copper and chromium. Type 1 may be required for applications involving severe forming.
- Type 2 - Nickel plus iron and other alloying elements, usually copper and molybdenum.
- 1.3.1 Unless a specific type is specified, either type may be supplied.
2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

MAM 2262 - Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A596 - Direct-Current Magnetic Properties of Materials Using Ring Test Procedures and the Ballistic Methods

ASTM A773 - D-C Magnetic Properties of Materials Using Ring and Permeameter Procedures with D-C Electronic Hysteresigraphs.

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Labor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall be an alloy containing approximately 80% nickel plus iron and other alloying elements (See 1.3) in such proportions as required to provide a product meeting the requirements of 3.3.

3.2 Condition: Hot rolled with or without subsequent cold reduction, annealed, \emptyset and descaled, having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish (See 8.2).

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Hardness: Shall be not higher than 75 HRB, or equivalent, determined in accordance with ASTM E18.

3.3.2 Magnetic Properties: Shall be as follows, determined in accordance with \emptyset ASTM A596 or ASTM A773 on specimens annealed by heating to $2150^{\circ}\text{F} \pm 25$ ($1177^{\circ}\text{C} \pm 14$) in a non-contaminating atmosphere having a dew point of -60°F (-51°C) or lower, holding at heat for 4 hours ± 0.25 , and cooling in a non-oxidizing atmosphere at a rate not greater than 100 F (56 C) degrees per hour to 800°F (427°C) or lower or at a cooling rate recommended by the alloy producer.

- 3.3.2.1 Maximum permeability, minimum 250,000
- 3.3.2.2 Permeability at 100 gauss (0.01T), minimum 70,000
- 3.3.2.3 Induction at 100 Oersteds, minimum 7,500 gauss (0.75T)
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2262 or MAM 2262.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with AMS 2371 and the following; a lot shall be all product of the same nominal thickness from the same heat of alloy:
- 4.3.1 Samples for magnetic properties testing shall be selected in accordance with one of the following methods; the sampling method used shall be reported with the test results:
- 4.3.1.1 A pilot sample nominally 0.014 inch (0.36 mm) thick from each heat of alloy.
- 4.3.1.2 At least one sample selected at random from each lot.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of test for hardness of each lot and the magnetic properties of each heat. This report shall include the purchase order number, heat number, AMS 7701B, cooling rate if other than 100 F (55 C) degrees per hour, method of sampling for magnetic tests, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 7701B, contractor or other direct supplier of product, part number, and quantity. When product for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of product to determine conformance to the requirements of this specification and shall include in the report either a statement that the product conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as in 5.1.1 unless purchaser permits a method from 5.1.2.

5.1.1 Each sheet and strip shall be marked on one face, in the respective location indicated below, with AMS 7701B, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

5.1.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.1.2 Flat Sheet and Flat Strip Over 6 Inches (152 mm) in Width: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.1. When the product is wound on cores, the tag or label may be attached to the core.

5.1.2 When purchaser permits, each sheet and strip may be marked near one end, coils being marked near the outside end, with AMS 7701B, heat number, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternate method, individual pieces and bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

5.2 Packaging:

5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.