

# AEROSPACE MATERIAL SPECIFICATION

**SAE** AMS7726

REV. G

Issued	1962-01
Revised	2000-07
Noncurrent	2006-05
Reaf Nonc	2012-04

Superseding AMS7726F

Iron-Nickel-Cobalt Alloy, Wire  
53Fe - 29Ni - 17Co  
Low Expansion, Glass Sealing, Annealed

K94610

## RATIONALE

AMS7726G has been reaffirmed to comply with the SAE five-year review policy.

## NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of May, 2006. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those specifications which have previously been widely used and which may be required for production or processing of existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs. "NONCURRENT" specifications are available from SAE upon request.

Similar but not necessarily identical products are covered in the following specifications. However, this listing is provided for information only and does not constitute authority to substitute these specifications for the "NONCURRENT" specification.

ASTM F 15, Iron-Nickel-Cobalt Sealing Alloy

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:   Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
SAE WEB ADDRESS:               http://www.sae.org

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS7726G>**

## 1. SCOPE:

### 1.1 Form:

This specification covers a low-expansion iron-nickel-cobalt alloy in the form of wire.

### 1.2 Application:

This wire has been used typically for the fabrication of lead wires and other electronic elements to be sealed to hard glasses during the assembly of electronic components, but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys

### 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 112 Determining the Average Grain Size

ASTM E 228 Linear Thermal Expansion of Solid Materials with a Vitreous Silica Dilatometer

ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall be approximately 53% iron, 29% nickel, and 17% cobalt by weight with residual elements not exceeding the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition, Residual Elements

Element	min	max
Carbon	--	0.04
Manganese	--	0.50
Silicon	--	0.20
Chromium	--	0.20
Molybdenum	--	0.20
Copper	--	0.20
Titanium	--	0.10
Aluminum	--	0.10
Magnesium	--	0.10
Zirconium	--	0.10
Sum of Ti + Al + Mg + Zr	--	0.20

### 3.2 Condition:

Cold drawn and bright annealed.

### 3.3 Properties:

Wire shall conform to the following requirements:

#### 3.3.1 As Received:

3.3.1.1 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

3.3.1.2 Hardness: Shall be not higher than 82 HRB, or equivalent (See 8.2), determined in accordance with ASTM E 18.

3.3.1.3 Glass Seal Test: Wire shall produce, with Corning Glass 7052 or equivalent, a glass-to-metal seal free from bubbles at the interface. The interface shall be free from cracks after immersion and stabilized in a mixture of dry ice and acetone maintained at  $-80\text{ }^{\circ}\text{C} \pm 2$  ( $-112\text{ }^{\circ}\text{F} \pm 4$ ). Annealing of the glass to relieve stresses after the sealing operation is permissible.

3.3.2 After Reannealing: Specimens to determine conformance to the following requirements shall be reannealed by heating in hydrogen atmosphere to  $900\text{ }^{\circ}\text{C} \pm 15$  ( $1652\text{ }^{\circ}\text{F} \pm 27$ ), holding at heat for 60 minutes  $\pm 5$ , further heating to  $1100\text{ }^{\circ}\text{C} \pm 15$  ( $2012\text{ }^{\circ}\text{F} \pm 27$ ), holding at heat for 15 minutes  $\pm 3$ , cooling from  $1100\text{ }^{\circ}\text{C} \pm 15$  ( $2012\text{ }^{\circ}\text{F} \pm 27$ ) to  $200\text{ }^{\circ}\text{C}$  ( $392\text{ }^{\circ}\text{F}$ ) or below in the hydrogen atmosphere at a rate not greater than  $5\text{ }^{\circ}\text{C}$  ( $9\text{ }^{\circ}\text{F}$ ) per minute, and air cooling to room temperature; specimens may be cooled to room temperature between the  $900\text{ }^{\circ}\text{C}$  ( $1652\text{ }^{\circ}\text{F}$ ) and  $1100\text{ }^{\circ}\text{C}$  ( $2012\text{ }^{\circ}\text{F}$ ) heating periods.

- 3.3.2.1 Coefficient of Thermal Expansion: Shall be as shown in Table 2, determined in accordance with ASTM E 228.

TABLE 2A - Linear Coefficient of Thermal Expansion, Inch/Pound Units

Temperature Range	Average Linear Coefficient of Thermal Expansion
	Inch/Inch/ per Degree Fahrenheit
86 to 752 °F	2.56 to 2.89 x 10 <sup>-6</sup>
86 to 842 °F	2.83 to 3.06 x 10 <sup>-6</sup>

TABLE 2B - Linear Coefficient of Thermal Expansion, SI Units

Temperature Range	Average Linear Coefficient of Thermal Expansion
	mm/mm per Degree Celsius
30 to 400 °C	4.60 to 5.20 x 10 <sup>-6</sup>
30 to 450 °C	5.10 to 5.50 x 10 <sup>-6</sup>

- 3.3.2.2 Temperature of Transformation: The temperature of transformation from gamma to alpha phase shall be not higher than -78 °C (-108 °F), determined by metallographic examination after cold soaking for not less than four hours.

#### 3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the wire.

## 3.5 Tolerances:

Shall conform to the following:

## 3.5.1 Diameter or Thickness: Shall be as shown in Table 3.

TABLE 3A - Diameter or Thickness Tolerances, Inch/Pound Units

Nominal Diameter or Distance Between Parallel Sides Inch	Tolerance, Inch Plus and Minus
0.002 to 0.0043, incl	0.0002
Over 0.0043 to 0.0079, incl	0.00025
Over 0.0079 to 0.0149, incl	0.0003
Over 0.0149 to 0.0199, incl	0.0004
Over 0.0199 to 0.0309, incl	0.0005
Over 0.0309 to 0.0409, incl	0.0006
Over 0.0409 to 0.0609, incl	0.0007
Over 0.0609 to 0.0809, incl	0.0008
Over 0.0809 to 0.1259, incl	0.0010
Over 0.1259 to 0.1569, incl	0.0015
Over 0.1569 to 0.250, incl	0.0020

TABLE 3B - Diameter or Thickness Tolerances SI Units

Nominal Diameter or Distance Between Parallel Sides Millimeters	Tolerance Millimeter Plus and Minus
0.05 to 0.109, incl	0.005
Over 0.109 to 0.201, incl	0.0064
Over 0.201 to 0.378, incl	0.008
Over 0.378 to 0.505, incl	0.010
Over 0.505 to 0.785, incl	0.013
Over 0.785 to 1.039, incl	0.015
Over 1.039 to 1.547, incl	0.018
Over 1.547 to 2.055, incl	0.020
Over 2.055 to 3.198, incl	0.025
Over 3.198 to 3.985, incl	0.038
Over 3.985 to 6.35, incl	0.051