



AEROSPACE MATERIAL SPECIFICATION

AMS 7732

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

Issued 11-1-70
Revised

STEEL WIRE, COPPER CLAD 99Fe For Electronic Applications

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Round wire clad with copper.
3. **APPLICATION:** Primarily for parts where essentially nonmagnetic properties are required.
4. **COMPOSITION:**

4.1 **Basis Wire (Core):**

	min	max
Carbon	--	0.08
Manganese	0.25 -	0.40
Phosphorus	--	0.04
Sulphur	--	0.05

- 4.1.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Carbon Steel, Wire Other Than Flat".
- 4.2 **Cladding (Sheath):** Shall be Electrolytic copper (99.90% min copper) conforming to ASTM B5.
5. **CONDITION:** Cold drawn or rolled, annealed, cleaned, clad, and annealed.
6. **TECHNICAL REQUIREMENTS:**
 - 6.1 **Cladding (Sheath) Thickness:** The weight of the completed core-and-sheath cross-section shall be 27 - 35% copper by weight. At any cross-section, the maximum thickness of the sheath shall not exceed twice the minimum thickness of the sheath.
 - 6.2 **Tensile Strength:** Shall be 50,000 - 100,000 psi, determined in accordance with the issue of ASTM E8 listed in the latest issue of AMS 2350.
 - 6.3 **Bending:** Finished wire shall be capable of withstanding bending at room temperature through an angle of 180 deg around a diameter equal to the nominal diameter of the wire without indication of cracking or of separation of the cladding (sheath) from the basis wire when examined under a magnification of 10X.
7. **QUALITY:** Material shall be uniform in quality, condition, temper, and cross section. Surfaces shall be free from scale, corrosion, cracks, seams, scratches, slivers, dirt, grease, oil, streaks, stains, pit marks, burns, dents, blisters, laps, grooves, inclusions, and other imperfections detrimental to fabrication or to performance of parts; magnification up to 30X may be used to determine compliance.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."