

**AEROSPACE  
MATERIAL  
SPECIFICATION**



**AMS 7878C**

Issued	MAY 1971
Revised	APR 1987
Reaffirmed	APR 1992
Noncurrent	MAR 1994
Cancelled	AUG 2002
Superseding	AMS 7878B

**Tungsten Carbide Powder  
Cobalt Coated**

**CANCELLATION NOTICE**

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of August 16, 2002. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 7878C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2002 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

**QUESTIONS REGARDING THIS DOCUMENT:**  
**TO PLACE A DOCUMENT ORDER:**  
**SAE WEB ADDRESS:**

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

**FAX: (724) 776-0243**  
**FAX: (724) 776-0790**

**1. SCOPE:****1.1 Form:**

This specification covers cobalt-coated tungsten carbide in the form of powder.

**1.2 Application:**

Primarily for producing plasma spray coatings to provide wear and fretting resistant surfaces.

**2. APPLICABLE DOCUMENTS:**

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

AMS 2350 Standards and Test Methods

**2.2 ASTM Publications:**

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM B214 Sieve Analysis of Granular Metal Powders

ASTM B215 Sampling Finished Lots of Metal Powders

**2.3 U.S. Government Publications:**

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

**2.3.1 Military Standards:**

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Power particles shall consist of a tungsten carbide core enclosed in a cobalt jacket. Composition shall conform to the following percentages by weight, determined by methods agreed upon by purchaser and vendor:

	min	max
Free Carbon (3.1.1)	--	0.03
Combined Carbon	6.12	6.15
Total Carbon	6.12	6.18
Cobalt	10.50	13.50
Iron	--	0.05
Other Impurities, each (3.1.1)	--	0.01
Other Impurities, total (3.1.1)	--	0.15
Tungsten	remainder	

3.1.1 Determination not required for routine acceptance.

## 3.2 Condition:

As manufactured.

## 3.3 Properties:

Powder shall conform to the following requirements:

3.3.1 Particle Size Distribution: Powder shall be supplied with the following particle size distribution. Sieve analysis shall be conducted in accordance with ASTM B214; subsieve (micron) analysis shall be conducted in accordance with a method approved by purchaser.

Mesh or Micron Size*	% By Weight	
	min	max
-270 mesh (46 $\mu$ m)	100.0	--
+325 mesh (45 $\mu$ m)	--	0.5
- 30 $\mu$ m	80.0	--
- 20 $\mu$ m	--	20

\* + indicates retained on sieve

- indicates passing through sieve

3.3.2 Plasma Spraying: Powder shall produce acceptable spray coatings; standards for acceptance and method of test shall be as agreed upon by purchaser and vendor.

3.4 Quality:

Powder, as received by purchaser, shall be thoroughly blended, uniform in color and quality, dry, and free from foreign materials and from imperfections detrimental to its spraying qualities.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of powder shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the powder conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and as preproduction tests and shall be performed prior to or on the initial shipment of powder to a purchaser, on each lot, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be in accordance with ASTM B215; sufficient powder shall be taken from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3 and the report of 4.5.1 shall state that such plan was used.

4.4 Approval:

4.4.1 Sample powder shall be approved by purchaser before powder for production use is supplied, unless such approval be waived by purchaser. Results of tests on production powder shall be essentially equivalent to those on the approved sample.