

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 7911

Issued

APR 1995

Submitted for recognition as an American National Standard

ALUMINUM BERYLLIUM, PREFORMS Hot Isostatic Pressed 38Al - 62Be

1. SCOPE:

1.1 Form:

This specification covers aluminum and beryllium powders consolidated by hot isostatic pressing (HIP) into the form of bar, rod, tubing, and shapes. (See 8.1.)

1.2 Application:

These preforms have been used typically for parts requiring high thermal conductivity, low density, and high modulus of elasticity, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.3.1 WARNING; Beryllium Alloy: Inhalation of dust or fumes may cause serious chronic lung disease. Potential cancer hazard based principally on animal tests.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions

AMS 7911

SAE

AMS 7911

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steel and Heat and Corrosion Resistant Steels and Alloys

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 311 Density of Cemented Carbides

ASTM E 8 Tension Testing of Metallic Materials

ASTM E 8M Tension Testing of Metallic Materials (Metric)

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

2.4 ANSI Publications:

Available from American National Standards Institute, Inc., 11 West 42nd Street, New York, NY 10036-8002.

ANSI B46.1 Surface Texture

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1; beryllium shall be determined by wet analysis (titration), oxygen by inert gas fusion, and other elements by spectrochemical methods or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Aluminum (3.1.1)	36.0	40.0
Beryllium	60.0	64.0
Oxygen	--	1.0
Carbon (3.1.2)	--	0.1
Other Metallics, each (3.1.2)	--	0.2

AMS 7911

SAE

AMS 7911

3.1.1 Aluminum content by difference.

3.1.2 Not required for routine analysis.

3.2 Condition:

Hot isostatically pressed (HIP) with subsequent stress relief heat treatment (See 8.2).

3.2.1 Surface Finish: The product shall be furnished with a machined surface. The standard surface finish shall be no greater than 110 Ra (3.2 μm), determined in accordance with ANSI B46.1.

3.3 Properties:

The product shall conform to the following requirements.

3.3.1 Tensile Properties: Shall be as shown in Table 2, determined at room temperature in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	38.0 ksi (262 MPa)
Yield Strength at 0.2% Offset	28.0 ksi (193 MPa)
Elongation in 1 inch (25.4 mm)	2%

3.3.2 Density: Shall be within the range of 2.071 to 2.122 g/cm^3 (0.0748 to 0.0767 lb/in^3), determined using a water displacement method in accordance with ASTM B 311 except that measurement shall be made on the product, not on a sample. If the product is shipped in the HIP and subsequent stress relief condition, density shall be determined after complete heat treatment.

3.4 Quality:

Preforms, as received by purchaser, shall be uniform in quality and condition and shall be free from imperfections detrimental to usage of the preforms.

3.5 Tolerances:

Shall conform to the dimensional tolerances shown in Table 3. (See 8.3.)

AMS 7911

SAE

AMS 7911

TABLE 3A - Dimensional Tolerances, Inch/Pound Units

Dimension	Inches	Tolerance Inch plus only
Diameter, Width, or Thickness	0.15 to 3, incl	0.015
Diameter, Width, or Thickness	Over 3 to 20, incl	0.062
Diameter, Width, or Thickness	Over 20	0.250
Length	Up to 20, incl	0.125
Length	Over 20	0.250

TABLE 3B - Dimensional Tolerances, SI Units

Dimension	Millimeters	Tolerance Millimeters plus only
Diameter, Width, or Thickness	3.8 to 76, incl	0.38
Diameter, Width, or Thickness	Over 76 to 508, incl	1.57
Diameter, Width, or Thickness	Over 508	6.35
Length	Up to 508, incl	3.18
Length	Over 508	6.35

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing:

Shall be in accordance with the following: a lot shall consist of all preforms manufactured from a specific powder blend and HIP cycle in the same condition. Mechanical properties may be determined from a sample shape (component) or from material produced as an integral part (prolongation) of a shape (component) from the lot.

4.3.1 Composition: One or more samples from each powder blend. Chemical analysis shall be performed on a powder blend basis.